



DATA SHEET NO. 3583-000

## SEAL CURE™/25 Curing and Sealing Compound (VOC-Compliant)

### DESCRIPTION

SEAL CURE/25 is an economical, high solids formulation of acrylic polymers and a quick-evaporating solvent. When applied on freshly placed concrete surfaces, the product forms a tough, uniform, moisture-retentive film for simultaneous curing and sealing. SEAL CURE/25 meets the 350 g/L VOC limit for concrete curing compounds.

### USES

SEAL CURE/25 is ideal for curing and sealing newly placed concrete, vertical or horizontal applications, when a high solids and high water retentive seal, yielding superior curing efficiency, is desired.

SEAL CURE/25 is suitable for commercial and industrial applications such as sidewalks, patios, driveways, and multi-level parking decks. It provides a durable finish that increases resistance to chemicals, oils, grease, de-icing salts, and abrasion.

For interior applications, specify and apply VOCOMP®-20, VOCOMP-25, or VOCOMP-30 curing and sealing compound from W. R. MEADOWS.

### FEATURES/BENEFITS

- Non-yellowing.
- Permeable film allows moisture in cured concrete to evaporate.
- Can be used on coloured/decorative concrete.
- Retains mix water in concrete to permit complete hydration of the cement paste for hard, dense concrete.
- Helps minimize hair-checking, thermal cracking, dusting, and other defects.
- Excellent moisture retention properties.
- Can be recoated after thorough cleaning of the existing surface.

### PACKAGING

18.9 litre pails, 205 litre drums

### COVERAGE

7.35 – 14.7 m<sup>2</sup> per litre (300 – 600 ft.<sup>2</sup>/U.S. gallon)  
Coverage is approximate and depends on the porosity of the surface.

### SPECIFICATIONS

- ASTM C 309, Type 1, Class A & B
- ASTM C 1315 Type 1, Class A
- AASHTO M 148, Type 1, Class B
- Complies with Canada VOC Concentration Limits for Architectural Coatings Regulations

### APPLICATION

**Surface Preparation ...** Apply as soon as all surface water has disappeared and the concrete surface will not be marred by walking workers. Surface to receive sealer must be dry and free of contaminants. Remove all stains or discolourations.

**Application Method ...** Apply using low-pressure sprayer. An 80° fan pattern spray tip rated at 1.8 L (1.0 gpm) provides an excellent even coating. Please contact sprayer manufacturer to ensure suitability of sprayer with product.

Product should not be applied during high temperature conditions in direct sunlight. These conditions cause rapid evaporation, which does not allow the film to form properly. Under these conditions, the film may peel, bubble, and/or turn white (blush).

Apply product as soon as all surface water has disappeared and the concrete surface will not be marred by walking workmen. Apply evenly over entire surface; avoid puddling in low areas. Restrict foot traffic for at least four hours. Twelve hours is preferred.

Product should not be applied to concrete containing excessive moisture. Entrapped moisture in a solvent-based sealer may cause the film to peel and/or turn white (blush).

Continued over ....

**W. R. MEADOWS OF CANADA**  
70 Hannant Court, Milton, ON L9T 5C1  
Phone: (905) 878-4122 • Fax: (905) 878-4125  
Montreal Sales: (877) 405-5186

Hampshire, IL / Cartersville, GA / York, PA / Fort Worth, TX  
Benicia, CA / Pomona, CA / Goodyear, AZ / Milton, ON /  
St. Albert, AB  
[www.wrmeadows.com](http://www.wrmeadows.com)

Additional coats may be applied once a previous coat has dried.

For optimum protection, apply a further coating of the product and/or apply a coating of HIAC™, or HIAC-PLUS  
Note: Concrete must be a minimum of seven days old prior to the application of HIAC or HIAC-PLUS.

Note: In cases when product is applied to existing concrete surfaces (more than 28 days old), the variations in colouration of the sands and aggregate present in the existing surface may be enhanced, causing the surface to appear discoloured.

**Drying Time ...** Product dries quickly. Drying times may be extended depending on application rate, temperature, humidity, and project conditions. Restrict foot traffic for at least four hours. Twelve hours is preferable.

**Cleanup ...** Clean tools after use with a solvent such as SEALTIGHT SOLVENT, xylene, or toluol.

#### PRECAUTIONS

For industrial use only. Apply without dilution or thinning VOC content of the product. **FOR EXTERIOR APPLICATION ONLY.** Surfaces treated with SEAL CURE/25 may become slippery under certain conditions. SEAL CURE/25 should not be applied during high temperature conditions in direct sunlight. These conditions cause rapid evaporation, which does not allow the film to form properly. Under these conditions, the film may peel, bubble and/or turn white (blush).

Do not apply SEAL CURE/25 if the temperature of the concrete is below 4° C (40° F). SEAL CURE/25 may be used on coloured concrete, but mottling may occur. Do not use on dense or non-porous surfaces, i.e. brick, stone, etc.

Concrete containing calcium chloride will remain dark longer when treated with SEAL CURE/25. Concrete floors properly cured with SEAL CURE/25 meet section 8.9 "Adhesion of Tile Cements" of ASTM C 1315. For other specifications, secure the approval of the paint or resilient flooring manufacturer before applying SEAL CURE/25. The specifier and used shall determine the suitability of product for specific applications and assume all responsibility in connection therewith

SEAL CURE/25 is a membrane-forming sealer. All membrane-forming sealers may darken concrete or magnify imperfections caused by variations in the porosity and/or finishing of the concrete.

#### HEALTH AND SAFETY

Contains solvent. Use with adequate ventilation and avoid prolonged breathing of vapours that may cause dizziness or suffocation. Avoid contact with skin and/or eyes. See product label and Material Safety Data Sheet for additional information. Read and follow all instructions and precautions. Harmful or fatal if swallowed.

#### MASTERFORMAT NUMBER AND TITLE

03 39 23 - Membrane Concrete Curing

#### LEED INFORMATION

May help contribute to LEED credits:

- MR Credit 2: Construction Waste Management
- MR Credit 5: Regional Materials

**For most current data sheet, further LEED information, and MSDS, visit [www.wrmeadows.com](http://www.wrmeadows.com).**

2011-07-22



© SEALTIGHT is a registered trade mark of W. R. Meadows

**WARRANTY:** W. R. Meadows of Canada warrants that, at the time and place we make shipment, our materials will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTY, EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM OF TRADE OR OTHERWISE. As the exclusive remedy for breach of this Warranty, we will replace defective materials, provided, however, that the buyer examine the materials when received and promptly notify us in writing of any defect before the materials are used or incorporated into a structure. Three (3) months after W. R. Meadows of Canada has shipped the materials, all our Warranty and other duties with respect to the quality of the materials delivered shall conclusively be presumed to have been satisfied, all liability therefore terminates and no action for breach of any such duties may thereafter be commenced. W. R. Meadows of Canada shall in no event be liable for consequential damages. Unless otherwise agreed to in writing, no warranty is made with respect to materials not manufactured by W. R. Meadows of Canada. We cannot warrant or in any way guarantee any particular method of use or application or the performance of materials under any particular condition. Neither this Warranty nor our liability may be extended or amended by our salesmen, distributors or representatives, or by our distributor's representatives, or by any sales information or drawings.