



CSI Code: 03050

No. 367

JULY 2004
(Supersedes September 2002)

MED-CURE™ Concrete Curing Compound & Hardener

DESCRIPTION

MED-CURE Concrete Curing Compound was specially formulated to supplement the W. R. MEADOWS' line of curing compounds and provide the contractor with a good, general-purpose curing compound for construction applications where economy is of prime importance. It contains no wax, resin or acids. MED-CURE meets maximum VOC content limits of 350 g/L for Concrete Curing Compounds as required by the U.S. EPA Architectural Coatings Rule.

USES

MED-CURE is ideal for curing, hardening and dustproofing exposed concrete floor slabs, sidewalks, driveways, beams, columns, etc. It can be used to provide a hard, dust-free surface on concrete floors to be painted or covered by resilient, carpeted, wood or synthetic flooring.

TECHNICAL DATA

- DRYING TIME...Depends on weather conditions and coverage, but will generally dry in one hour.
- FLASH POINT...Product will not flash.

PACKAGING

5 Gallon (18.93 liter) Pails
55 gallon (208.20 liter) Drums

COVERAGE

BROOMED SURFACE: 400 sq.ft./gal.
(9.82 sq.m/L)
TROWELED SURFACE: 600 sq.ft./gal.
(14.73 sq.m/L)

FEATURES AND BENEFITS

- Penetrates to cure and harden in one easy application
- Provides a low-maintenance finished surface
- Tint aids in identifying coverage
- Ideal for new or old, interior or exterior, horizontal or vertical concrete surfaces
- Dries fast and may be re-coated if desired
- Application tools may be cleaned with water
- VOC compliant...actual VOC content is 0

ADDITIONAL CURING COMPOUNDS FROM W. R. MEADOWS CAN BE FOUND BY VISITING OUR WEBSITE: www.wrmeadows.com



CONTINUED ON REVERSE SIDE...

Application Tools



Manual Sprayer



Paint Roller

APPLICATION

Preparation... Application equipment must be clean and free of any previously used materials.

Mixing... For optimum performance, gentle mixing or agitation is recommended. CAUTION: TO AVOID FOAMING, DO NOT MIX EXCESSIVELY.

Application Method...New Concrete: Apply MED-CURE as soon as surface water has disappeared and the surface is dry to the touch or hard enough to walk on. Apply one even coat with a pressure hand sprayer or paint roller.

Existing (Old) Concrete: Clean surface thoroughly with a trisodium phosphate solution and rinse thoroughly. Apply MED-CURE after the surface has dried. NOTE: Keep heavy traffic off surface for 24-48 hours after applying MED-CURE.

Clean-up... Application equipment may be cleaned easily with soap and water while still wet.

PRECAUTIONS

DO NOT DILUTE. Do not apply if the temperature of the concrete is less than 40°F (4°C). KEEP FROM FREEZING. If MED-CURE is accidentally sprayed or spilled on glass, brick, aluminum, painted surfaces, etc., flush immediately with water. Do not over-apply.

HEALTH HAZARDS

This product will not support combustion. Read and follow application information and use in accordance with the Health and Safety Information shown on the label. Refer to Material Safety Data Sheet for complete health and safety information.

TO VERIFY MOST RECENT TECHNICAL DATA SHEET IS BEING USED, VISIT OUR WEBSITE: www.wrmeadows.com



LIMITED WARRANTY

“W. R. MEADOWS, INC. warrants at the time and place we make shipment, our material will be of good quality and will conform with our published specifications in force on the date of acceptance of the order.” Read complete warranty. Copy furnished upon request.

Disclaimer

The information contained herein is included for illustrative purposes only, and to the best of our knowledge, is accurate and reliable. W. R. MEADOWS, INC. cannot however under any circumstances make any guarantee of results or assume any obligation or liability in connection with the use of this information. As W. R. MEADOWS, INC. has no control over the use to which others may put its product, it is recommended that the products be tested to determine if suitable for specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect or engineer, contractor and owner for the design, application and proper installation of each product. Specifier and user shall determine the suitability of products for specific application and assume all responsibilities in connection therewith.