



DATA SHEET NO. 3300-135

1215 WHITE Pigmented Curing Compound

DESCRIPTION

1215 White Pigmented Curing Compound is a waterborne resin based curing compound containing suspended white pigment. It permits complete hydration of the cement by retaining at least 95% of the water present in the concrete at the time of application, for at least 7 days. The white pigment reflects the heat-producing rays of the sun, keeping concrete surfaces cooler and preventing excessive heat build-up and resultant thermal cracking during the curing period.

USE

Reflective curing compound for exterior use on freshly placed concrete surfaces, both horizontal and vertical, particularly where protection from the sun's heat is required.

Recommended for use on driveways, walls, sidewalks, concrete highways, and runways, overpasses, bridges, tunnels, etc.

FEATURES

1215 White Pigmented Curing Compound contains SUSPENSOID, a unique additive which assists pigment dispersion and prevents excessive pigment settlement.

Excellent moisture retention properties.

Excellent heat reflective properties.

Excellent spray ability.

Easy clean up.

CAUTION

Not recommended for use on concrete surfaces that are later to be painted, tiled, hardened, sealed or treated in any manner.

Avoid breathing vapours. Avoid prolonged contact with skin.

FOR INDUSTRIAL USE ONLY.

STANDARDS

ASTM C 309, Type 2, Class B.

AASHTO M148, Type II, Class B

Approved by the Ministry of Transportation, Quebec.

DATA

Coverage 4.9 m²/litre (240 ft.²/gal.)

Packaging 18.9 litre pail

205 litre drum

APPLICATION INSTRUCTIONS

Product container label provides all application information. Read and follow all instructions and precautions.

Only nominal agitation of 1215 is required prior to each use. Do not employ constant re-circulating pumps or high-speed mixers.

Apply by low-pressure (30 psi) hand or power spray as soon as the surface water disappears from horizontal surfaces, or immediately after forms are removed from vertical surfaces.

An 80° fan pattern spray tip rated at 1.8 litres (0.4 gal. /72 oz.) per minute provides an excellent even coating.

Apply evenly over the entire surface, avoiding puddling in low areas.

Restrict foot traffic for at least 4 hours

Clean tools and equipment immediately after use with water. Once dried, material would need to be cleaned with SEALTIGHT Solvent, Xylene or Toluol. *Continued over*

W. R. MEADOWS OF CANADA
70 Hannant Court, Milton, ON L9T 5C1
Phone: (905) 878-4122 Fax: (905) 878-4125
Montreal Sales: (877) 405-5186

Hampshire, IL / Cartersville, GA / York, PA / Fort Worth, TX
Benicia, CA / Pomona, CA / Goodyear, AZ / Milton, ON /
St. Albert, AB
www.wrmeadows.com

Proper application is the responsibility of the user. Field visits by W. R. MEADOWS personnel are for the purpose of making technical recommendations only, and are not to supervise or provide quality control on the job-site.

SPECIFICATION CLAUSE

Section 03 39 23.

Curing Compound W. R. MEADOWS 1215 White Pigmented Concrete Curing Compound; conforming to (ASTM C 309, Type 2, Class B) (AASHTO M-148 Type II, Class B).

FOR BEST PERFORMANCE, ENSURE MOST RECENT TECHNICAL DATA SHEET IS BEING USED ... VISIT OUR WEBSITE AT:

www.wrmeadows.com

2007-01-18



© SEALTIGHT is a registered trade mark of W. R. Meadows

WARRANTY: W. R. Meadows of Canada warrants that, at the time and place we make shipment, our materials will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTY, EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM OF TRADE OR OTHERWISE. As the exclusive remedy for breach of this Warranty, we will replace defective materials, provided, however, that the buyer examine the materials when received and promptly notify us in writing of any defect before the materials are used or incorporated into a structure. Three (3) months after W. R. Meadows of Canada has shipped the materials, all our Warranty and other duties with respect to the quality of the materials delivered shall conclusively be presumed to have been satisfied, all liability therefore terminates and no action for breach of any such duties may thereafter be commenced. W. R. Meadows of Canada shall in no event be liable for consequential damages. Unless otherwise agreed to in writing, no warranty is made with respect to materials not manufactured by W. R. Meadows of Canada. We cannot warrant or in any way guarantee any particular method of use or application or the performance of materials under any particular condition. Neither this Warranty nor our liability may be extended or amended by our salesmen, distributors or representatives, or by our distributor's representatives, or by any sales information or drawings.