



## CEM-KOTE® FLEX ST Flexible Cementitious Waterproofing



ANSI/NSF Standard 61

Drinking Water System  
Components

### FEATURES

- **Approved ANSI/NSF Standard 61 – Barrier Materials**
- Superior flexibility
- Bridges substrate crack up to 1.6 mm (1/16")
- Long term crack resistance
- Fast cure waterproofing
- Approved for potable water tanks (>38m<sup>3</sup> - 10,000 USG)
- Superior freeze/thaw resistance
- Excellent salt scaling resistance
- Effective protection against acid rain
- Self-curing
- Continuous water immersion possible
- Superior negative/positive waterproofing
- Breathable
- Salt resistant
- Easy mixing & application = sprayable

### PRODUCT DESCRIPTION

#### Basic Use

**CEM-KOTE FLEX ST** is designed for positive and negative waterproofing of concrete structures in new construction and restoration. It is suitable for water and wastewater tanks, secondary containment structures, tunnels, concrete slabs, balconies and patios with light to medium traffic. In new construction, where superior flexibility is required (waste water treatment facilities), **CEM-KOTE FLEX ST** is reinforced with **REINFORCING FABRIC HD** throughout. In restoration, **REINFORCING FABRIC NW** is used just over the cracks to provide bridging.

#### Composition and Materials

**CEM-KOTE FLEX ST** is a highly flexible, fibre-reinforced, breathable, cementitious slurry, consisting of dry Component A and liquid Component B.

#### Limitations

Do not apply **CEM-KOTE FLEX ST** when the temperature is expected to be below 4°C (40°) within 48 hours, or when rain is imminent. Follow hot weather concreting precautions when applying **CEM-KOTE FLEX ST** at temperatures exceeding 25°C (77°F) or under sunny and windy conditions. For low temperature exposures, use **CEM-KOTE FLEX PLUS**.

#### Health and Safety

**CEM-KOTE FLEX ST** is non-toxic. Your skin might be sensitive to hydraulic cement or the liquid additive. We recommend use of rubber gloves. Avoid contact with eyes and prolonged contact with skin. If contact occurs, flush immediately with water. Seek medical advice if irritation occurs. Harmful if digested. Keep product out of reach of children. **FOR INDUSTRIAL USE ONLY.** Consult MSDS for additional information.

#### Colour

Industrial Grey, Light Grey, White.

#### Packaging

**CEM-KOTE FLEX ST Premix Kit**, consists of dry Component A, packaged in 16 kg (35.3 lb.) bags and liquid Component B, packaged in plastic jugs. **Industrial Grey** in 4.8 L (1.3 U.S.gal.); **Light Grey** in 4.8 L (1.3 U.S.gal.).

#### Yield

**CEM-KOTE FLEX ST**; Yields 10.5 L (0.37 ft.<sup>3</sup>) and covers approximately 6.6 m<sup>2</sup> @ 1.6 mm (70.6 ft.<sup>2</sup> @ 63 mils) thickness per kit, applied in two (2) coats.

The actual coverage will depend on surface roughness and the thickness applied. The applicator must carry out a sample application to determine the actual coverage for the given substrate and application thickness.

#### Storage and Transportation

**CEM-KOTE FLEX ST**, when stored on pallets in a dry, cool area, free from moisture and direct sunlight, has a shelf life of 12 months. The liquid Component B must not freeze. Packaged 40 kits per pallet.

Continued over ...

**W. R. MEADOWS OF CANADA**  
70 Hannant Court, Milton, ON L9T 5C1  
Phone: (905) 878-4122 • Fax: (905) 878-4125  
Montreal Sales: (877) 405-5186

Hampshire, IL / Cartersville, GA / York, PA / Fort Worth, TX  
Benicia, CA / Pomona, CA / Goodyear, AZ / Milton, ON /  
St. Albert, AB  
[www.wrmeadows.com](http://www.wrmeadows.com)

## TECHNICAL DATA

Ultimate Tensile Strain (ASTM D 412 Mod.)	
@ 20°C, (68°F) non-reinforced	20%
@ 20°C, (68°F) reinforced	30%
Ultimate Tensile Stress (ASTM D 412 Mod.)	
@ 20°C, (68°F) non-reinforced	0.82 MPa (120 psi)
@ 20°C, (68°F) reinforced	3.05 MPa (440 psi)
Crack Spanning (Gemite ISO TP 005)	
@ 20°C, (68°F) non-reinforced	0.5 mm (20 mils)
@ 20°C, (68°F) reinforced	1.6 mm (63 mils)
Water Vapour Permeance, (ASTM E 96)	
Wet cup 1.6 mm	697 ng/Pa.s.m <sup>2</sup> (12.8 perms)
Water Vapour Permeability, Engelfried-Klopfer Sd <3 m	S <sub>d</sub> = 0.265 m
Salt Scaling Resistance, (ASTM C672)	
Excellent	
Hydraulic Impermeability TTP 1411 (negative side), 2 mm thickness	Water head >38.4 m(>126 ft.)
A high porosity concrete block, coated with <b>CEM-KOTE FLEX ST</b> , "burst" at 38.4 m (126 ft.) water head pressure with <b>CEM-KOTE FLEX ST</b> showing no sign of wetness	

## INSTALLATION

Follow manufacturer's most recent application procedures and details to assure quality installation. The applicator must, prior to bid, confirm the detailing, use of the **REINFORCING FABRIC**, correct surface preparation and application procedures with manufacturer's technical services. The applicator must also arrange a pre-installation meeting with the manufacturer's technical representative, general contractor, and site engineer to review the installation procedure. The project specification supersedes the Gemite guide specification.

### Surface Preparation

Remove all deteriorated and loose concrete, form release agents, oil, grease, laitance, dust, dirt and efflorescence by dry or wet sandblast, shotblast, or high-pressure water (minimum 34.5 MPa [5,000 psi]). Repair deeper areas using **GEM-PLAST TC** or **MEADOW-CRETE® OV** from W. R. MEADOWS. The proper surface preparation is essential for a successful waterproofing and concrete repair using **CEM-KOTE FLEX ST**. Remove all loose rust from any exposed reinforcing steel and apply two coats of **PATCH-PRIME™** rust proofing from W. R. MEADOWS.

### Crack Treatment

All cracks must be treated using **CEM-KOTE FLEX ST** and **REINFORCING FABRIC NW**. Pre-fill any open cracks larger than 2 mm (80 mils) with **CEM-KOTE FLEX ST**. Apply a thin coat of **CEM-KOTE FLEX ST**, 15-25 cm (6-10") wide, over the crack. Embed a strip of **REINFORCING FABRIC NW** into the wet **CEM-KOTE FLEX ST** and apply a second coat to fully cover the **REINFORCING FABRIC NW**.

### Cove Installation

Install 40 – 50 mm (1 1/2" - 2") "coves" in vertical and horizontal corners (all 90° angles) using **MEADOW-CRETE OV**. All the coves are also reinforced with well embedded and covered **REINFORCING FABRIC HD**.

### Mixing

Thoroughly mix the liquid Component B prior to its use. Use paddle or helix mortar mixer or heavy-duty drill (400-600 rpm) with a mixing paddle. Pour approximately 80% of component B into a clean mixer and gradually add the dry component A, while mixing, until a smooth and lump free mix is obtained. Lumps will form if the dry material is added suddenly into the liquid. Add the remaining liquid, while mixing, to achieve the consistency required for a given application. A small amount of water can be added, if required, at higher ambient temperatures.

### Application

Trowel or brush apply **CEM-KOTE FLEX ST** to a minimum thickness of 1.6 mm (63 mils) in two (2) coats to a saturated surface dry (SSD) concrete. **CEM-KOTE FLEX ST** can also be spray applied using a hopper gun or positive displacement (moyno or carrousel) pump, with a suitable plastering spray nozzle. When using spraying, brush each coat to eliminate all pinholes. The second coat must be applied into a wet first coat, usually within 10-15 minutes, depending on temperature and relative humidity. The delayed application of the second coat could result in its debonding.

### Reinforcing Fabric

In some projects, **REINFORCING FABRIC HD** may have to be used throughout. When using **REINFORCING FABRIC HD**, apply first a thin layer of **CEM-KOTE FLEX ST** by brushing or spraying. When spraying, brush each coat to eliminate all "pinholes." Embed **REINFORCING FABRIC HD** into the first coat and follow with a second coat. **REINFORCING FABRIC HD** must be fully covered and must not protrude through the surface. The total minimum applied thickness of **CEM-KOTE FLEX ST**, including **REINFORCING FABRIC HD**, must be 1.6 mm (63 mils).

### Curing

Cure **CEM-KOTE FLEX ST** by air-drying for a minimum of 3 days prior to a continuous exposure to water. Protect fresh applications from rain, strong wind and intense sunlight for 12 hours. When working under tarps at freezing temperatures, use electrical heaters and "forced" venting. Avoid using propane heaters to prevent "carbonation" of the material.

### Cleanup

All tools must be cleaned with water immediately after use. Cured material can only be removed mechanically.

## WARRANTY

A limited twelve (12) month Material Replacement Warranty is available. For details, contact Technical Service.

## TECHNICAL SERVICE

For advice on suitability of **CEM-KOTE FLEX ST** for a specific application, specification assistance and application advice, contact Technical Service at 1-800-563-3618.

### Short Specification

The waterproofing will be **CEM-KOTE FLEX ST**, a flexible, polymer modified cement, manufactured by Gemite Products Inc. It will be mixed and applied according to the current manufacturer's specifications and recommendations. The suitability of **CEM-KOTE FLEX ST** for a specific use, the surface preparation method, detailing and application procedures must be checked with the Technical Services prior to bid.

## MANUFACTURER

Gemite® Products Inc.,  
1787 Drew Road,  
Mississauga, ON L5S 1J5  
Phone: 905-672-2020  
Website: [www.gemite.com](http://www.gemite.com)

Fax: 905-672-6780

2010-03-11