



DATA SHEET NO. 3250-242

CERAMAR® Flexible Foam Expansion Joint

DESCRIPTION

CERAMAR is a flexible foam expansion joint filler composed of a unique synthetic foam of isomeric polymers in a very small, closed-cell structure. Gray in colour, CERAMAR is a lightweight, flexible, highly resilient material offering recovery qualities of over 99%. The compact, closed-cell structure will absorb almost no water.

USES

CERAMAR flexible foam expansion joint filler provides an excellent joint filler and backup material for use in either horizontal or vertical applications where expansion and contraction movements must be accommodated. CERAMAR is compatible with all currently popular cold-applied sealants, caulks, and hot-pour joint sealing compounds. It is lightweight and easy to cut or form in the field without waste.

CERAMAR compresses easily for use with shrinkage-compensating concrete and it may be used to relieve stress and pressure in concrete pavements.

FEATURES/BENEFITS

- May be sealed with hot- or cold-applied sealants.
- User friendly, lightweight, flexible foam ... forms or wraps around curved or circular surfaces.
- Cuts easily on the job with a razor knife ... no breakage or waste.
- Offers high resiliency and 99% recovery qualities ... low compression values ... non-extruding ... minimal water absorption.
- Resists ultraviolet degradation ... will not rot or deteriorate.
- Non-impregnated ... no staining or bleeding.
- Bonds easily with common cartridge adhesives.
- Non-gassing.

SPECIFICATIONS

- ASTM D5249, Type 2
- ASTM D1752, Sections 5.1 - 5.4, with compression requirement modified to 10 psi (7.03 g/mm²) minimum and 25 psi (17.58 g/mm²) maximum.
- ASTM D7174-05

TECHNICAL DATA*

Compression, 50%	89.6 kPa (9 g/mm ²) (13 psi)
Extrusion	2.5 mm (0.1")
Recovery	99.21%
Water Absorption, volume %	0.246

Test Method – ASTM D545 [12.7 mm (1/2") thick test specimen]

*All technical data is typical information, but may vary due to test methods, conditions and operators.

PACKAGING

Furnished in standard sheets 1.22 m (48") wide, 3.05 m (10') long. Also available in pre-cut widths of 50.8 mm - 1.17 m (2" - 46").

Thickness	Approx. Wt./100 m ²	Approx. Wt./100 ft. ²	Pcs. /bundle	Shipping Wt./Bundle
6.4 mm (1/4")	15.29 kg	3.13 lbs.	100	72.58 kg (160 lbs.)
9.5 mm (3/8")	22.93 kg	4.70 lbs.	100	108.86 kg (240 lbs.)
12.7 mm (1/2")	30.52 kg	6.25 lbs.	75	113.40 kg (250 lbs.)
19.1 mm (3/4")	45.90 kg	9.40 lbs.	50	108.86 kg (240 lbs.)
25.4 mm (1")	61.03 kg	12.50 lbs.	40	117.94 kg (260 lbs.)

APPLICATION

For horizontal applications, position CERAMAR against the forms, at interrupting columns and objects or adjacent to abutting structures, before placing concrete. Vertical applications may call for CERAMAR to be placed between panels, panel-to-column joints, or in block wall joints prior to sealing. CERAMAR may be used with all hot- and cold-applied sealants.

PRECAUTIONS

Due to its light weight, CERAMAR will float and must be held in place by compression or with a sealant.

HEALTH AND SAFETY

Refer to Safety Data Sheet for complete health and safety information.

Continued over ...

W. R. MEADOWS® OF CANADA
70 Hannant Court, Milton, ON L9T 5C1
38 Rayborn Crescent, St. Albert, AB T8N 4B1
(800) 342-5976
Montreal Sales: (877) 405-5186

Hampshire, IL / Cartersville, GA / York, PA / Fort Worth, TX
Benicia, CA / Pomona, CA / Goodyear, AZ / Milton, ON
St. Albert, AB
www.wrmeadows.com

MASTERFORMAT NUMBER AND TITLE

03 15 00 - Concrete Accessories

LEED INFORMATION

May help contribute to LEED credits:

- MRc9: Construction and Demolition Waste Management

For most recent data sheet, further LEED information, and SDS, visit www.wrmeadows.com.

2019-12-24



© SEALTIGHT is a registered trade mark of W. R. Meadows

WARRANTY: W. R. Meadows of Canada warrants that, at the time and place we make shipment, our materials will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTY, EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM OF TRADE OR OTHERWISE. As the exclusive remedy for breach of this Warranty, we will replace defective materials, provided, however, that the buyer examine the materials when received and promptly notify us in writing of any defect before the materials are used or incorporated into a structure. Three (3) months after W. R. Meadows of Canada has shipped the materials, all our Warranty and other duties with respect to the quality of the materials delivered shall conclusively be presumed to have been satisfied, all liability therefore terminates and no action for breach of any such duties may thereafter be commenced. W. R. Meadows of Canada shall in no event be liable for consequential damages. Unless otherwise agreed to in writing, no warranty is made with respect to materials not manufactured by W. R. Meadows of Canada. We cannot warrant or in any way guarantee any particular method of use or application or the performance of materials under any particular condition. Neither this Warranty nor our liability may be extended or amended by our salesmen, distributors or representatives, or by our distributor's representatives, or by any sales information or drawings.