



W. R. MEADOWS

SEALTIGHT

DATA SHEET NO. 3300-252

MED-CURE™

Concrete Curing Agent, Hardener, and Dustproofers

DESCRIPTION

MED-CURE is a ready-to-use, water-based, VOC-compliant concrete curing agent, hardener, and dustproofers. It is residue-free and contains no wax, resin, or other materials that would inhibit the bond of subsequent coatings and/or treatments over substrate treated with MED-CURE

USES

MED-CURE is ideal as a curing aid as well as for hardening and dustproofing exposed concrete floor slabs, sidewalks, driveways, beams, columns, etc. It can be used to provide a dust-free surface on concrete floors to be painted or covered by resilient, carpeted, wood, or synthetic flooring.

FEATURES/BENEFITS

- Meets the moisture retention requirement of ASTM C309 on hard trowel concrete.
- Penetrates to aid curing, as well as to harden concrete, in one easy application.
- Minimizes hair checking, thermal cracking, dusting, and other defects.
- Provides a low-maintenance, finished surface.
- Tinted product available which aids in identifying coverage.
- Ideal for new, old, interior, exterior, horizontal, and vertical concrete surfaces.
- Dries fast and may be recoated if desired.
- Application tools may be cleaned with water.
- VOC-compliant.
- Does not prevent the adhesion of subsequent coatings, treatments, or flooring material.

PACKAGING

3.78 Litre (1 U.S. Gal.) Units
18.9 Litre (5 U.S. Gal.) Pails
205 Litre (54 U.S. Gal.) Drums

COVERAGE

Broomed Surface: 7.36 m²/L - 12.27 m²/L
(300 - 500 ft.²/gal.)
Troweled Surface: 12.27 m²/L - 17.18 m²/L
(500 - 700 ft.²/gal.)

Coverage is approximate and may vary depending on surface finish/texture, concrete condition, climatic conditions, etc. Always apply to a test area first to determine actual coverage rate before full-scale application.

SHELF LIFE

When stored indoors in original, unopened containers at temperatures between 4° - 32° C, optimum performance and best use is obtained within one year of date of manufacture.

SPECIFICATIONS

- Complies with Canada VOC Concentration Limits for Architectural Coatings Regulations.
- Meets Canadian Food Inspection Agency requirements.

APPLICATION

Surface Preparation

Fresh (New) Concrete ... Apply as soon as all surface water has disappeared and the concrete surface will not be marred by walking workers.

Existing (Old) Concrete: ... Concrete surface must be clean and dry with all stains, oil, grease, dust, and dirt removed prior to application.

Application Method ... Use a sprayer or short-nap roller to apply a uniform film. Avoid puddling in low areas. If puddles occur, brush or roll them out. A standard industrial-grade sprayer, such as a Chapin 1949, and a spray nozzle that produces a flow of 0.379 LPM (0.1 GPM) under 276 kPa (40 psi) of pressure, is recommended.

Continued over ...

W. R. MEADOWS® OF CANADA
70 Hannant Court, Milton, ON L9T 5C1
38 Rayborn Crescent, St. Albert, AB T8N 4B1
(800) 342-5976
Montreal Sales: (877) 405-5186

Hampshire, IL / Cartersville, GA / York, PA / Fort Worth, TX
Benicia, CA / Pomona, CA / Goodyear, AZ / Milton, ON
St. Albert, AB
www.wrmeadows.com

Mixing ... For optimum performance, gentle mixing or agitation is recommended.

Drying Time ... MED-CURE dries in approximately one hour. Drying times may vary depending on application rate, temperature, humidity, wind, and project conditions.

Clean Up ... Application equipment may be cleaned easily with soap and water while still wet.

PRECAUTIONS

DO NOT DILUTE. Do not apply if the temperature of the concrete is less than 4.4° C. KEEP FROM FREEZING. If MED-CURE is accidentally sprayed or spilled on glass, brick, aluminum, painted surfaces, etc., flush immediately with water. Do not over-apply. Over-application or puddling of MED-CURE on the surface may lead to white crystals forming on the surface which are difficult to remove. Mechanical abrasion is the only effective manner to remove crystals.

HEALTH AND SAFETY

This product will not support combustion. Read and follow application information and use in accordance with the health and safety information shown on the label. Refer to Safety Data Sheet for complete health and safety information.

MASTERFORMAT NUMBER AND TITLE

03 35 00 - Concrete Finishing

LEED INFORMATION

May help contribute to LEED credits:

- MRc9: Construction and Demolition Waste Management
- EQc2: Low-Emitting Materials [For Healthcare and Schools (exterior-applied products) ONLY]

For most recent data sheet, further LEED information, and SDS, visit www.wrmeadows.com.



2017-11-10

© SEALTIGHT is a registered trade mark of W. R. Meadows

WARRANTY: W. R. Meadows of Canada warrants that, at the time and place we make shipment, our materials will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTY, EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM OF TRADE OR OTHERWISE. As the exclusive remedy for breach of this Warranty, we will replace defective materials, provided, however, that the buyer examine the materials when received and promptly notify us in writing of any defect before the materials are used or incorporated into a structure. Three (3) months after W. R. Meadows of Canada has shipped the materials, all our Warranty and other duties with respect to the quality of the materials delivered shall conclusively be presumed to have been satisfied, all liability therefore terminates and no action for breach of any such duties may thereafter be commenced. W. R. Meadows of Canada shall in no event be liable for consequential damages. Unless otherwise agreed to in writing, no warranty is made with respect to materials not manufactured by W. R. Meadows of Canada. We cannot warrant or in any way guarantee any particular method of use or application or the performance of materials under any particular condition. Neither this Warranty nor our liability may be extended or amended by our salesmen, distributors or representatives, or by our distributor's representatives, or by any sales information or drawings.