



DATA SHEET NO. 3300-333

EVAPRE™- RTU Ready-To-Use Evaporation Retardant

DESCRIPTION

EVAPRE-RTU is a ready-to-use evaporation retardant that is high quality and water-based. It is specifically designed to form a thin monomolecular film to reduce rapid moisture loss from the concrete surface prior to curing. EVAPRE-RTU provides a significant aid in producing high-quality concrete flatwork. Rapid evaporation of water is retarded, slab surface conditions are normalized, and workers can adhere more closely to established finishing schedules when using EVAPRE-RTU. EVAPRE-RTU is VOC-compliant.

EVAPRE-RTU significantly reduces plastic shrinkage, cracking, wind crusting, stickiness, and sponginess, which often cause poor and uneven surface texture. These conditions result when the hydration is more rapid than the movement of bleed water to the surface. EVAPRE-RTU effectively combats and minimizes the effects of rapid drying conditions such as low humidity, low dew point, high winds, direct sunlight, hot weather, heated concrete, or placement of concrete in a heated enclosure or interior area during cold weather. The protective film shield disappears as soon as the concrete is no longer plastic.

USES

EVAPRE-RTU is ideal for use as an evaporation retardant for concrete surfaces where the evaporation rate exceeds the rate of bleeding. EVAPRE-RTU can be used with condensed silica fume concrete, concrete containing fly ash, and all cementitious products. When applying surface hardeners, EVAPRE-RTU can be used after screeding and after the first floating operation, if necessary.

NOTE:

EVAPRE-RTU is specifically designed to fight off the destructive effects of early rapid evaporative moisture loss. Early evaporative moisture loss is addressed in American Concrete Institute (ACI) Committee 305R-91: Recommended Practice for Hot Weather Concreting. This report contains a chart on page five which depicts the effect of concrete and air temperatures, relative humidity, and wind velocity on the rate of evaporation of surface moisture from concrete. It provides a graphic method for estimating the loss of surface moisture for various weather conditions.

FEATURES/BENEFITS

- Significantly reduces plastic shrinkage and cracking caused by evaporation in low humidity, high temperatures, and high winds.
- Allows use of lower slump and lower water:cement ratio concrete.
- Provides smooth and durable concrete flatwork.
- Reduces wind crusting, stickiness, and sponginess, which often cause poor and uneven surface texture.
- Allows finishing crews to adhere to established schedules.
- Reduces overall cost because timing of finishing operations is less critical.
- VOC compliant.
- Helps minimize surface cracking due to early water loss of silica fume concrete.

PACKAGING

18.9 Litre (5 U.S. Gal.) Pails
208 Litre (55 U.S. Gal.) Drums

COVERAGE

EVAPRE-RTU should be applied at 4.9 - 9.8 m²/L (200 - 400 ft.²/U.S. gal.) Quantity applied will increase if more than one application is made, as in adverse drying conditions.

Continued over

W. R. MEADOWS OF CANADA
70 Hannant Court, Milton, ON L9T 5C1
21 Streambank Ave., Sherwood Park, AB T8H 1N1
(800) 342-5976
Montreal Sales: (877) 405-5186

Hampshire, IL / Cartersville, GA / York, PA / Fort Worth, TX
Benicia, CA / Pomona, CA / Goodyear, AZ / Milton, ON /
Sherwood Park, AB
www.wrmeadows.com

SHELF LIFE

When stored indoors in original, unopened containers at temperatures between 4° - 32° C, optimum performance and best use is obtained within one year of date of manufacture.

APPLICATION

STEP 1: Agitate EVAPRE-RTU before applying.

STEP 2: Apply EVAPRE-RTU with a commercial sprayer, such as a Chapin 1949. Use a spray tip that produces a flow rate of 1.9 LPM (0.5 GPM) under 0.276 MPa (40 psi) of pressure.

STEP 3: EVAPRE-RTU should be applied immediately after screeding and/or between finishing operations, as needed. Application is simplified by the fugitive pigment, which will disappear completely upon drying. Do not allow puddling. Do not over-apply.

STEP 4 - Clean all equipment immediately after use with soap and water.

STEP 5 - Finish concrete surface as required.

STEP 6 - Cure concrete after bleed water or excess surface water has dissipated. The use of EVAPRE-RTU does not negate the need for a quality concrete curing or curing and sealing compound from W. R. MEADOWS.

Note ... The residue remaining on the surface after finishing will not impair bonding or alter colour. The protective shield usually lasts as long as the concrete is plastic. Therefore, all concrete surfaces must be properly cured as well.

PRECAUTIONS

DO NOT USE EVAPRE-RTU as a finishing aid for cementitious materials, including dry shake surface hardeners or toppings. EVAPRE-RTU should not be worked into the concrete surface, nor should it be used to re-temper the concrete. EVAPRE-RTU should not be applied during final trowelling operations. EVAPRE-RTU is not a curing agent.

W. R. MEADOWS is not responsible for compatibility or results when EVAPRE-RTU is used with other manufacturer's products.

MASTERFORMAT NUMBER AND TITLE

03 00 00 - Concrete

LEED INFORMATION

May help contribute to LEED credits:

- MRc9: Construction and Demolition Waste Management
- EQc2: Low-Emitting Materials [For Healthcare and Schools (exterior-applied products) ONLY]

For most recent data sheet, further LEED information, and SDS, visit www.wrmeadows.com.

2018-06-18



© SEALTIGHT is a registered trade mark of W. R. Meadows

WARRANTY: W. R. Meadows of Canada warrants that, at the time and place we make shipment, our materials will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTY, EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM OF TRADE OR OTHERWISE. As the exclusive remedy for breach of this Warranty, we will replace defective materials, provided, however, that the buyer examine the materials when received and promptly notify us in writing of any defect before the materials are used or incorporated into a structure. Three (3) months after W. R. Meadows of Canada has shipped the materials, all our Warranty and other duties with respect to the quality of the materials delivered shall conclusively be presumed to have been satisfied, all liability therefore terminates and no action for breach of any such duties may thereafter be commenced. W. R. Meadows of Canada shall in no event be liable for consequential damages. Unless otherwise agreed to in writing, no warranty is made with respect to materials not manufactured by W. R. Meadows of Canada. We cannot warrant or in any way guarantee any particular method of use or application or the performance of materials under any particular condition. Neither this Warranty nor our liability may be extended or amended by our salesmen, distributors or representatives, or by our distributor's representatives, or by any sales information or drawings.