



DATA SHEET NO. 3300-719

TOP-STOP™ HORIZONTAL

Spray-Applied, Water-Soluble Surface Retarder

DESCRIPTION

TOP-STOP HORIZONTAL is a spray-applied, water-soluble surface retarder designed to slow the set of surface mortar of concrete to produce an exposed aggregate finish. It temporarily delays the set of Portland cement at the top surface, while the underlying concrete sets normally. TOP-STOP HORIZONTAL is easy to use, producing beautiful exposed aggregate concrete flatwork with consistent results. It is non-flammable and VOC compliant.

USES

TOP-STOP HORIZONTAL may be used to produce an architectural finish on concrete slabs by exposing the natural colour and texture of the aggregate. TOP-STOP HORIZONTAL exposes the aggregate on floor slabs, sidewalks and tilt-up and pre-cast panels or any normal horizontal concrete application. It produces roughened bonding surfaces for subsequent concrete toppings and roughens horizontal surfaces for construction joints in power plants, dams and other civil engineering projects. The rough finish obtained from using TOP-STOP HORIZONTAL may be used as a mechanical key for later concrete lifting or rendering.

FEATURES/BENEFITS

- Architectural-quality appearance with original colour and texture of the aggregate without sandblasting.
- Easy removal of the concrete surface.
- Eliminates hacking, chipping, or blasting of the surface.
- No danger of acid residue from strong washing compounds.
- Easy to use.
- Less supervision of field personnel.
- No expensive equipment required.
- Uniform coverage results in uniform aggregate exposure; consistent results.
- Easy water clean up.
- VOC compliant.

PACKAGING

3.78 Litre Units
18.93 Litre Pails
205 Litre Drums

COVERAGE

Coverage is approximately 3.68 - 7.36 m²/L (150 - 300 ft.²/gal.) to retard the exposed aggregate to a depth of 3.2 mm - 4.8 mm (1/8" - 3/16"). Coverage may vary due to porosity and condition of the concrete.

SHELF LIFE

When stored indoors in original, unopened containers at temperatures between 4° - 32° C, optimum performance and best use is obtained within one year of date of manufacture.

SPECIFICATIONS

- Complies with Canada VOC Concentration Limits for Architectural Coatings Regulations

TECHNICAL DATA

Colour:	Green
Solids, Wt. %:	13
Density, kg/L:	1.04
Coverage, m ² /L (ft. ² /gal)	3.68 - 7.36 m ² /L (150 - 300 ft. ² /gal.)

APPLICATION

Apply TOP-STOP HORIZONTAL with a low-pressure sprayer, such as a Chapin 1949, along with a nozzle that provides a 0.379 LPM spray rate. Apply immediately after screeding when concrete has lost its sheen, or as soon as bleed water has disappeared. Apply only after all finishing operations are complete. Avoid puddles and over-spraying.

Cover concrete with wet burlap or plastic sheeting to prevent drying out. Secure the edges of the plastic sheeting to prevent ballooning. Do not use curing compounds. Concrete admixtures which affect the setting time should not be used without first conducting a test patch. Periodically check concrete to determine depth of retarded mortar, making sure concrete hardens.

Continued over ...

W. R. MEADOWS® OF CANADA
70 Hannant Court, Milton, ON L9T 5C1
21 Streambank Ave., Sherwood Park, AB T8H 1N1
(800) 342-5976
Montreal Sales: (514) 865-2406

Hampshire, IL / Cartersville, GA / York, PA / Fort Worth, TX
Benicia, CA / Pomona, CA / Goodyear, AZ / Milton, ON
Sherwood Park, AB
www.wrmeadows.com
info@wrmeadows.com

Within 12 - 24 hours of application, remove burlap or plastic sheeting one section at a time and wash the retarded surface mortar using a water broom or stiff brush. Do not use excessive force. Test a small area to determine if depth of retarded mortar is at desired level. If the depth is greater than desired, allow the slab to cure longer before exposing the aggregate.

Aggregate color can be enhanced using EXPO-GLOSS® OTC from W. R. MEADOWS.

Clean Up ... Clean tools and equipment with soap and water before material is allowed to dry.

PRECAUTIONS

Apply only on freshly poured concrete. Depth of the exposed aggregate will be affected by environmental conditions, such as extreme temperatures, as well as the water pressure and scrubbing action used during removal. A test patch under exact job conditions is recommended. Do not use on vertical concrete or form applications. Do not use on concrete containing calcium chloride or other set accelerators. Do not apply to frozen surfaces. Protect treated area from freezing, rain, strong winds, and extreme sunlight. Do not store in metal sprayers for long periods of time. Direct contact may result in mild irritation. Refer to safety data sheet for complete health and safety information. Keep from freezing.

MASTERFORMAT NUMBER AND TITLE

03 05 00 – Common Work Results for Concrete

LEED INFORMATION

May help contribute to LEED credits:

- EQc2: Low-Emitting Materials [For Healthcare and Schools (exterior-applied products) ONLY]

For most recent data sheet, further LEED information, and SDS, visit www.wrmeadows.com.



2019-10-31

© SEALTIGHT is a registered trade mark of W. R. Meadows

WARRANTY: W. R. Meadows of Western Canada warrants that, at the time and place we make shipment, our materials will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTY, EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM OF TRADE OR OTHERWISE. As the exclusive remedy for breach of this Warranty, we will replace defective materials, provided, however, that the buyer examine the materials when received and promptly notify us in writing of any defect before the materials are used or incorporated into a structure. Three (3) months after W. R. Meadows of Western Canada has shipped the materials, all our Warranty and other duties with respect to the quality of the materials delivered shall conclusively be presumed to have been satisfied, all liability therefore terminates and no action for breach of any such duties may thereafter be commenced. W. R. Meadows of Western Canada shall in no event be liable for consequential damages. Unless otherwise agreed to in writing, no warranty is made with respect to materials not manufactured by W. R. Meadows of Western Canada. We cannot warrant or in any way guarantee any particular method of use or application or the performance of materials under any particular condition. Neither this Warranty nor our liability may be extended or amended by our salesmen, distributors or representatives, or by our distributor's representatives, or by any sales information or drawings.