



## DATA SHEET NO. 3460-200

### INTRAGUARD™

#### Penetrating, Water-Based, Silane/Siloxane Sealing Compound

##### DESCRIPTION

INTRAGUARD is a water-based, penetrating sealing compound for concrete and masonry surfaces. INTRAGUARD is water-repellent, specifically designed to reduce the intrusion of water and chlorides into the substrate. This proprietary blend of silane and siloxane penetrates into the pores of the concrete and masonry to reduce scaling caused by deicing salts as well as protecting vertical masonry surfaces from the ingress of water. Good concrete and concreting practices must be used, as INTRAGUARD will not be effective on improperly designed, placed or cured concrete.

##### USES

INTRAGUARD is for use on concrete and masonry surfaces, including concrete parking lots, driveways, walkways, and vertical walls. The product is designed to help provide protection from de-icing chemicals and moisture intrusion on properly cured and placed concrete. The product can be used on both horizontal and vertical surfaces. Suitable application include architectural concrete, concrete block, split-face block, pavers, stucco, porous and dense brick, clay tile, etc.

##### FEATURES/BENEFITS

- When properly applied INTRAGUARD does not form a film – it penetrates the surface to form an integral barrier to moisture penetration.
- Leaves no gloss or shine.
- Transparent, non-staining.
- Breathable – does not trap moisture.
- Reduces chloride penetration into concrete and masonry surfaces.
- Helps protect properly placed and cured concrete and masonry from scaling and freeze/thaw damage caused by de-icing chemicals.
- Water-based, VOC-compliant.
- Allows masonry to breathe.

##### PACKAGING

3.79 Litre (1 U.S. Gallon) Units (4/Cartron)  
18.93 Litre (5 U.S. Gallon) Pails  
1040.99 Litre (275 Gallon) Totes

##### COVERAGE

Coverage rate is approximately 1.2 - 6.1 m<sup>2</sup>/L (50 - 250 ft.<sup>2</sup>/gal.). Coverage is approximate and may vary depending on surface finish/texture, concrete condition, climatic conditions, etc. Always apply to a test area first to determine actual coverage rate before full-scale application.

##### SHELF LIFE

When stored indoors in original, unopened containers at temperatures between 4° - 32° C, optimum performance and best use is obtained within one year of date of manufacture.

##### SPECIFICATIONS

- Complies with VOC Concentration Limits for Architectural Coatings Regulations in Canada

##### TECHNICAL & PERFORMANCE DATA\*

Property	Test Method	Test Data
Appearance	Visual	Milky white emulsion
Density, g/cm <sup>3</sup> (lb./gal.):	ASTM D1475	0.99 (8.30)
Flash point, °C:	ASTM D98	>100
Dry to touch, hours:	ASTM C309	1 - 2
Scaling reduction:	ASTM C672	Reduces scaling at 50 cycles

\*All technical data is typical information and will vary due to testing methods, site conditions, temperature, curing, procedures, batching, and expected variations in naturally occurring raw materials. Statistical differences in test results should be anticipated. On-site testing results may not correlate to published laboratory results due to testing variations.

##### APPLICATION

**Surface Preparation** ... Protect people, vehicles, property, plants, and all surfaces from product, splash, residue, and wind drift. Surfaces must be structurally sound, clean and free from dirt, bitumen, efflorescence,

### W. R. MEADOWS® OF CANADA

70 Hannant Court, Milton, ON L9T 5C1  
21 Streambank Ave., Sherwood Park, AB T8H 1N1  
(800) 342-5976  
Montreal Sales: (514) 865-2406

Hampshire, IL / Cartersville, GA / York, PA / Fort Worth, TX  
Benicia, CA / Pomona, CA / Goodyear, AZ / Milton, ON  
Sherwood Park, AB  
[www.wrmeadows.com](http://www.wrmeadows.com)  
[info@wrmeadows.com](mailto:info@wrmeadows.com)

oil, curing compounds, form oil, and other foreign matter. Masonry joints must be checked and repointed where necessary. All wall and roof flashings, caulking, and sealants must be in good condition and the surface fully cured and thoroughly dry before application. Though INTRAGUARD may be applied to slightly damp surfaces, best performance is achieved on a clean, thoroughly dried and absorbent surface. Excessive moisture inhibits penetration, reducing the service life and performance of the treatment. Always test for compatibility. For optimum results, wait 14 - 28 days before applying INTRAGUARD to new concrete and masonry. For optimum performance, the moisture content of the substrate must not exceed 4%.

**Surface and Air Temperatures ...** Optimum surface and air temperature is 4° C and rising and 35° C and falling during application. If freezing conditions exist before application, let surface to receive treatment thaw.

**Test Application ...** Always perform a test application on each type of surface prior to full-scale application to determine suitability and final appearance. Test using the recommended application instructions. Let area dry thoroughly before inspection.

**Application Method ...** INTRAGUARD can be sprayed, brushed or rolled. For best results, using a sprayer such as Chapin 1949 and a spray nozzle that produces a spray pattern of 0.1 GPM (0.379 LPM) under 40 psi (0.276 MPa) of pressure is recommended. Note: Hot, windy conditions will evaporate the water carrier, reducing penetration and performance. On hot, windy days, apply early in the day and in shade, if possible.

**Horizontal Application ...** Amply saturate the surface with INTRAGUARD. Use enough to completely wet the surface. Do not let the product puddle on the surface or dry on the surface. Roll or brush out puddles. DO NOT OVERAPPLY. After 5 - 10 minutes, remove all excess sealer from the surface. On highly permeable surfaces, additional coats may be necessary.

**Vertical Application ...** Apply from the bottom up. To ensure proper penetration, sufficient material should be applied to allow a flood of material to run down at least 152.4 - 254 mm (6" - 10") below the spray point. Allow the material to penetrate for 10 - 15 minutes, then apply

a second application "wet on wet." The second application will require less material than the first.

**NOTE:** Hot, windy conditions will evaporate the water carrier, reducing penetration and performance. On hot, windy days, apply early in the day and in shade, if possible.

Protect surfaces from rainfall for six hours following treatment. Many surfaces need several days to develop optimum water repellency.

**Cleanup ...** Immediately clean tools, equipment, and overspray with soap and warm water.

#### PRECAUTIONS

DO NOT DILUTE OR ALTER. MIX THOROUGHLY PRIOR TO USE. DO NOT FREEZE. INTRAGUARD will not hide existing surface stains. Do not apply to surfaces with temperatures of <4.4° C or >35° C. Prevent from being spilled or over sprayed onto nearby water sources. Temporary darkening of some substrates may occur. Protect surfaces from rainfall for a minimum of six hours following treatment. If rainfall occurs and surface turns white, thoroughly flush surface and reapply product when dry. For above grade applications, INTRAGUARD will not prevent water penetration through structural cracks or open joints. Not intended for use on surfaces that will be constantly submerged in water. Apply a small test patch application prior to full-scale application. Refer to Safety Data Sheet for complete health and safety information.

**MASTERFORMAT NUMBER AND TITLE CLAUSE**  
03 35 00 – Concrete Finishing

#### LEED INFORMATION

May help contribute to LEED credits:

- MRc9: Construction and Demolition Waste Management
- EQc2: Low-Emitting Materials [For Healthcare and Schools (exterior-applied products) ONLY]

**For most current data sheet, further LEED information, and SDS, visit [www.wrmeadows.com](http://www.wrmeadows.com).**

2019-04-22

© SEALTIGHT is a registered trade mark of W. R. Meadows

**WARRANTY:** W. R. Meadows of Canada warrants that, at the time and place we make shipment, our materials will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTY, EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM OF TRADE OR OTHERWISE. As the exclusive remedy for breach of this Warranty, we will replace defective materials, provided, however, that the buyer examine the materials when received and promptly notify us in writing of any defect before the materials are used or incorporated into a structure. Three (3) months after W. R. Meadows of Canada has shipped the materials, all our Warranty and other duties with respect to the quality of the materials delivered shall conclusively be presumed to have been satisfied, all liability therefore terminates and no action for breach of any such duties may thereafter be commenced. W. R. Meadows of Canada shall in no event be liable for consequential damages. Unless otherwise agreed to in writing, no warranty is made with respect to materials not manufactured by W. R. Meadows of Canada. We cannot warrant or in any way guarantee any particular method of use or application or the performance of materials under any particular condition. Neither this Warranty nor our liability may be extended or amended by our salesmen, distributors or representatives, or by our distributor's representatives, or by any sales information or drawings.