



DATA SHEET NO. 3900-422

MEADOW-PATCH® 20

Light Grey, Fast Setting, General Purpose Cementitious Repair Mortar

DESCRIPTION

MEADOW-PATCH 20 is a one-component, cementitious, fast setting restoration/repair mortar. The product has a light grey color and is designed for vertical, overhead, and horizontal applications. This fast setting, low slump repair mortar may be troweled, shaped, molded, and shaved before taking a final set. MEADOW-PATCH 20 is an excellent patching solution for difficult vertical and overhead applications without using expensive and intricate forming techniques.

USES

MEADOW-PATCH 20 is easy to mix and apply. This fast setting, low slump mortar is designed to minimize downtime. Because of its versatility, MEADOW-PATCH 20 can be used vertically, horizontally, or overhead. Whether the installation is interior or exterior, MEADOW-PATCH 20 is an excellent choice for fast repairs above-, below-, or on-grade. Typical applications include repairs to curb and gutters, precast concrete elements, tie-rod holes, concrete pipe, columns, beams, or any other general-purpose repairs.

FEATURES/BENEFITS

- Architectural-grade, light grey colour.
- Low slump design for easy molding and shaping/No forms needed.
- May be feather-edged/Tenacious bond.
- May be used vertically, horizontally, or overhead/Highly versatile.
- Excellent freeze-thaw characteristics/Long term repair stability.
- Fast setting/Increases turnaround time.
- Highly suitable for precast and cast-in-place concrete patching.
- Designed to aesthetically blend with typical concrete.
- Suitable for concrete pipe construction work.

PACKAGING

22.7 Kg (50 Lb.) Pails

22.7 Kg (50 Lb.) Bags

COVERAGE

MEADOW-PATCH 20 yield package is 0.013 m³ (0.45 ft.³).

SHELF LIFE

One year from date of manufacture when stored indoors on pallets in a cool, dry area. Do not store product outside.

TECHNICAL DATA

Set times per ASTM C191

Initial: 8 - 12 minutes

Final: 15 - 20 minutes

Compressive strength per ASTM C 109

@ 3 hours: 8.2 MPa (1,200 psi)

@ 1 day: 17.2 MPa (2,500 psi)

@ 7 days: 41.3 MPa (6,000 psi)

@ 28 days: 44.8 MPa (6,500 psi)

For jobs requiring a faster set time, MEADOW-PATCH 5 from W. R. MEADOWS is recommended.

APPLICATION

Surface Preparation ... Prepare concrete substrate in accordance with International Concrete Repair Institute (ICRI) Technical Guideline #310.2: Specifying Concrete Surface Preparation for Sealers, Coatings, and Polymer Overlays. Mechanically roughen or high pressure water-jet existing concrete substrate to a minimum concrete surface profile (CSP) of four or higher, depending on substrate condition. Remove all unsound concrete and provide a profiled, porous surface. Substrate must be structurally sound, dust-free, and free of grease, oil, dirt, curing compounds, release agents, or any other surface or penetrated contaminants that will adversely affect bond. Sanding, cup grinding, or wire-abrading are not approved surface preparation methods. Substrate must be saturated, surface dry (SSD) and free of standing water.

Continued over ...

W. R. MEADOWS® OF CANADA

70 Hannant Court, Milton, ON L9T 5C1
Phone: (905) 878-4122 • Fax: (905) 878-4125

Montreal Sales: (877) 405-5186

Hampshire, IL / Cartersville, GA / York, PA / Fort Worth, TX
Benicia, CA / Pomona, CA / Goodyear, AZ / Milton, ON
St. Albert, AB

www.wrmeadows.com

Prime SSD substrate with slurry coat consisting of two parts powder to one part water or ACRY-LOK™ from W. R. MEADOWS (for enhanced bonding). Do not allow slurry coat to become dry or tack-free. If slurry coat becomes dry or tack-free prior to application of the bulk mix, reapply slurry coat after the already primed substrate has been properly saturated to SSD condition. For increased bond, prime substrate with REZI-WELD™ 1000 medium-viscosity structural bonding agent from W. R. MEADOWS and follow surface prep and application procedures as outlined on that data sheet.

Mixing ... MEADOW-PATCH 20 requires 3.3 – 3.78 L (3.5 – 4 quarts) of potable water per unit depending on desired consistency. Mix for three minutes or until homogenous and lump-free. Do not mix more material than can be placed and finished within 8 - 12 minutes at 25° C (77° F). Do not over-mix. MEADOW-PATCH 20 may be mixed with 4.7 L (1.25 U.S. gal.) of ACRY-LOK per unit to achieve greater durability and enhanced performance.

Placement ... Compact MEADOW-PATCH 20 into properly prepared SSD substrate prior to bulk placement. Finish surface with a wood or steel trowel or sponge float. MEADOW-PATCH 20 may be applied up to 51 mm (2"). Do not re-temper or over-work product. Follow American Concrete Institute (ACI) 305 "Standard on Hot Weather Concreting" or 306 "Standard on Cold Weather Concreting" when applicable.

Curing ... Cure MEADOW-PATCH 20 immediately following application using a suitable water-based curing compound from W. R. MEADOWS or in accordance with ACI 308, 1100-CLEAR or 1220-WHITE from W. R. MEADOWS is recommended for curing. (Do not use solvent-based curing compounds.) When conditions exist for early water loss, such as, but not limited to, high temperature [32° C (90° F)], high winds, direct sun, low humidity, or thin and/or small area patches, wet curing is recommended for 24 hours, immediately followed by an application of 1100-CLEAR or 1220-WHITE curing compound.

PRECAUTIONS

MEADOW-PATCH 20 is recommended for concrete repairs only. Not intended to be used as a self-levelling underlayment or topping. MEADOW-PATCH 20 is designed as a trowel down repair mortar. Do not apply below 1.7°C (35°F) or above 32.2°C (90°F) or when rain is imminent. Protect from freezing for a minimum 24 hours. Do not bridge moving cracks. Extend existing control, construction, and expansion joints through MEADOW-PATCH 20. For large areas with no control, expansion, or construction joints, refer to ACI guidelines. The length-to-width ratio of the repair area should not exceed 2 to 1. Do not add any admixtures. Exceeding liquid requirements shall result in reduced physical

properties. Realize that set time will decrease as the product, air, substrate, and mixing liquid temperature increases and will increase as the temperature decreases. Featheredging may result in reduced durability and performance. Maximum application thickness should not exceed 51 mm (2") when applied neat. Protect from conditions that may cause early water loss: wind, low humidity, high temperature, direct sunlight. Early water loss is amplified in thin applications. Failure to follow industry standard practices may result in decreased material performance.

HEALTH AND SAFETY

Avoid direct contact with this product, as it may cause skin and eye irritation. Utilize gloves and safety glasses to minimize direct contact. Avoid inhalation of dust. Inhalation may cause respiratory irritation and/ or lung disease (silicosis). This product contains silicon dioxide, which is classified by the IARC and NTP as probably carcinogenic to humans (IARC Group 2A). The use of NIOSH approved respiratory protection is recommended in dusty environments. Refer to Material Safety Data Sheet for complete Health and Safety Information. Keep product out of reach of children.

MASTERFORMAT NUMBER AND TITLE

03 01 40.71 - Rehabilitation of Precast Concrete

LEED INFORMATION

May help contribute to LEED credits:

- MR Credit 2: Construction Waste Management
- MR Credit 4: Recycled Content
- MR Credit 5: Regional Materials

For most recent data sheet, further LEED information, and MSDS, visit www.wrmeadows.com.

2015-02-16



© SEALTIGHT is a registered trade mark of W. R. Meadows.

WARRANTY: W. R. Meadows of Canada warrants that, at the time and place we make shipment, our materials will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTY, EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM OF TRADE OR OTHERWISE. As the exclusive remedy for breach of this Warranty, we will replace defective materials, provided, however, that the buyer examine the materials when received and promptly notify us in writing of any defect before the materials are used or incorporated into a structure. Three (3) months after W. R. Meadows of Canada has shipped the materials, all our Warranty and other duties with respect to the quality of the materials delivered shall conclusively be presumed to have been satisfied, all liability therefore terminates and no action for breach of any such duties may thereafter be commenced. W. R. Meadows of Canada shall in no event be liable for consequential damages. Unless otherwise agreed to in writing, no warranty is made with respect to materials not manufactured by W. R. Meadows of Canada. We cannot warrant or in any way guarantee any particular method of use or application or the performance of materials under any particular condition. Neither this Warranty nor our liability may be extended or amended by our salesmen, distributors or representatives, or by our distributor's representatives, or by any sales information or drawings