



W. R. MEADOWS[®]

SEALTIGHT[®]

DATA SHEET NO. 3930-399

SPEED-E-ROC[™]

Rapid-Setting Anchoring Cement Grout

DESCRIPTION

SPEED-E-ROC is a pourable, rapid setting and hardening, high strength, hydraulic cement compound designed for anchoring and grouting. SPEED-E-ROC has a controlled expansion system and is non-shrink. SPEED-E-ROC has a set time of 10 – 20 minutes at 25° C and obtains 34.4 MPa in one hour.

USES

SPEED-E-ROC is ideally suited for anchoring rails, bolts, ties, dowels, reinforcing steel, threaded rods, sign posts, parking meters, street signs, and ornamental steel work into concrete or any other properly-prepared, porous, hardened material. SPEED-E-ROC may be used as a precision, highly flowable and rapid-setting grout for machinery base plates, bearing plates and columns. It is suitable for industrial, residential and civil engineering applications. The product can be used in interior or exterior applications and freeze-thaw environments.

FEATURES/BENEFITS

- Very rapid hardening and setting properties.
- Suitable for exterior and interior applications.
- Freeze-thaw stable.
- Very high one-hour and 24-hour strengths.
- Controlled expansion.
- Cement-based; contains no chloride accelerators.
- Grey colour; similar appearance to concrete.
- Non-metallic; contains no chlorides.
- Easy to use; just mix with water.
- Very pourable.
- Accelerates Portland cement based materials.

PACKAGING

3.6 Kg Tub
22.7 Kg Pail

COVERAGE

Pail yields 0.014 m³ (0.50 ft.³). Tub yields 0.0022 m³ (0.08 ft.³). Yields are based on 3.8 L of water per pail of SPEED-E-ROC and will vary based on substrate profile, variations in mix water amounts, and waste. Field trials should be performed to determine yields based on jobsite conditions.

SHELF LIFE

Two years from date of manufacture when stored indoors on pallets in a dry, cool area. Do not store product outside.

TECHNICAL DATA

The following physical properties were obtained using the water to powder ratio of 3.8 L/22.7 kg of SPEED-E-ROC at 23.8° C.

Set Time (Per ASTM C 191)	10 – 20 minutes
Controlled Expansion	0.08%
Compressive Strength (Per ASTM C 109 – air cured)	
@ 1 hour	27.6 MPa
@ 24 hours	40 MPa
@ 28 days	48.9 MPa

All technical data is typical information, but may vary due to testing methods, conditions, and operators.

APPLICATION

For Anchoring into Concrete or Porous Hardened Material

Surface Preparation ... Substrate must be structurally sound and free of any contaminants that will adversely affect bond. Drill anchor hole using a rotary percussion hammer. Prepared surface must be dust-free and have a sufficient profile to ensure adequate mechanical lock.

Pre-soak repair zone prior to application of SPEED-E-ROC to a saturated, surface dry (SSD) condition and free of standing water.

Anchor bolts must be installed utilizing a washer. The anchor hole diameter shall be no larger than what is required for the anchor bolt and washer assembly to slide to the bottom of anchor hole and rest on bolt head.

W. R. MEADOWS[®] OF CANADA

70 Hannant Court, Milton, ON L9T 5C1
38 Rayborn Crescent, St. Albert, AB T8N 4B1
(800) 342-5976
Montreal Sales: (877) 405-5186

Hampshire, IL / Cartersville, GA / York, PA / Fort Worth, TX
Benicia, CA / Pomona, CA / Goodyear, AZ / Milton, ON
St. Albert, AB
www.wrmeadows.com

Grouting ... Substrate must be structurally sound and free of any contaminant that will adversely affect bond. Prepared surface must be dust-free and have a sufficient profile to ensure adequate mechanical lock. Pre-soak repair zone prior to application of SPEED-E-ROC to a SSD condition and free of standing water. Ensure forming system is watertight to avoid excessive leakage of SPEED-E-ROC from the grout zone. Use a suitable release agent, such as DUOGARD® from W. R. MEADOWS, on forms to aid in the removal process.

Mixing ... Mix one part potable water to six parts of SPEED-E-ROC or until homogenous, ump-free, pourable mixture is obtained.

Mix 22.7 kg pail with approximately 3.8. L of potable water. Mix 3.6 kg tub with approximately 0.6 L of potable water.

PRECAUTIONS

Not intended to be used as an underlayment or overlay. Do not apply below 35° F (1.7° C) or above 95° F (35° C) or when rain is imminent. Protect from freezing for a minimum of 24 hours. SPEED-E-ROC should be crowned or shaped as to allow water flow away from anchor and/or coated with a concrete sealer or penetrating sealer. SPEED-E-ROC is not intended to be used in submerged or continuously wet applications. Do not add any admixtures. Exceeding liquid requirements shall result in reduced physical properties. Realize that set time will decrease as the product, air, substrate, and mixing liquid temperature increases and will be increased as the temperature decreases. Failure to follow industry standard practices may result in decreased material performance.

HEALTH AND SAFETY

Avoid inhalation of dust. Avoid direct contact with this product. Utilize gloves and safety glasses to minimize direct contact. If contact occurs, wash affected areas with mild soap and water. Keep product out of reach of children. For industrial use only. Refer to Safety Data Sheet for complete health and safety information.

MASTERFORMAT NUMBER AND TITLE

03 62 13 - Non-Metallic Non-Shrink Grouting

LEED INFORMATION

May help contribute to LEED credits:

- MR Credit 2: Construction Waste Management
- MR Credit 5: Regional Materials

For most recent data sheet, further LEED information, and SDS, visit www.wrmeadows.com.

2015-07-24



© SEALTIGHT is a registered trade mark of W. R. Meadows

WARRANTY: W. R. Meadows of Canada warrants that, at the time and place we make shipment, our materials will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTY, EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM OF TRADE OR OTHERWISE. As the exclusive remedy for breach of this Warranty, we will replace defective materials, provided, however, that the buyer examine the materials when received and promptly notify us in writing of any defect before the materials are used or incorporated into a structure. Three (3) months after W. R. Meadows of Canada has shipped the materials, all our Warranty and other duties with respect to the quality of the materials delivered shall conclusively be presumed to have been satisfied, all liability therefore terminates and no action for breach of any such duties may thereafter be commenced. W. R. Meadows of Canada shall in no event be liable for consequential damages. Unless otherwise agreed to in writing, no warranty is made with respect to materials not manufactured by W. R. Meadows of Canada. We cannot warrant or in any way guarantee any particular method of use or application or the performance of materials under any particular condition. Neither this Warranty nor our liability may be extended or amended by our salesmen, distributors or representatives, or by our distributor's representatives, or by any sales information or drawings.