



DATA SHEET NO. 4726-000

POURTHANE® NS Non-Sag Joint Sealant

DESCRIPTION

POURTHANE NS is an elastomeric, low-modulus, one-component, moisture-curing, non-sag, polyurethane sealant. The product requires no mixing and typically requires no priming to bond to many materials, including concrete and masonry.

USES

POURTHANE NS has very good adhesion to most construction materials. It is particularly recommended for expansion joints between precast concrete panels and seams on wooden, aluminum, and PVC joinery. POURTHANE NS is highly recommended for bonding concrete and baked clay roof tiles. The product is designed for the civil and industrial construction markets.

FEATURES/BENEFITS

- Ready to use and easy to gun and tool/No mixing and speeds application.
- Low VOC content.
- +/- 35% joint movement capability/Maintains flexibility in moving joints.
- No primer required for most construction materials/Cost reduction.
- Maintains excellent weather resistance/Gives long lasting joint seal.
- Delivers a practical service temperature range/Can be used in all climates.
- Packaged in cartridges, sausages, and in bulk/Jobsite waste is reduced.
- Superior bonding/Long lasting baked clay roof tile application.

PACKAGING

300 mL (10.1 Oz.) Cartridges (24/Carton)
592 mL (20 Oz.) Sausages (20/Carton)
18.9 L (5 Gal.) Pails

AVAILABLE COLOURS

Limestone, Stone, Medium Bronze, Special Bronze, Off White, White, Gray, Aluminum Gray, Tan, Redwood Tan, Black

SHELF LIFE

When stored indoors and in original, unopened containers at temperatures between 4° - 35° C, shelf life is one year from date of manufacture, except for pails, which have a shelf life of six months.

COVERAGE

This chart shows the approximate number of lineal meters that can be sealed per litre. One litre is approximately three cartridges.

Joint Depth	Joint Width						
	6.4 mm (1/4" mm)	9.5 mm (3/8")	12.7 mm (1/2")	15.9 mm (5/8" mm)	19.1 mm (3/4")	22.2 mm (7/8")	25.4 mm (1")
6.4 mm (1/4")	93.9	62.5	46.9	37.2			
9.5 mm (3/8")				25	20.7	17.7	15.5
12.7 mm (1/2")					15.5	13.4	11.6

When estimating, figure 3 cartridges/L (11 cartridges/gal)..

Cubic cm/gal. – 1000 cm³ (231 in.³)

Cubic cm/cartridge – 344.13 cm³ (21 in.³)

For triangular cross-section joints:

6.35 mm (1/4") each side – 49.6 m/L (616 linear ft./gal.)

12.7 mm (1/2") each side – 12.4 m/L (154 linear ft./gal.)

19.1 mm (3/4") each side – 5.5 m/L (68 linear ft./gal.)

SPECIFICATIONS/STANDARDS

- ASTM C 920-11, Type S, Grade NS, Class 35, Use T₁, T₂, NT, O, M, G, A
- Federal Specification TT-S-00230C, Type II, Class A
- ISO 11600-F-25LM

Continued over ...

W. R. MEADOWS® OF CANADA
70 Hannant Court, Milton, ON L9T 5C1
21 Streambank Ave., Sherwood Park, AB T8H 1N1
(800) 342-5976
Montreal Sales: (514) 865-2406

Hampshire, IL / Cartersville, GA / York, PA / Fort Worth, TX
Benicia, CA / Pomona, CA / Goodyear, AZ / Milton, ON
Sherwood Park, AB
www.wrmeadows.com
info@wrmeadows.com

TECHNICAL DATA

Property	Typical Value	Test Method
Tensile Strength, MPa (psi)	1.24 (180)	ASTM D412
Elongation	903%	ASTM D412
Tear Strength, pli	7.39 kN/m (42.2 lb./in.)	ASTM D624
Peel on Aluminum-Dry	23 c.f.	ASTM C794
Peel on Glass-Dry	28 c.f.	ASTM C794
Peel on Concrete Mortar-Dry	25 c.f.	ASTM C794
Shore A Hardness	30 - 40	ASTM C661
Specific Gravity @ 20° C	1.27	
Movement Capability	±35	ASTM C719
Stain and Color Change	Pass	ASTM C510
Weathering Resistance	Excellent	ASTM C793
Substrate Staining	None	
UV Resistance	Good	
Rheological Properties	Pass	ASTM C639
Application Temperature	5° - 40° C	
Service Range	-40° to 82.2° C	
Tack-Free	165 Minutes	ASTM C679
Final Cure	4 - 7 days	
Paint Compatibility	Water-Based: Compatible	
	Solvent-Based: Check Compatible	
VOC Content	96 g/L	

APPLICATION

Surface Preparation ... Substrate must be clean, dry, and free of dust and grease. Be sure interfaces are free of curing compounds and/or saw residue.

Application Method ... POURTHANE NS can be applied with a manual or pneumatic caulking gun. Use typical joint sealing practices and proper joint design of 2:1 width to depth ratio when applying. Horizontal joints require a minimum of 6.4 mm (1/4") depth and maximum 12.7 mm (1/2") depth. CERA-ROD™ from W. R. MEADOWS may be used as a joint backing material to control sealant depth and provide joint configuration. Condition material to 65° - 75° F (18.3° - 23.9° C) before using. After application, the product can be smoothed with a damp knife.

Cleanup ... Application tools can be cleaned with toluene or xylene before curing. Afterwards, mechanical cleaning will be required.

PRECAUTIONS

Check for compatibility to materials and working techniques not outlined above. POURTHANE NS must be fully cured prior to installation of other materials over the product. Do not apply on wet substrates. Do not apply at temperatures outside application temperature range. (See physical properties chart.) For joints subject to water immersion, use DECK-O-SEAL® 125 and/or DECK-O-SEAL GUN GRADE with REZI-WELD™ 1000 from W. R. MEADOWS.

MASTERFORMAT NUMBER AND TITLE

07 92 13 - Elastomeric Joint Sealants
32 13 73 - Concrete Paving Joint Sealants

LEED INFORMATION

May help contribute to LEED credits:

- MRc9: Construction and Demolition Waste Management
- EQc2: Low-Emitting Materials [For Healthcare and Schools (exterior-applied products) ONLY]

For most current data sheet, further LEED information, and SDS, visit www.wrmeadows.com.

2020-04-27



© SEALTIGHT is a registered trade mark of W. R. Meadows

WARRANTY: W. R. Meadows of Canada warrants that, at the time and place we make shipment, our materials will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTY, EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM OF TRADE OR OTHERWISE. As the exclusive remedy for breach of this Warranty, we will replace defective materials, provided, however, that the buyer examine the materials when received and promptly notify us in writing of any defect before the materials are used or incorporated into a structure. Three (3) months after W. R. Meadows of Canada has shipped the materials, all our Warranty and other duties with respect to the quality of the materials delivered shall conclusively be presumed to have been satisfied, all liability therefore terminates and no action for breach of any such duties may thereafter be commenced. W. R. Meadows of Canada shall in no event be liable for consequential damages. Unless otherwise agreed to in writing, no warranty is made with respect to materials not manufactured by W. R. Meadows of Canada. We cannot warrant or in any way guarantee any particular method of use or application or the performance of materials under any particular condition. Neither this Warranty nor our liability may be extended or amended by our salesmen, distributors or representatives, or by our distributor's representatives, or by any sales information or drawings.