



W. R. MEADOWS

SEALIGHT

DATA SHEET NO. 7110-501

501 FOUNDATION COATING

DESCRIPTION

501 FOUNDATION COATING solvent-type dampproofing is an asbestos-free, fibered and non-fibered asphalt compound containing an exclusive wetting agent to convert a naturally hydrophobic surface to a hydrophilic surface to assure proper coating adhesion. 501 FOUNDATION COATING is flexible and will span small holes and hairline cracks. The product will withstand temperature changes and will not crack under normal expansion and contraction.

USES

501 FOUNDATION COATING solvent-type dampproofing is ideal for reducing dampness and moisture infiltration through foundation walls, parapets, fire walls, tanks, culverts, cisterns, and bridge abutments. The product is also applicable for stone-backing, above-grade cavity wall applications, and below-grade masonry wall dampproofing. 501 FOUNDATION COATING also helps to minimize internal structural damage from mildew and mold. With the addition of a reinforcing fabric, it can also be used as a waterproofing coating.

FEATURES/BENEFITS

- Ready to use ... no heating or thinning required.
- Dries rapidly ... fast and economical way to protect concrete and masonry foundation walls from moisture penetration.
- Easy to apply ... no special equipment needed.

PACKAGING

18.9 Litre (5 U.S. Gallon) Pails
205 Litre (54 U.S. Gallon) Drums

COVERAGE

Coverage is 0.39 - 0.74 m²/L (16 - 30 ft.²/gal.) depending on porosity of the surface.

SHELF LIFE

When stored indoors in original, unopened containers at temperatures between 4° - 32° C, optimum performance and best use is obtained within two years of date of manufacture.

SPECIFICATIONS

- CGSB 37-GP-6Ma
- Complies with Canada VOC Concentration Limits for Architectural Coatings Regulations

TECHNICAL DATA

Appearance	Black
Solids	63%
Weight	0.93 kg/L (7.8 lb./U.S. gal.)
Drying Time	Touch dry: 4 hours @ 21° C Firm dry: 24 hours
Flammability	Wet: Flammable Dry: Burns
Water Content	1% Maximum

APPLICATION

Surface Preparation ... All surfaces to be coated must be thoroughly cleaned of all scale, loose mortar, dust, rust, dirt, oil, grease, and other foreign matter. Use a wire brush, sandblast, or other methods in keeping with good construction practices. Before product application, fill voids, cracks, and holes in concrete with cement mortar and allow to dry. At temperatures below 4° C, use a prime coat of 600 ASPHALT PRIMER from W. R. MEADOWS, applied at a minimum rate of 4.1 m²/L (200 ft.²/U.S. gal.). Apply at least one coat of 501 FOUNDATION COATING at a minimum rate of 0.39 - 0.74 m²/L (16 - 30 ft.²/gal.). Do not apply in rain or when rain is threatening.

Continued over ...

W. R. MEADOWS® OF CANADA
70 Hannant Court, Milton, ON L9T 5C1
38 Rayborn Crescent, St. Albert, AB T8N 4B1
(800) 342-5976
Montreal Sales: (877) 405-5186

Hampshire, IL / Cartersville, GA / York, PA / Fort Worth, TX
Benicia, CA / Pomona, CA / Goodyear, AZ / Milton, ON
St. Albert, AB
www.wrmeadows.com

Backfilling ... Backfilling should be done within 24 to 48 hours after application. Protect cured application from damage by using PROTECTION COURSE (VIBRAFLEX® PC) and MEL-DRAIN™ from W. R. MEADOWS. Prolonged exposure to ultraviolet sunrays should be minimized.

Cleanup ... While still wet, material may be removed with mineral spirits. Once dried, the material can be removed with kerosene or petroleum naphtha. Solvent manufacturer precautions should be adhered to when using a solvent for cleanup.

HEALTH AND SAFETY

Handle as a combustible product. Read and follow application information and precautions. Refer to Safety Data Sheet for complete health and safety information.

MASTERFORMAT NUMBER AND TITLE

07 11 13 - Bituminous Dampproofing

LEED INFORMATION

May help contribute to LEED credits:

- MRc9: Construction and Demolition Waste Management

For most current data sheet, further LEED information, and SDS, visit www.wrmeadows.com.



2017-03-03

© SEALTIGHT is a registered trade mark of W. R. Meadows

WARRANTY: W. R. Meadows of Western Canada warrants that, at the time and place we make shipment, our materials will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTY, EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM OF TRADE OR OTHERWISE. As the exclusive remedy for breach of this Warranty, we will replace defective materials, provided, however, that the buyer examine the materials when received and promptly notify us in writing of any defect before the materials are used or incorporated into a structure. Three (3) months after W. R. Meadows of Western Canada has shipped the materials, all our Warranty and other duties with respect to the quality of the materials delivered shall conclusively be presumed to have been satisfied, all liability therefore terminates and no action for breach of any such duties may thereafter be commenced. W. R. Meadows of Western Canada shall in no event be liable for consequential damages. Unless otherwise agreed to in writing, no warranty is made with respect to materials not manufactured by W. R. Meadows of Western Canada. We cannot warrant or in any way guarantee any particular method of use or application or the performance of materials under any particular condition. Neither this Warranty nor our liability may be extended or amended by our salesmen, distributors or representatives, or by our distributor's representatives, or by any sales information or drawings.