



DATA SHEET NO. 7110-505

505 SEALMASTIC™ Fibrated Foundation Coating

DESCRIPTION

505 SEALMASTIC fibrated foundation coating is an asphalt-based, cutback type, fibrated dampproofing coating.

USES

505 SEALMASTIC fibrated foundation coating is designed to be used for dampproofing and waterproofing masonry and concrete walls and for dampproofing and waterproofing concrete floors.

FEATURES/BENEFITS

- Ready to use ... no heating or thinning required.
- Dries rapidly ... fast and economical way to protect concrete and masonry foundation walls from moisture penetration.
- Easy to apply ... no special equipment needed.
- Crack resistant.

PACKAGING

18.9 Litre (5 U.S. gallon) Pails

COVERAGE

Coverage is 0.39 - 0.74 m²/L (16 - 30 ft.²/gal.) depending on porosity of the surface.

SHELF LIFE

When stored indoors in original, unopened containers at temperatures between 4° - 32° C, optimum performance and best use is obtained within two years of date of manufacture.

SPECIFICATIONS

Complies with CGSB 37-GP-16M. To be applied according to CGSB 37-GP-36M.

TECHNICAL DATA

Colour:	Black
Solids:	61%
Weight:	1 kg/L (10 lb./gal.)
Drying Time:	Touch dry: 3.5 hours Firm dry: 24 hours
Flammability	Wet: Flammable Dry: Burns
Water Content	1% Maximum
Flash Point	40° C

APPLICATION

Surface Preparation ... Surface shall be firm and free from loose particles, cracks, grease, oil, and other foreign matter. Surface must be free from frost, snow, and ice.

Application Method ... At temperatures below 4° C, use a prime coat of 600 ASPHALT PRIMER from W. R. MEADOWS applied at a minimum rate of 4.1 m²/L (200 ft.²/U.S. gal.). Apply by spray or brush at least one coat of 505 SEALMASTIC. Protect cured application from damage by using PROTECTION COURSE (VIBRAFLEX® PC) and MEL-DRAIN™ from W. R. MEADOWS.

PRECAUTIONS

If there is excessive hydrostatic pressure on the surface, a more complete waterproofing specification must be used. Consult a technical representative for further assistance. If material has thickened due to low temperatures, leave the containers in a heated building overnight. **Do not heat with an open flame.** Contains flammable solvents. Keep away from heat and open flames. Use in a well-ventilated area. Avoid use where solvent odours are objectionable

MASTERFORMAT NUMBER AND TITLE

07 11 13 - Bituminous Dampproofing

W. R. MEADOWS® OF CANADA
70 Hannant Court, Milton, ON L9T 5C1
38 Rayborn Crescent, St. Albert, AB T8N 4B1
(800) 342-5976
Montreal Sales: (877) 405-5186

Hampshire, IL / Cartersville, GA / York, PA / Fort Worth, TX
Benicia, CA / Pomona, CA / Goodyear, AZ / Milton, ON
St. Albert, AB
www.wrmeadows.com

LEED INFORMATION

May help contribute to LEED credits:

- IEQ Credit 3.1: Construction Indoor Air Quality Management Plan – During Construction
- MR Credit 2: Construction Waste Management
- MR Credit 5: Regional Materials

For most recent data sheet, further LEED information, and SDS, visit www.wrmeadows.com.

2016-10-24



© SEALTIGHT is a registered trade mark of W. R. Meadows

WARRANTY: W. R. Meadows of Western Canada warrants that, at the time and place we make shipment, our materials will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTY, EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM OF TRADE OR OTHERWISE. As the exclusive remedy for breach of this Warranty, we will replace defective materials, provided, however, that the buyer examine the materials when received and promptly notify us in writing of any defect before the materials are used or incorporated into a structure. Three (3) months after W. R. Meadows of Western Canada has shipped the materials, all our Warranty and other duties with respect to the quality of the materials delivered shall conclusively be presumed to have been satisfied, all liability therefore terminates and no action for breach of any such duties may thereafter be commenced. W. R. Meadows of Western Canada shall in no event be liable for consequential damages. Unless otherwise agreed to in writing, no warranty is made with respect to materials not manufactured by W. R. Meadows of Western Canada. We cannot warrant or in any way guarantee any particular method of use or application or the performance of materials under any particular condition. Neither this Warranty nor our liability may be extended or amended by our salesmen, distributors or representatives, or by our distributor's representatives, or by any sales information or drawings.