



W. R. MEADOWS

SEALIGHT

## DATA SHEET NO. 6332-000

### BEM One-Component Waterproofing Membrane

#### DESCRIPTION

BEM is a one-component, cold-applied, non-slump waterproofing material that can be used for a variety of applications with building envelope products from W. R. MEADOWS. BEM cures to form a tough, flexible waterproofing membrane. BEM is a high quality moisture curing elastomeric waterproofing and sealing material.

#### USES

BEM can be used in the forming of fillets and reinforcement at corners and as a flashing material.

#### FEATURES/BENEFITS

- Bonds to asphalt and concrete.
- Solvent-free; will not shrink.
- Skins over in 50 minutes.
- Does not freeze.
- Cures to a tough, flexible membrane.

#### PACKAGING

828 mL (28 Oz.) Cartridges (12 per Carton)

#### COVERAGE

As a corner reinforcement and fillet, approximately 1.1 m/L (14 lineal ft./gal.). For a 76.2 mm (3") flashing, approximately 1.4 m/L (17 lineal ft./gal.) As a fillet, approximately 10.9 m/L (135 lineal ft./gal.).

#### SHELF LIFE

When stored indoors and in original, unopened containers at temperatures between 4° - 21° C (40° - 70° F), shelf life is one year from date of manufacture.

#### SPECIFICATIONS

- Canada VOC Concentration Limits for Architectural Coatings Regulations

#### TECHNICAL DATA

VOC Content: 42 g/L

#### APPLICATION

**Surface Preparation ...** All surfaces to be covered with BEM should be clean, free of all contaminants, dry, and frost-free.

**Application Method ...** Trowel on BEM to a minimum thickness of 90 mils. BEM may be applied to both primed and unprimed asphalt and concrete surfaces. Apply in 76.2 mm (3") or 101.6 mm (4") wide strips of material over terminations. When used as a corner reinforcement, apply a minimum of 152.4 mm (6") wide in each direction. When used as a fillet, the face should be a minimum of 19.1 mm ( $\frac{3}{4}$ "). At drains and protrusions, BEM should overlap the AIR-SHIELD™, MEL-ROL®, and/or PRECON® membrane at a minimum of 50.8 mm (2") and should extend 152.4 mm (6") above the surface or to the top of the wearing course.

If applying fresh material over the cured membrane, the cured membrane should be lightly washed and wiped with alcohol. Allow for a few minutes to dry and trowel on the fresh material.

**Drying Time ...** 50 minutes +/- 15 minutes. Discard material that begins to thicken and becomes difficult to apply. BEM will cure to form a tough, flexible membrane.

**Cleanup ...** Tools can be cleaned with alcohol. Follow manufacturer's precautions when using alcohol for cleanup. Cured material is best removed by mechanical means.

#### PRECAUTIONS

BEM is not to be used as a liner in a water-containing structure or as an exposed or wearing surface. BEM is a fluid-applied waterproofing membrane that is designed to be used as part of a complete waterproofing and drainage system. Do not use on surfaces that are later to be painted. Do not store in high temperatures. Refer to Safety Data Sheet for complete health and safety information.

#### MASTERFORMAT NUMBER AND TITLE

07 14 00 – Fluid-Applied Waterproofing  
07 14 16 – Cold Fluid-Applied Waterproofing

Continued Over ...

**W. R. MEADOWS® OF CANADA**  
70 Hannant Court, Milton, ON L9T 5C1  
38 Rayborn Crescent, St. Albert, AB T8N 4B1  
(800) 342-5976  
Montreal Sales: (877) 405-5186

Hampshire, IL / Cartersville, GA / York, PA / Fort Worth, TX  
Benicia, CA / Pomona, CA / Goodyear, AZ / Milton, ON  
St. Albert, AB  
[www.wrmeadows.com](http://www.wrmeadows.com)

## LEED INFORMATION

May help contribute to LEED credits:

- EA Credit 1: Optimize Energy Performance
- IEQ Credit 3.1: Construction Indoor Air Quality Management Plan: During Construction
- IEQ Credit 4.2: Low-Emitting Materials – Paints and Coatings
- IEQ Credit 7.1: Thermal Comfort – Design
- MR Credit 2: Construction Waste Management
- MR Credit 5: Regional Materials

For most recent data sheet, further LEED Information, and SDS, visit [www.wrmeadows.com](http://www.wrmeadows.com).



2015-12-22

© SEALTIGHT is a registered trade mark of W. R. Meadows

**WARRANTY:** W. R. Meadows of Western Canada warrants that, at the time and place we make shipment, our materials will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTY, EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM OF TRADE OR OTHERWISE. As the exclusive remedy for breach of this Warranty, we will replace defective materials, provided, however, that the buyer examine the materials when received and promptly notify us in writing of any defect before the materials are used or incorporated into a structure. Three (3) months after W. R. Meadows of Western Canada has shipped the materials, all our Warranty and other duties with respect to the quality of the materials delivered shall conclusively be presumed to have been satisfied, all liability therefore terminates and no action for breach of any such duties may thereafter be commenced. W. R. Meadows of Western Canada shall in no event be liable for consequential damages. Unless otherwise agreed to in writing, no warranty is made with respect to materials not manufactured by W. R. Meadows of Western Canada. We cannot warrant or in any way guarantee any particular method of use or application or the performance of materials under any particular condition. Neither this Warranty nor our liability may be extended or amended by our salesmen, distributors or representatives, or by our distributor's representatives, or by any sales information or drawings.