



PC2R PROTECTION COURSE

Waterproofing Protection Course

DESCRIPTION

PC2R PROTECTION COURSE is a 94 mil (2.4 mm) thick SBS (styrene-butadiene-styrene) modified bitumen protection course. The product consists of a fiberglass mat saturated and coated with an asphaltic and SBS elastomer blend, ensuring a durable, flexible, and easy to install protection course.

This elastomeric asphaltic blend provides high elasticity and flexibility to the sheet. The fiberglass reinforcement ensures high tensile strength, dimensional stability, and puncture- and tear-resistance.

USES

PC2R PROTECTION COURSE is designed to be utilized as a protection course with HRM 714 and HYDRALASTIC™ 836 from W. R. MEADOWS. PC2R PROTECTION COURSE provides protection from damage caused by foot traffic. In high traffic areas with vehicular traffic, or areas where extreme physical abuse is anticipated, use PROTECTION COURSE PC-3 from W. R. MEADOWS. Place overburden within 30 days of application of PC2R PROTECTION COURSE. PC2R PROTECTION COURSE is used in-between slab construction, such as plaza decks, roof terraces, promenade decks, pedestrian concourses, tunnels, parking garage decks, and planter boxes.

FEATURES/BENEFITS

- Supplied in easily to apply rolls – labor savings.
- Bottom surface of the Sanded-Sanded design ensures adhesion to the still liquid-hot waterproofing membrane.
- Top surface of the Sanded-Sanded design provides improved slip resistance.
- Tough, durable and flexible
- Full width fiberglass matting improves flexural strength.
- Easily cut with a roofer's knife or shears for fitting at protrusions

PACKAGING

Roll Dimensions: 39 3/8" x 49' 1" (1 m x 15 m). Each roll is approximately 161 sq. ft. (14.96 sq. m) gross and approximately 150 sq. ft. (13.94 sq. m) net depending on overlap pattern.

Roll Weight - 94 lb./roll (43 kg/m²)

SHELF LIFE

Five years when properly stored. Store PC2R PROTECTION COURSE palletized and protect from direct sun and physical damage. Do not store at temperatures above 100° F (38° C) or in direct sun for extended periods of time. Do not double-deck pallets.

SPECIFICATIONS/STANDARDS

- ASTM D6163 Type I, Grade S

TECHNICAL DATA

Physical Properties (ASTM D5147)	Typical Test Results
Thickness	94 Mils (2.38 mm)
Tensile Strength (lbf./in), 0°F (MD/XMD)	120/110 lbf./in
Tensile Strength (lbf./in), 73°F (MD/XMD)	97/67 lbf./in
Elongation (% @ Max Load), 0°F, (MD/XMD)	4%
Elongation (% @ Max Load), 73°F (MD/XMD)	3%
Tear Strength (lbf.), (MD/XMD), 73°F	105/75 lbf.
Low Temperature Flexibility	0°F (-18°C)
Dimensional Stability, %	<0.2%

CONTINUED ON REVERSE SIDE ...

W. R. MEADOWS, INC.

P.O. Box 338 • HAMPSHIRE, IL 60140-0338
 Phone: 847/214-2100 • Fax: 847/683-4544
 1-800-342-5976
www.wrmeadows.com • info@wrmeadows.com

HAMPSHIRE, IL / CARTERSVILLE, GA / YORK, PA
 FORT WORTH, TX / BENICIA, CA / POMONA, CA
 GOODYEAR, AZ / MILTON, ON / SHERWOOD PARK, AB

APPLICATION

Roll out and embed into the hot, liquid-tacky HRM 714 and HYDRALASTIC 836 and over lap 2 - 3". Light roll or broom into place. For added waterproofing and protection against protrusions, seal all laps with HRM 714. PC2R PROTECTION COURSE should be installed in such as fashion to form a continuous protective layer that is tightly bonded over the entire waterproofing membrane.

LIMITATIONS

PC2R PROTECTION COURSE is not compatible with HYDRALASTIC 836 SL, some Polyether & most Urethane waterproofing membranes, oils and solvents. Where PC2R PROTECTION COURSE is adhered to a waterproofing membrane, use an approved adhesive. Do not apply PC2R PROTECTION COURSE over liquid waterproofing membranes containing volatile solvents until all of the solvent has evaporated. Compatibility to other building materials or products is the sole responsibility of the specifier or end-user. Consult membrane manufacturer for specific application details prior to placing PC2R PROTECTION COURSE. Read and follow application information and precautions. Refer to Safety Data Sheet for complete health and safety information.

For most current data sheet, further LEED information, and SDS, visit www.wrmeadows.com.



LIMITED WARRANTY

W. R. MEADOWS, INC. warrants at the time and place we make shipment, our material will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. Read complete warranty. Copy furnished upon request.

Disclaimer

The information contained herein is included for illustrative purposes only, and to the best of our knowledge, is accurate and reliable. W. R. MEADOWS, INC. cannot however under any circumstances make any guarantee of results or assume any obligation or liability in connection with the use of this information. As W. R. MEADOWS, INC. has no control over the use to which others may put its product, it is recommended that the products be tested to determine if suitable for specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect or engineer, contractor and owner for the design, application and proper installation of each product. Specifier and user shall determine the suitability of products for specific application and assume all responsibilities in connection therewith.