



MasterFormat: 07 13 00

DECEMBER 2023

PRECON® PLUS TAPE

Polymeric Waterproofing Membrane Tape

DESCRIPTION

PRECON PLUS TAPE is a composite sheet membrane comprised of a polyolefin film, elastomeric membrane and a release paper. It is nominally 60 mils thick and is nominally 12" (304.8 mm) wide.

USES

PRECON PLUS TAPE is design to be used to bond the end laps of PRECON PLUS. PRECON PLUS TAPE will also be used for detailing side laps of PRECON PLUS in special conditions as such shotcrete installations.

FEATURES/BENEFITS

- Self-adhesive.
- Easy to apply with removable release paper.
- Provides a secure, durable bond.
- Conforms to ASTM D5385 when used with PRECON PLUS to form the overlap detail.
- Installations down to 20° F (-7° C).
- Primeless Installation, no need to wait for primer to dry.

PACKAGING

12" (nominal) x 50' (203.2 mm x 15.24 m) Rolls, 4/Cartron.

SHELF LIFE

When stored indoors between 40° - 90° F (4° - 32° C), optimum performance and best use is obtained within two years of date of manufacture.

SPECIFICATIONS/STANDARDS

- Conforms to ASTM D5385 when used with PRECON PLUS to form the end and side lap detail.

APPLICATION

Application Method.... Ensure that the PRECON PLUS is dry, clean, dust-free, and free of dew, frost, grease, oil, dirt, curing compounds, release agents, coatings, or any other surface contaminants that will adversely affect the bond.

Remove the release paper on the one side of the PRECON PLUS TAPE and overlap 6" (152.4 mm) onto both sides of the end or side lap and roll press the tape onto the PRECON PLUS. Roll press using a linoleum type roller at least three times. The elastomeric membrane is a pressure sensitive membrane forming adhesive that must be properly pressed rolled to ensure adequate bond.

Reference the END LAP or SIDE LAP TAPING METHOD TECHNICAL BULLETIN at www.wrmeadows.com for detailed visual installation instructions.

PRECAUTIONS

Concrete should be poured within 60 days of membrane installation. Extended UV exposure over 60 days will require reinstallation of PRECON PLUS TAPE. Minimum PRECON PLUS surface, PRECON PLUS TAPE, and air temperature must be 20° F (-7° C) and rising at time of installation.

For most recent data sheet, sustainability information, and SDS, visit www.wrmeadows.com.

CONTINUED ON THE REVERSE SIDE ...

W. R. MEADOWS, INC.

P.O. Box 338 • HAMPSHIRE, IL 60140-0338
Phone: 847/214-2100 • Fax: 847/683-4544
1-800-342-5976
www.wrmeadows.com • info@wrmeadows.com

HAMPSHIRE, IL / CARTERSVILLE, GA / YORK, PA
FORT WORTH, TX / BENICIA, CA / POMONA, CA
GOODYEAR, AZ / MILTON, ON / SHERWOOD PARK, AB



LIMITED WARRANTY

W. R. MEADOWS, INC. warrants at the time and place we make shipment, our material will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. Read complete warranty. Copy furnished upon request.

Disclaimer

The information contained herein is included for illustrative purposes only, and to the best of our knowledge, is accurate and reliable. W. R. MEADOWS, INC. cannot however under any circumstances make any guarantee of results or assume any obligation or liability in connection with the use of this information. As W. R. MEADOWS, INC. has no control over the use to which others may put its product, it is recommended that the products be tested to determine if suitable for specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect or engineer, contractor and owner for the design, application and proper installation of each product. Specifier and user shall determine the suitability of products for specific application and assume all responsibilities in connection therewith.