



DATA SHEET NO. 071916-795

DECK-O-SHIELD™

Concrete Deck, Waterfall, and Natural Stone Sealer

DESCRIPTION

DECK-O-SHIELD is a ready-to-use, water-based sealer/water repellent for natural stone, concrete, and masonry surfaces. DECK-O-SHIELD is designed for use as a sealer/water repellent on waterfalls in or around swimming pools; the product will limit the penetration of water into structurally sound, crack-free surfaces. The product can also be used as a sealer/water repellent for natural stone decks, walkways, or patios; virtually any area located near or around swimming pool areas. Surfaces treated with DECK-O-SHIELD will inhibit the penetration of salts, reducing "whitening" or staining.

USES

DECK-O-SHIELD weatherproofs and protects virtually all waterfalls, decks, porches, patios, and walkways around pools, including the following surfaces: natural stone, mortar joint, concrete, brick, concrete block, stucco.

Another advantage DECK-O-SHIELD provides is that the product will not alter the colour or tint of the surface after application. There is no need for worry when applying DECK-O-SHIELD, because the product will have no adverse effects on surface appearance after application.

FEATURES/BENEFITS

- Breathable – allows moisture in cured concrete to evaporate.
- DECK-O-SHIELD is not a film-forming material – it penetrates the surface to form an integral barrier to moisture penetration.
- Transparent, non-staining.
- Surface appearance after application and complete drying is virtually unchanged.
- Reduces entrapment of dirt particles and other contaminants that cause discolouration; inhibits soiling.
- Protects against efflorescence and rust staining.
- Helps resist stains from spills.
- Protects against salt staining and "whitening" caused by salt in the water.
- Water-based, VOC compliant.
- One component.

PACKAGING

3.78 Litre (1 U.S. Gallon) Containers
18.9 Litre (5 U.S. Gallon) Pails

COVERAGE*

Natural Stone **	1.84 – 4.29 m ² /L (75 - 175 ft. ² /U.S. gal.)
Concrete	2.45 – 4.29 m ² /L (100 - 175 ft. ² /U.S. gal.)
Masonry	2.45 – 4.29 m ² /L (100 - 175 ft. ² /U.S. gal.)
Stucco Surfaces	1.47 – 2.45 m ² /L (60 - 100 ft. ² /U.S. gal.)
Concrete Block**	1.23 – 2.45 m ² /L (50 - 100 ft. ² /U.S. gal.)

*Always apply a test area to determine actual coverage rates. Coverage rates will vary greatly, due to the porosity of the substrate.

**Due to porosity, certain stone and block applications may require a significant increase in coverage rates –additional applications may be necessary.

SHELF LIFE

When stored indoors and in original, unopened containers at temperatures between 4° - 32° C (40° - 90° F), shelf life is a minimum of two years from date of manufacture.

TECHNICAL DATA

Dry to Touch	1 – 2 hours (Typical) Allow 12 – 14 hours between coats for multiple coat applications
Colour	Milky white Emulsion

Continued over ...

W. R. MEADOWS OF CANADA
70 Hannant Court, Milton, ON L9T 5C1
Phone: (905) 878-4122 • Fax: (905) 878-4125
Montreal Sales: (877) 405-5186

Hampshire, IL / Cartersville, GA / York, PA / Fort Worth, TX
Benicia, CA / Pomona, CA / Goodyear, AZ / Milton, ON
St. Albert, AB
www.wrmeadows.com

APPLICATION

Surface Preparation ... Protect people, vehicles, property, plants, and all non-masonry surfaces from product, splash, residue, and wind drift. Thoroughly clean the surface. Though DECK-O-SHIELD may be applied to slightly damp surfaces, best performance is achieved on a clean, thoroughly dried and absorbent surface. Excessive moisture inhibits penetration, reducing the service life and performance of the treatment. Always test for compatibility. Surfaces must be structurally sound, clean, and free from dirt, efflorescence, and stains.

Surface and Air Temperatures ... Optimum surface and air temperature is 4° - 35° C (40° - 95° F) during application and eight hours after. If freezing conditions exist before application, let surface to receive treatment thaw. The DECK-O-SHIELD water carrier may freeze at low temperatures or evaporate at high temperatures. Both conditions impair penetration and results.

Equipment ... Apply with brush, roller, or low-pressure spray (<0.34 MPa [<50 psi]), depending on surface texture, area, etc. Fan tips are recommended for sprayers. A Chapin 1949 sprayer with a 0.3785 Lpm (0.1 gpm) nozzle is recommended.

Test Application ... Always perform a test application on each type of surface prior to full-scale application to determine suitability and final appearance. Test using the recommended application instructions. Let area dry thoroughly before inspection.

Vertical Application Instructions ... For best results, apply to a visibly dry and absorbent surface.

Spray ... Saturate from the bottom up, creating a 10 - 20 cm (4" - 8") rundown below the spray contact point. Let the first application penetrate for 5 - 10 minutes. Re-saturate while surface still appears moist. Less product will be needed for the second application.

Brush or Roller ... Saturate uniformly. Let penetrate for 5 - 10 minutes. Brush out heavy runs and drips that do not penetrate.

Dense Surface Application Instruction ... Apply a single coat. Use enough to completely wet the surface without creating drips, puddles or rundown. DO NOT OVER APPLY. Test for application rate.

Horizontal Application Instructions ... Saturate in a single application. Use enough to keep surface wet for 2 - 3 minutes before penetration. Broom out any puddles or drips until they soak in.

Note: Hot, windy conditions will evaporate the water carrier, reducing penetration and performance. On hot, windy days, apply early in the day and in shade, if possible. Treated surfaces dry to touch in 1 - 2 hours. Protect surfaces from rainfall for six hours following treatment. Many surfaces need several days to develop optimum water repellency.

Additional Coats ... Once the surface being treated has received the optimum amount of DECK-O-SHIELD, any additional coats will bead up on the surface. Discontinue application once this occurs. The CS-309™, EXPO-GLOSS®, DECRA-SEAL™, and VOCOMP® series of products, as well as HIAC®, all from W. R. MEADOWS, can be applied over a surface treated with DECK-O-SHIELD. The resulting barrier will provide water beading, and depending on product used, will also provide a glossy surface appearance. The initial application of DECK-O-SHIELD must be applied properly and at recommended application rate.

Clean Up ... Immediately clean tools, equipment and overspray with soap and warm water.

PRECAUTIONS

DO NOT DILUTE OR ALTER. MIX CONTAINER THOROUGHLY PRIOR TO USE. DO NOT FREEZE. DECK-O-SHIELD is a water repellent, not a waterproofing or vapour barrier. It will not hide existing surface stains. DECK-O-SHIELD should not be applied to surfaces that are to receive caulks or sealants. Application over fully cured elastomeric sealants typically will not affect the sealant. Do not apply to surfaces with temperatures of <4° C (40° F) or >35° C (95° F). Prevent from being spilled or over sprayed onto nearby water sources. Temporary darkening of some substrates may occur. Apply a small test patch application prior to full-scale application. Refer to material safety data sheet for complete health and safety information.

MASTERFORMAT NUMBER AND TITLE

07 19 00 – Water Repellents

For most recent data sheet, further LEED information, and MSDS, visit www.deckoseal.com.

2013-07-31



© SEALTIGHT is a registered trade mark of W. R. Meadows

WARRANTY: W. R. Meadows of Canada warrants that, at the time and place we make shipment, our materials will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTY, EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM OF TRADE OR OTHERWISE. As the exclusive remedy for breach of this Warranty, we will replace defective materials, provided, however, that the buyer examine the materials when received and promptly notify us in writing of any defect before the materials are used or incorporated into a structure. Three (3) months after W. R. Meadows of Canada has shipped the materials, all our Warranty and other duties with respect to the quality of the materials delivered shall conclusively be presumed to have been satisfied, all liability therefore terminates and no action for breach of any such duties may thereafter be commenced. W. R. Meadows of Canada shall in no event be liable for consequential damages. Unless otherwise agreed to in writing, no warranty is made with respect to materials not manufactured by W. R. Meadows of Canada. We cannot warrant or in any way guarantee any particular method of use or application or the performance of materials under any particular condition. Neither this Warranty nor our liability may be extended or amended by our salesmen, distributors or representatives, or by our distributor's representatives, or by any sales information or drawings.

W. R. MEADOWS OF CANADA
70 Hannant Court, Milton, ON L9T 5C1
Phone: (905) 878-4122 • Fax: (905) 878-4125
Montreal Sales: (877) 405-5186

Hampshire, IL / Cartersville, GA / York, PA / Fort Worth, TX
Benicia, CA / Pomona, CA / Goodyear, AZ / Milton, ON
St. Albert, AB

www.wrmeadows.com