



DATA SHEET NO. 7200-724

AIR-SHIELD™ LM

Liquid Membrane Air/Vapour Barrier and Liquid Moisture Barrier

DESCRIPTION

AIR-SHIELD LM is a single-component, liquid-applied, water-based, polymer-modified air/vapour and liquid moisture barrier. AIR-SHIELD LM cures to form a tough, seamless, elastomeric membrane, which exhibits excellent resistance to air and moisture transmission.

USES

AIR-SHIELD LM has been specifically formulated to act as an air/vapour and liquid moisture barrier within the building envelope. It may be applied to most common surfaces and integrated into various wall systems. AIR-SHIELD LM is suitable for both new construction and restoration. Primary applications include cavity wall and masonry wall construction. AIR-SHIELD LM works equally well as an air and/or vapour barrier on precast concrete, cast-in-place concrete, masonry (concrete block), interior and exterior gypsum board, Styrofoam, primed steel, aluminum mill finish, anodized aluminum, primed galvanized metal, drywall, and plywood.

FEATURES/BENEFITS

- Low permeability – prevents the transmission of air and inhibits moisture and vapour from passing through porous building materials.
- Highly flexible – bridges cracks, which may form in the substrate.
- User friendly – single-component, water-based technology allows for simple, safe application and easy cleanup
- Liquid applied – simplifies detailing and assures a monolithic, seamless membrane when applied to a rough or smooth surface.
- Sprayable – with appropriately configured airless spray equipment – low application costs.
- Excellent adhesion – remains firmly bonded to the substrate, even when applied over damp surfaces.
- VOC content is 0.0 g/L. Produces no harmful odours.
- Compatible with other asphalt-based emulsion products.
- May be applied to “green” concrete.
- Self-sealing: Nails and fasteners can be used without compromising performance.

PACKAGING

18.9 Litre (5 U.S. Gallon) Pails
208.2 Litre (55 U.S. Gallon) Drums*
*Available upon special order only

COVERAGE

Application Rate 0.49 - 0.61 m²/L
(20 – 25 ft.²/gal.)

Wet Film Thickness 60 mil (1.5 mm)

Cured Film Thickness 45 mil (1.15 mm)

Coverage dependant on substrate type, weather, and application conditions.

SHELF LIFE

When stored indoors in original, unopened containers at temperatures between 4° - 32° C, optimum performance and best use is obtained within six months of date of manufacture.

SPECIFICATIONS

- Meets CAN/CGSB-51-33, Type 1 Water Vapour Permeance Requirements.
- 2010 National Building Code of Canada.
- Complies with Canada VOC Concentration Limits for Architectural Coatings Regulations.

TECHNICAL DATA

% Solids	70
Colour	Black
Elongation (ASTM D-412)	1500%
Water Vapour Permeance (ASTM E-96, Procedure B)	IBC Class I Vapour Retarder 0.1 Perms or Less
Service Temperature	-29° - 60° C (-20° - 140° F)
Application Temperature	Above -1° C (30° F)
Storage Temperature	4° C to 30° C (40° F to 90° F)

Air Leakage

Test Method	ASTM E 2178-01	ASTM E 2357
Pressure	75 Pa (1.57 lb./ft. ²)	75 Pa (1.57 lb./ft. ²)
AIR-SHIELD LM Results	<0.02 L/S/M ² (<0.004 cfm/ft. ²)	<0.2 L/S/M ² (<0.04 cfm/ft. ²)

*Independent tests available upon request.

Continued Over ...

W. R. MEADOWS® OF CANADA
70 Hannant Court, Milton, ON L9T 5C1
38 Rayborn Crescent, St. Albert, AB T8N 4B1
(800) 342-5976
Montreal Sales: (877) 405-5186

Hampshire, IL / Cartersville, GA / York, PA / Fort Worth, TX
 Benicia, CA / Pomona, CA / Goodyear, AZ / Milton, ON
 St. Albert, AB
www.wrmeadows.com

APPLICATION

Surface Preparation ... All surfaces must be clean (free of all coatings and curing compounds), structurally sound, and relatively smooth. Prepare substrate per manufacturer's instruction prior to application of membrane.

Exterior Sheathing Panels ... Exterior sheathing panels are to be installed and fastened per manufacturer's recommendation. For detailed application information, see INSTALLATION INSTRUCTIONS: JOINT TREATMENT OF EXTERIOR SHEATHING PANELS WHEN USING AIR-SHIELD LM available at www.wrmeadows.com.

Rough Openings and Protrusions ... Refer to AIR-SHIELD ROUGH OPENINGS INSTALLATION GUIDELINES document available at www.wrmeadows.com for recommendations on protrusions and rough openings.

Concrete Masonry Units ... Before applying AIR-SHIELD LM to CMU surfaces, patch all cracks, protrusions, small voids, offsets, details, irregularities, and small deformities with MEADOW-PATCH® 5 or MEADOW-PATCH 20 from W. R. MEADOWS at least two hours before application.

Application Method ... AIR-SHIELD LM may be applied by spraying or by using a 19 mm (3/4") minimum nap roller. (For recommendations on spray equipment, consult W. R. MEADOWS technical staff.)

Thoroughly, mechanically mix AIR-SHIELD LM prior to application. AIR-SHIELD LM may be sprayed on at a minimum coverage thickness of 60 mils wet (45 mils dry). Note: A single coat may achieve desired thickness. However, if material slumps due to temperature or substrate conditions, two coats (30 mils wet) may be necessary to obtain the 60 mils wet thickness. Apply the second coat after the first coat has dried (approximately one to two hours). Frequently inspect surface area with a wet mil gauge to ensure consistent thickness. Work material well into any fluted rib forming indentations. Porous masonry block walls may require additional coats to obtain desired thickness. AIR-SHIELD LM may be exposed to open air for 30 - 40 days, depending on specific weather conditions at jobsite.

Curing and Drying ... Allow material to dry at air and surface temperatures of -1° C (30° F) or higher. Curing times will be affected by relative humidity, temperature, and airflow. The following times are given for average conditions and standard thicknesses. Actual times may differ, depending on specific conditions present on job at time of application. It is recommended that AIR-SHIELD LM be allowed to air dry to a tack-free film before application of specified insulation.

Tack free film: 1 hour
Full cure: 48 hours

Cleanup ... Uncured AIR-SHIELD LM cleans up easily while wet with water. Cured material is best removed by xylene (xylol) or by mechanical means.

PRECAUTIONS

AIR-SHIELD LM is not designed to perform as a permanently exposed membrane. Keep containers tightly sealed. **KEEP FROM FREEZING.** Do not apply AIR-SHIELD LM if rainfall is forecast or imminent. Do not apply AIR-SHIELD LM when air, material, and surface temperatures are expected to fall below -1° C (30° F) within four hours of completed application.

LEED INFORMATION

May help contribute to LEED credits:

- EA Credit 1: Optimize Energy Performance
- IEQ Credit 3.1: Construction Indoor Air Quality Management Plan - During Construction
- IEQ Credit 4.2: Low-Emitting Materials – Paints and Coatings
- IEQ Credit 7.1: Thermal Comfort – Design
- MR Credit 2: Construction Waste Management
- MR Credit 5: Regional Materials

MASTERFORMAT NUMBER AND TITLE

07 27 26 – Fluid-Applied Membrane Air Barriers

For CAD details, most recent data sheet, further LEED information, and SDS, visit www.wrmeadows.com.



2016-11-18

© SEALTIGHT is a registered trade mark of W. R. Meadows

WARRANTY: W. R. Meadows of Canada warrants that, at the time and place we make shipment, our materials will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTY, EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM OF TRADE OR OTHERWISE. As the exclusive remedy for breach of this Warranty, we will replace defective materials, provided, however, that the buyer examine the materials when received and promptly notify us in writing of any defect before the materials are used or incorporated into a structure. Three (3) months after W. R. Meadows of Canada has shipped the materials, all our Warranty and other duties with respect to the quality of the materials delivered shall conclusively be presumed to have been satisfied, all liability therefore terminates and no action for breach of any such duties may thereafter be commenced. W. R. Meadows of Canada shall in no event be liable for consequential damages. Unless otherwise agreed to in writing, no warranty is made with respect to materials not manufactured by W. R. Meadows of Canada. We cannot warrant or in any way guarantee any particular method of use or application or the performance of materials under any particular condition. Neither this Warranty nor our liability may be extended or amended by our salesmen, distributors or representatives, or by our distributor's representatives, or by any sales information or drawings.