

NO. 727-A

OCTOBER 2016  
(Supersedes February 2015)

## HYDRASTOP SA

### Pre-Applied Waterproofing Membrane

#### DESCRIPTION

HYDRASTOP SA is a composite, self-adhered sheet membrane comprised of a non-woven fabric, elastomeric membrane, and coated release paper. Once concrete is poured against HYDRASTOP SA and the concrete cures, a mechanical bond forms that secures the concrete to the membrane. The HYDRASTOP SA system is comprised of the HYDRASTOP SA membrane as well as MEL-DRAIN™ composite drainage board from W. R. MEADOWS.

#### USES

HYDRASTOP SA is used as a pre-applied waterproofing membrane in vertical applications where access to the site requires a pre-applied waterproofing membrane prior to pouring the foundation walls.

#### FEATURES/BENEFITS

- Provides a waterproof seal between the membrane and poured concrete wall.
- Helps prevent moisture migration into the structure.

#### PACKAGING

39" x 50' (991 mm x 15.2 m) long rolls, one roll per carton. Store cartons on pallets and cover if left outside. Keep materials away from sparks and flames.

#### APPLICATION

**Surface Preparation ...** Inspect all surfaces for any conditions detrimental to the proper completion of the work. Surfaces should be structurally sound. Remove debris or any other foreign material that could damage the membrane.

**Application Method ...** HYDRASTOP SA may be applied at temperatures down to 40° F (5° C). MEL-PRIME™ from W. R. MEADOWS should be used to enhance the bond at the selvage edge when conditions warrant it.

**Membrane Application ...** Mechanically attach with fasteners every 12" (304.8 mm) across the top, within ½" (13 mm) of the top edge of the membrane. Install the membrane with the fabric side facing toward the concrete pour. Remove release paper and roll press onto MEL-DRAIN drainage board.

Prior to application of the blindside membrane, attach MEL-DRAIN™ rolled matrix drainage system from W. R. MEADOWS to lagging or soil retention system.

Remove release paper on 3" (76.1 mm) overlap. Apply membrane and roll press into place with a tile type roller.

**End Laps ...** Overlap membrane 6" (152.4 mm). Prior to overlap, apply BEM, HYDRALASTIC 836, or MEL-ROL® LIQUID MEMBRANE (two-component) from W. R. MEADOWS in area to be lapped. Roll press membrane into BEM, HYDRALASTIC 836, or MEL-ROL LIQUID MEMBRANE. At terminations of membrane, apply BEM, HYDRALASTIC 836 or MEL-ROL LIQUID MEMBRANE 12" (304.8 mm) wide centered over the termination and while still wet, embed 12" (304.8 mm) wide DETAIL FABRIC into the HYDRALASTIC 836 or MEL-ROL LIQUID MEMBRANE and roll press into place. Ensure that DETAIL FABRIC is centered over the termination with 6" (152.4 mm) on each side of lap edge. Apply additional HYDRALASTIC 836 on all terminations of DETAIL FABRIC.

**Penetrations and Protrusions ...** Detail around all horizontal and vertical penetrations using MEL-ROL LIQUID MEMBRANE (two-component). Apply MEL-ROL LIQUID MEMBRANE by forming a fillet around the pipe or protrusion, overlapping the fabric side of HYDRASTOP SA and the protrusion a minimum of 2.5" (64 mm). If the gap between the protrusion and the membrane is greater than ½" (13 mm), apply DETAIL FABRIC over the fully-cured MEL-ROL LIQUID MEMBRANE (minimum 24 hours cure required). All penetration and protrusion surfaces must be clean, rust-free, and sound prior to application of MEL-ROL LIQUID MEMBRANE.

**Patching ...** Prior to pouring, inspect membrane for punctures or damage and repair as necessary with HYDRALASTIC 836 and/or DETAIL FABRIC..

#### PRECAUTIONS

Concrete should be poured within 60 days of membrane installation. For installations below 40° F (4° C), contact W. R. MEADOWS technical services. When using bar supports, use those with a flat bottom.

*CONTINUED ON REVERSE SIDE...*

**W. R. MEADOWS, INC.**

P.O. Box 338 • HAMPSHIRE, IL 60140-0338  
Phone: 847/214-2100 • Fax: 847/683-4544  
1-800-342-5976  
[www.wrmeadows.com](http://www.wrmeadows.com)

HAMPSHIRE, IL / CARTERSVILLE, GA / YORK, PA  
FORT WORTH, TX / BENICIA, CA / POMONA, CA  
GOODYEAR, AZ / MILTON, ON / ST. ALBERT, AB

**LEED INFORMATION**

May help contribute to LEED credits:

- EA Credit 1: Optimize Energy Performance
- IEQ Credit 3.1: Construction Indoor Air Quality Management  
Plan: During Construction
- IEQ Credit 7.1: Thermal Comfort – Design
- MR Credit 2: Construction Waste Management
- MR Credit 5: Regional Materials

**TECHNICAL DATA**

Property	Test Method	HYDRASTOP SA Results
Color		Black
Thickness	ASTM D 1000	90 Mils (Nominally)
Low Temp Flexibility	ASTM D 1970, 180° @ -25° F (-32° C)	Pass
Resistance to Hydrostatic Head	ASTM D 5385-93	230' (70 m)
Elongation	ASTM D 412-06	> 400%
Crack Cycling	ASTM C 836 @ -15° F (-26° C)	Pass
Puncture Resistance	ASTM E 154	260 lb. (1155 N)
Peel Adhesion to Concrete	ASTM D 903	10 lb./in (1754 N/m)
Resistance to Penetration by Termites	Texas A&M Method Percentage of Penetration	0.0%
Resistance to Penetration by Pesticides	ASTM F 2130 Percentage of Penetration	0.0%



**LIMITED WARRANTY**

W. R. MEADOWS, INC. warrants at the time and place we make shipment, our material will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. Read complete warranty. Copy furnished upon request.

**Disclaimer**

The information contained herein is included for illustrative purposes only, and to the best of our knowledge, is accurate and reliable. W. R. MEADOWS, INC. cannot however under any circumstances make any guarantee of results or assume any obligation or liability in connection with the use of this information. As W. R. MEADOWS, INC. has no control over the use to which others may put its product, it is recommended that the products be tested to determine if suitable for specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect or engineer, contractor and owner for the design, application and proper installation of each product. Specifier and user shall determine the suitability of products for specific application and assume all responsibilities in connection therewith.