



MasterFormat:

03 30 00

07 16 16

MARCH 2026

WATERSTOP HPW

Hydrophilic Swell Strip

DESCRIPTION

WATERSTOP HPW is a hydrophilic swell strip composed of synthetic rubber with excellent swelling capabilities. It retains its own shape after wet-drying cycles and is intended for creating watertight sealing of non-moving construction joints. WATERSTOP HPW will provide superior performance over the service life of the structure.

USES

WATERSTOP HPW can be installed both vertically and horizontally. It is used to seal non-moving construction joints against water migration in concrete and reinforced concrete construction, including concrete footings, walls, floors, tunnels, and parking and plaza decks. The waterstop is also used to seal around pipes and other penetrations. WATERSTOP HPW has superior performance up to 6 bar (87 psi) water pressure.

FEATURES/BENEFITS

- Provides both extreme and delayed free-swell properties.
- Provides additional strength and structure.
- Good chemical resistance and swelling capability in high alkaline environments.
- Excellent re-swelling performance during wet/dry cycling.
- Provides controlled swelling.

PACKAGING

Roll size:

3/4" x 1/4" x 33' (20 mm x 5 mm x 10 m)

Five Rolls per Carton

STORAGE AND HANDLING

Protect from moisture. Store indoors on skid or pallet. Storage temperature is -15°F to 165°F (-25°C to 75°C).

APPLICATION

Surface Preparation ... Ensure surfaces are structurally sound, dry, free from protrusions, debris and compounds detrimental to adhesion. Fill minor cracks, voids, and depressions with WATERSTOP LIQUID HPW prior to installation of WATERSTOP HPW.

Application Method ... WATERSTOP HPW is intended for use on vertical and horizontal construction joints and should be recessed a minimum of 3" (76.2 mm) from outside surfaces. Ensure all ends are firmly butted together.

For rough concrete, apply WATERSTOP LIQUID HPW to fill voids and provide additional adhesion to the concrete while preventing water or concrete from seeping under WATERSTOP HPW.

For troweled smooth surfaces, three attachment methods are available.

- Nails/Fasteners: Attach WATERSTOP HPW with a washer nail [1" (25.44 mm) shank] with washer [5/8" -13/16" (15 - 23 mm)]. Tapcon fasteners are recommended.
- Adhesive attachment: standard urethane construction adhesive.
- WATERSTOP LIQUID HPW: Lay a 1/8" - 1/4" (3.2 - 6.4 mm) bead of WATERSTOP LIQUID HPW along the joint. Surfaces to receive the WATERSTOP HPW cannot have protrusions greater than 1/2" (12.7 mm). Press WATERSTOP HPW into uncured WATERSTOP LIQUID HPW and nail every 15" (381 mm) on center. Attach WATERSTOP HPW with a washer nail [1" (25.44 mm) shank] with washer [5/8" -13/16" (15 - 23 mm)]. Butt ends for a continuous application.

CONTINUED ON REVERSE SIDE ...

W. R. MEADOWS, INC.

P.O. Box 338 • Hampshire, IL 60140-0338
 Phone: 847/214-2100 • Fax: 847/683-4544
 1-800-342-5976
 www.wrmeadows.com • info@wrmeadows.com

HAMPSHIRE, IL / CARTERSVILLE, GA / YORK, PA
 FORT WORTH, TX / BENICIA, CA / POMONA, CA
 GOODYEAR, AZ / MILTON, ON / SHERWOOD PARK, AB

Property	WATERSTOP HPW Results
Color	Green
Volume expansion in potable water	500%
Volume expansion in concrete water (High alkalinity)	400%
Hardness, Shore A	35
Tensile Strength	290 psi (2 MPa)
Elongation	>400%

PRECAUTIONS

Keep WATERSTOP HPW dry; protect from exposure to the elements.

For most current data sheet, sustainability information, and SDS, visit www.wrmeadows.com.



LIMITED WARRANTY

W. R. MEADOWS, INC. warrants at the time and place we make shipment, our material will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. Read complete warranty. Copy furnished upon request.

Disclaimer

The information contained herein is included for illustrative purposes only, and to the best of our knowledge, is accurate and reliable. W. R. MEADOWS, INC. cannot however under any circumstances make any guarantee of results or assume any obligation or liability in connection with the use of this information. As W. R. MEADOWS, INC. has no control over the use to which others may put its product, it is recommended that the products be tested to determine if suitable for specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect or engineer, contractor and owner for the design, application and proper installation of each product. Specifier and user shall determine the suitability of products for specific application and assume all responsibilities in connection therewith.