



DATA SHEET NO. 3150-741

ECO-COAT™ Concrete Form Release Agent

DESCRIPTION

ECO-COAT concrete form release agent is a natural oil-based product, which provides quick easy and clean release of concrete forms. ECO-COAT acts as a bond breaker and form cleaner, is non-staining, will not wash off once it has dried, cuts clean-up time, and eliminates voids, defects, and buildup of concrete.

USES

ECO-COAT is used to prevent concrete from bonding to forms. ECO-COAT may be used on sealed or unsealed plywood forms, timber, metal, spiral-wound tube, fiberglass, and plastic. ECO-COAT may also be used to prevent concrete from bonding to paving machines, precast equipment, mixers, vibrators, and other concrete equipment. ECO-COAT is particularly suited to applications where the noxious and flammable vapours of conventional solvent-based release agents are a concern and where a safe, environmentally friendly form release is required.

FEATURES/BENEFITS

- Designed as an all-purpose form release agent.
- Will work well under a variety of situations.
- Comes ready to use.

PACKAGING

18.9 Litre Pail
205 Litre Drum

COVERAGE

The coverage rate of ECO-COAT will vary depending on the method of application and the substrate. The following table is a guide only.

Plywood	12 - 18 m ² /L (600 - 900 ft. ²)
Timber	8 - 16 m ² /L (400 - 800 ft. ² /gal.)
Steel	18 - 30 m ² /L (900 - 1500 ft. ² /gal.)

SHELF LIFE

When stored indoors in original, unopened containers at temperatures between 4° - 32° C, optimum performance and best use is obtained within two years of date of manufacture.

TECHNICAL DATA

Color: Dark Yellow-Amber
Application Temperature: Greater than -10° C

APPLICATION

Surface Preparation ... Ensure that forms are clean, dry, and smooth. If plywood edges are worn, apply a coat or two of ECO-COAT to the edges.

Application Method ... ECO-COAT is suitable for application by sprayer (such as a Chapin 1949), roller, brush, or rag. A low-pressure spray nozzle with a 0.379 LPM (0.1 GPM) spray rate is most commonly used.

Apply ECO-COAT using care not to over-apply. Surface retardation may result from over-application. Two light coats are preferable to one heavy coat. Apply second coat at right angles to the first. Allow a few minutes to dry before placing concrete. All forms should be recoated before each subsequent use.

MASTERFORMAT NUMBER AND TITLE

03 11 00 – Concrete Forming

LEED INFORMATION

May help contribute to LEED credits:

- MRc9: Construction and Demolition Waste Management
- EQc2: Low-Emitting Materials
For Healthcare and Schools (exterior-applied products) ONLY]

Continued over ...

W. R. MEADOWS® OF CANADA
70 Hannant Court, Milton, ON L9T 5C1
38 Rayborn Crescent, St. Albert, AB T8N 4B1
(800) 342-5976
Montreal Sales: (877) 405-5186

Hampshire, IL / Cartersville, GA / York, PA / Fort Worth, TX
Benicia, CA / Pomona, CA / Goodyear, AZ / Milton, ON
St. Albert, AB
www.wrmeadows.com

For most recent data sheet, further LEED information, and SDS, visit www.wrmeadows.com.

2017-11-01



© SEALTIGHT is a registered trade mark of W. R. Meadows

WARRANTY: W. R. Meadows of Canada warrants that, at the time and place we make shipment, our materials will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTY, EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM OF TRADE OR OTHERWISE. As the exclusive remedy for breach of this Warranty, we will replace defective materials, provided, however, that the buyer examine the materials when received and promptly notify us in writing of any defect before the materials are used or incorporated into a structure. Three (3) months after W. R. Meadows of Canada has shipped the materials, all our Warranty and other duties with respect to the quality of the materials delivered shall conclusively be presumed to have been satisfied, all liability therefore terminates and no action for breach of any such duties may thereafter be commenced. W. R. Meadows of Canada shall in no event be liable for consequential damages. Unless otherwise agreed to in writing, no warranty is made with respect to materials not manufactured by W. R. Meadows of Canada. We cannot warrant or in any way guarantee any particular method of use or application or the performance of materials under any particular condition. Neither this Warranty nor our liability may be extended or amended by our salesmen, distributors or representatives, or by our distributor's representatives, or by any sales information or drawings.