



DATA SHEET NO. 7900-442

CERA-ROD™

Non-Gassing, Heat-Resistant Backer Rod

DESCRIPTION

CERA-ROD is a closed-cell, round, flexible, continuous-length, non-absorbent, non-gassing, non-staining, non-shrinking material extruded from a cross-linked polyethylene. Compression/deflection is approximately 55.2 KPa (8 psi) at 25% deflection.

USES

CERA-ROD is used in joints or large cracks in Portland cement or asphalt concrete. It provides the correct sealant reservoir configuration, controls joint depth, and prevents sealant run-out through the bottom of the joint. CERA-ROD also acts as a bond breaker to prevent bottom side sealant adhesion.

FEATURES/BENEFITS

- Works equally well in concrete joints/cracks or asphalt cracks.
- Use with hot-applied joint sealants ... will not melt, shrink, evaporate, or stain.
- Retains its original diameter and is non-gassing when exposed to high sealant temperatures.
- Prevents run-out through voids or bottom of the joint ... saves sealant material.
- Acts as a bond breaker to stop sealant adhesion to the bottom side of the joint.
- Fast and easy to apply.

PACKAGING

Cartons weigh 4.99 kg (11 lb.) each, except the 38.1 mm (1/2") and 50.8 mm (2") sizes that weigh 13.61 kg (30 lb.) each.

SPECIFICATIONS

- ASTM D 5249, Type 1, Type 3

COLOUR

White

STANDARD SIZES

Rod Diameter	Lineal Metres per Carton	Lineal Feet per Carton
9.5 mm (3/8")	1097	3600
12.7 mm (1/2")	762	2500
15.9 mm (5/8")	472.44	1550
22.2 mm (7/8")	259.08	850
25.4 mm (1")	167	550
31.8 mm (1 1/4")	121.92	400
38.1 mm (1 1/2")	168	552
50.8 mm (2")	109	360

APPLICATION

Crack and Joint Preparation ... Remove all dirt and foreign matter.

Application Method ... Install CERA-ROD with a single-wheeled or three-wheeled roller, depending on application. Avoid stretching or puncturing the material. CERA-ROD needs to be held in compression to work effectively. The diameter of the rod should be 3.2 mm (1/8") larger than the width of the joint for joint widths up to 19.1 mm (3/4"). For joints 19.1 mm (3/4") and larger, add 6.4 mm (1/4") to diameter rod selection. Applications for all hot-applied joint sealants from W. R. MEADOWS can follow immediately.

Continued over ...

W. R. MEADOWS® OF CANADA

70 Hannant Court, Milton, ON L9T 5C1
38 Rayborn Crescent, St. Albert, AB T8N 4B1
(800) 342-5976
Montreal Sales: (877) 405-5186

Hampshire, IL / Cartersville, GA / York, PA / Fort Worth, TX
Benicia, CA / Pomona, CA / Goodyear, AZ / Milton, ON
St. Albert, AB
www.wrmeadows.com

PRECAUTIONS

Temperature limit of product is 210° C. Read and follow application information and Safety Data Sheet information.

MASTERFORMAT NUMBER AND TITLE

07 91 23 - Backer Rods

LEED INFORMATION

May help contribute to LEED credits:

- MRc9: Construction and Demolition Waste Management

For most current data sheet, further LEED information, and SDS, visit www.wrmeadows.com.

2018-01-30



© SEALTIGHT is a registered trade mark of W. R. Meadows

WARRANTY: W. R. Meadows of Canada warrants that, at the time and place we make shipment, our materials will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTY, EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM OF TRADE OR OTHERWISE. As the exclusive remedy for breach of this Warranty, we will replace defective materials, provided, however, that the buyer examine the materials when received and promptly notify us in writing of any defect before the materials are used or incorporated into a structure. Three (3) months after W. R. Meadows of Canada has shipped the materials, all our Warranty and other duties with respect to the quality of the materials delivered shall conclusively be presumed to have been satisfied, all liability therefore terminates and no action for breach of any such duties may thereafter be commenced. W. R. Meadows of Canada shall in no event be liable for consequential damages. Unless otherwise agreed to in writing, no warranty is made with respect to materials not manufactured by W. R. Meadows of Canada. We cannot warrant or in any way guarantee any particular method of use or application or the performance of materials under any particular condition. Neither this Warranty nor our liability may be extended or amended by our salesmen, distributors or representatives, or by our distributor's representatives, or by any sales information or drawings.