



W. R. MEADOWS.

SEALTIGHT

DATA SHEET NO. 7900-802

SAFE-SEAL® 3405

High Performance, Cold-Applied, One-Component, Horizontal Crack and Joint Sealant

DESCRIPTION

SAFE-SEAL 3405 is a high performance, polymer-modified asphalt emulsion horizontal joint and crack sealant. It is a one-component, self-leveling material that can easily be poured into openings 3.2 mm up to 25.4 mm (1/8" up to 1") wide. At 24° C (75° F) and 50% humidity, a typical joint of 12.7 mm x 12.7 mm (1/2" x 1/2") becomes tack-free in two hours or less. After full cure, the product will remain flexible at cold temperatures and will not flow at high temperatures.

FEATURES/BENEFITS

- No hot kettle required/ Safe to use; no danger of burns.
- No expensive equipment needed/No equipment maintenance, breakdowns, fires, etc.
- Allows use of smaller, non-specialized crews/ Reduced installation costs.
- Can be applied to damp cracks/Saves time ... no need for joints to fully dry.
- Pours directly from container/ Easy to apply.
- VOC compliant/ Environmentally safe.
- User-friendly/ Easy to clean up.

LEED INFORMATION

- IEQ Credit 4.1: Low Emitting Materials: Adhesives and Sealants
- MR Credit 2: Construction Waste Management
- MR Credit 5: Regional Materials

USE

SAFE-SEAL 3405 is ideal for small-, medium-, or large-scale sealing projects on parking lots, highways, street maintenance, driveways, airport aprons, and runways. SAFE-SEAL 3405 should be used in any application where superior performance is a necessity or where a hot-applied product is either too dangerous or impractical. It offers excellent bonding properties, high resiliency, and resistance to weathering. SAFE-SEAL 3405 may be used wherever the measurable ASTM D 3405 specification is required. It provides a soft, flexible sealant for either concrete or asphalt pavement repairs. This material remains pliable and will not track in warm weather or become brittle and crack in cold weather.

*ADDITIONAL COLD-APPLIED MEADOWS PRODUCTS

- SOF-SEAL® - two-component, cold-applied, polymer horizontal joint sealer
- GARDOX® - two-component, cold-applied, modified coal tar urethane for concrete joints
- CERA-ROD™ - backer rod
- #158 - one-component, cold- and pressure-applied, rubberized asphalt sealant
- DECK-O-SEAL® - two-component, elastomeric, polysulfide-based joint sealant

*W. R. MEADOWS also provides the industry's most extensive line of hot-applied asphalt based sealants to meet a variety of performance requirements.

Continued over

W. R. MEADOWS OF CANADA
70 Hannant Court, Milton, ON L9T 5C1
Phone: (905) 878-4122 • Fax: (905) 878-4125
Montreal Sales: (877) 405-5186

Hampshire, IL / Cartersville, GA / York, PA / Fort Worth, TX
Benicia, CA / Pomona, CA / Goodyear, AZ / Milton, ON /
St. Albert, AB
www.wrmeadows.com

TECHNICAL DATA

UNCURED:

| | |
|----------------|------|
| Solids, % | 72 |
| Viscosity, CPS | 6000 |

CURED:

| | |
|------------------------------------|-------------------|
| Penetration, mm/10 | 70 |
| Resilience, % | 63 |
| Softening Point, ° C | 82 |
| Wt. Per 3.8 litres (1 U.S. gallon) | 3.74 kg (8.3 lb.) |

Surface and Joint Preparation ... The joints and cracks to be sealed must be clean. Dust, dirt, and laitance should be removed prior to application. Proper routing should be slightly larger than existing crack/joint to ensure proper adhesion to sidewalls

Asphalt Pavement and Maintenance Sealing ... For ideal sealing with maximum effectiveness, it is suggested that cracks or joints should be routed out to provide a sealant reservoir 12.7 mm (1/2") wide with a minimum depth of 12.7 mm (1/2"). This provides for a 1:1 width-to-depth ratio. To control and maintain the suggested joint depth and sealant usage, CERA-ROD may be installed in the joint opening

New Concrete Pavement Sealing ... Designated joint width and depth is determined by the appropriate highway or pavement authority. Typical joint configuration would be 9.54 mm (3/8") wide with a minimum 12.7 mm (1/2") depth for an approximate 1:1 width-to-depth ratio. CERA-ROD may be installed in the joint opening to control depth and sealant usage

Application Method ... SAFE-SEAL 3405 should be applied into the crack/joint, slightly overfilling. SAFE-SEAL 3405 may be poured from the container or a commercial sealing pot equipped with a narrow pouring spout and shut-off valve. Once applied, a follow-up should be done with a soft, rubber, U-shaped squeegee to form a wipe zone of approximately 76.2 – 101.6 mm (3" – 4") wide along the crack/joint and flush with the highway or pavement surface.

ADDITIONAL INFORMATION

Colour: Black (cured)
Packaging: 3.78 litre (1 U.S. gallon) container
18.93 litre (5 U.S. gallon) pail
Coverage: A joint 12.7 mm x 12.7 mm (1/2" x 1/2") covers approx. 22.8 metres/3.78 litres (75 lineal ft./U.S.gal.)
Cleanup: Use water before product cures. Once material is cured, use a solvent-based cleaner.
Shelf life: 6 months, when properly stored in unopened container.

PRECAUTIONS

KEEP FROM FREEZING. Storage temperature should not exceed 32° C (90° F). Do not apply SAFE-SEAL 3405 if rainfall is forecast or imminent within 24 hours. Do not apply SAFE-SEAL 3405 when air, material, and surface temperatures are expected to fall below 10° C (50° F) within eight hours of completed application. SAFE-SEAL 3405 is not recommended for sealing cracks or joints in tennis courts.

MASTERFORMAT 2004 NUMBER AND TITLE

32 12 73 Asphalt Paving Joint Sealants

FOR MOST CURRENT DATA SHEET, FURTHER LEED INFORMATION, AND MSDS, VISIT www.wrmeadows.com.

2009-12-1



© SEALTIGHT is a registered trade mark of W. R. Meadows

WARRANTY: W. R. Meadows of Canada warrants that, at the time and place we make shipment, our materials will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTY, EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM OF TRADE OR OTHERWISE. As the exclusive remedy for breach of this Warranty, we will replace defective materials, provided, however, that the buyer examine the materials when received and promptly notify us in writing of any defect before the materials are used or incorporated into a structure. Three (3) months after W. R. Meadows of Canada has shipped the materials, all our Warranty and other duties with respect to the quality of the materials delivered shall conclusively be presumed to have been satisfied, all liability therefore terminates and no action for breach of any such duties may thereafter be commenced. W. R. Meadows of Canada shall in no event be liable for consequential damages. Unless otherwise agreed to in writing, no warranty is made with respect to materials not manufactured by W. R. Meadows of Canada. We cannot warrant or in any way guarantee any particular method of use or application or the performance of materials under any particular condition. Neither this Warranty nor our liability may be extended or amended by our salesmen, distributors or representatives, or by our distributor's representatives, or by any sales information or drawings.