



## 825 PARGE-ALL Pre-Mixed Parging

### DESCRIPTION

825 PARGE-ALL is a single-component sand/cement blend designed for coating or parging vertical surfaces. 825 PARGE-ALL is a pre-mixed blend of sand, cement, chemical admixtures, polypropylene fibre, and acrylic cement modifiers. The acrylic modifiers in 825 PARGE-ALL make it very well suited for the thin coatings that are typical of parging applications.

### USES

825 PARGE-ALL is recommended for parging over rigid foam insulation. 825 PARGE-ALL provides protection for rigid polystyrene insulation against damage by weather, ultraviolet (UV) rays, and normal physical wear. It may also be used directly on concrete foundations.

### PACKAGING

25 Kg Pails

### COVERAGE

Approximately 9.3 m<sup>2</sup> (50 ft.<sup>2</sup>) per 25 kg pail of 825 PARGE-ALL. On rougher surfaces, or if a thicker, highly textured surface is desired, coverage will be reduced.

### SHELF LIFE

One year from date of manufacture when stored indoors on pallets in a dry, cool area. Do not store product outside.

### TECHNICAL DATA

Color	Concrete Grey
	Contains fibers and acrylic polymers
	Non-metallic and contains no chlorides, plasters, or gypsum
Pot Life	45 minutes (approximately)

### APPLICATION

**Surface Preparation ...** Ensure that rigid foam insulation is securely fastened to concrete. The surface shall be firm and free of loose particles, grease, oil and other foreign matter.

Apply self-sticking fibreglass tape over joints between insulation panels, to all outside corners, over fastener heads, and damaged insulation areas.

## DATA SHEET NO. 3900-825

**Mixing ...** Add the 25 kg dry contents to approximately 3.5 liters of water and mix thoroughly with an electric drill (400 - 600 rpm).

The mix will appear dry for the first 30 - 60 seconds of the mixing process.

**DO NOT ADD WATER** at this stage. As mixing continues, the acrylic polymer will re-emulsify, producing a workable mix.

**Application Method ...** Apply 825 PARGE-ALL with a trowel, masonry brush, or other suitable tool, to a thickness of 3 mm (1/8") and create the desired surface texture immediately.

Cover only about 1 m<sup>2</sup> (10.76 ft.<sup>2</sup>) section at one time.

Clean tools periodically to avoid buildup of material.

**Curing ...** Protect against rapid surface evaporation due to heat and wind. Allow to air cure for 48 hours if painting is desired.

**Cleanup ...** All tools must be cleaned with water after use. Cured material can only be removed mechanically.

### PRECAUTIONS

DO NOT apply 825 PARGE-ALL when the temperature is expected to be below 4° C (40° F) within 24 hours or when rain is imminent.

Protect from conditions that may cause early water loss such as: wind, low humidity, high temperatures, and direct sunlight. Early water loss is also amplified in thin applications.

Realize that set time will decrease as the product, air, substrate, and mixing liquid temperature increase and will be increased as the temperature decreases.

When using 825 PARGE-ALL on extruded foam, rasping is necessary to create a surface profile for proper bonding.

Continued over ...

**W. R. MEADOWS OF CANADA**  
70 Hannant Court, Milton, ON L9T 5C1  
21 Streambank Ave., Sherwood Park, AB T8H 1N1  
(800) 342-5976  
Montreal Sales: (877) 405-5186

Hampshire, IL / Cartersville, GA / York, PA / Fort Worth, TX  
Benicia, CA / Pomona, CA / Goodyear, AZ / Milton, ON /  
Sherwood Park, AB  
[www.wrmeadows.com](http://www.wrmeadows.com)

Follow hot weather concreting practices when applying 825 PARGE-ALL at temperatures exceeding 25° C, or under sunny and windy conditions.

If the foam has been degraded by UV exposure, the damaged surface is to be removed to provide a sound surface prior to the application of 825 PARGE-ALL.

Ensure the foam is flat and sound prior to installation of 825 PARGE-ALL.

Due to normal variation in Portland cement colour, batch-to-batch colour variation will occur.

#### **HEALTH AND SAFETY**

Contains Portland cement. Avoid eye contact or prolonged contact with skin. In case of eye contact, flush eyes with copious amounts of water for at least 15 minutes and get prompt medical attention.

#### **MASTERFORMAT NUMBER AND TITLE**

03 01 30.61 – Resurfacing of Cast-in-Place Concrete

#### **LEED INFORMATION**

May help contribute to LEED credits:

- MRc9: Construction and Demolition Waste Management

**For most current data sheet, LEED information and SDS, visit [www.wrmeadows.com](http://www.wrmeadows.com)**

2018-05-16



© SEALTIGHT is a registered trade mark of W. R. Meadows

**WARRANTY:** W.R. MEADOWS of Western Canada warrants that, at the time and place we make shipment, our materials will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTY, EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM OF TRADE OR OTHERWISE. As the exclusive remedy for breach of this Warranty, we will replace defective materials, provided, however, that the buyer examine the materials when received and promptly notify us in writing of any defect before the materials are used or incorporated into a structure. Three (3) months after W.R. MEADOWS of Western Canada has shipped the materials, all our Warranty and other duties with respect to the quality of the materials delivered shall conclusively be presumed to have been satisfied, all liability therefore terminates and no action for breach of any such duties may thereafter be commenced. W.R. MEADOWS of Western Canada shall in no event be liable for consequential damages. Unless otherwise agreed to in writing, no warranty is made with respect to materials not manufactured by W.R. MEADOWS of Western Canada. We cannot warrant or in any way guarantee any particular method of use or application or the performance of materials under any particular condition. Neither this Warranty nor our liability may be extended or amended by our salesmen, distributors or representatives, or by our distributor's representatives, or by any sales information or drawings.