



MasterFormat: 03 01 00



GEM-PLAST TC

Leveling and Finishing Waterproof Mortar

DESCRIPTION

GEM-PLAST TC is a one-component, polymer-modified, high performance, Portland-based mortar used for leveling of surfaces before application of waterproofing coatings.

USES

GEM-PLAST TC is used for interior and exterior applications over concrete and masonry. It is suitable for cisterns, reservoirs, wastewater containment facilities, swimming pools, and above- and below-grade walls and floors, including cold storage rooms and food processing plants.

FEATURES/BENEFITS

- Self-curing
- Highly crack resistant
- Tough and durable
- Excellent bond
- Can be featheredged
- Easy to clean
- Superior freeze/thaw resistance
- Non-flammable
- Non-toxic
- Breathable
- Excellent workability/Easy application

PACKAGING

22.7 kg (50 Lb.) Bags

COVERAGE/YIELD

12.5 L (0.44 ft.³)

Covers approximately 4.2 m² @ 3 mm (42.4 ft.² @ 1/8") thickness per bag.

SHELF LIFE

When stored on pallets in a dry, cool area, shelf life is 12 months.

TECHNICAL DATA

Modulus of Rupture (ASTM C438)	5.5 - 6.9 MPa (800 - 100 psi)
Compressive Strength (ASTM C109 Modified)	34.5 - 37.9 MPa (5000 - 5500 psi)
Freeze-Thaw Resistance (ASTM C666, Procedure A)	Weight Loss <1%
Available Colours	Industrial Grey, White

APPLICATION

Surface Preparation ... Remove all loose particles, dirt, oil, grease, form release agents, laitance, efflorescence, and any other bond inhibiting materials by wet or dry sand blasting or high pressure water blast [min. 35 MPa (5000 psi)]. The substrate must be saturated surface damp and free of any standing water prior to application.

Crack Treatment ... Any existing cracks must be treated separately.

Mixing ... Mix GEM-PLAST TC with 5.0 L (1.3 gal.) of water, using paddle or helix mortar mixer, or heavy duty (400 - 600 rpm) drill with a suitable mixing paddle. Gradually add dry powder into water, while mixing, and mix until the mix is smooth and lump-free.

Adjust the water for the desirable consistency for brush application, or a little stiffer consistency for trowel application. Do not exceed 5.2 L (1.4 gal.) per bag. Do not overmix.

Application Method ... Apply GEM-PLAST TC by trowel to a uniform specified 3 - 6.35 mm (1/8" - 1/4") thickness. If spraying, use a trowel to remove any air and obtain full contact throughout.

Curing ... Protect against rapid drying by water misting, wet burlap, or non-solvent surface evaporation retardant for 24 hours.

Cleanup ... All tools must be cleaned with water immediately after use. Cured material can only be removed mechanically.

LIMITATIONS/PRECAUTIONS

Do not apply GEM-PLAST TC when the temperature is expected to be below 4° C within 48 hours, or when rain is imminent. Follow Hot Weather concreting precautions when applying at temperatures above 25° C, or under sunny and windy conditions. Maximum applied thickness must not exceed 6.35 mm (1/4").

HEALTH AND SAFETY

Avoid direct contact with this product, as it may cause skin and eye irritation. Utilize gloves and safety glasses to minimize direct contact. Avoid inhalation of dust. Inhalation may cause respiratory irritation and/or lung disease (silicosis). This product contains silicon dioxide, which is classified by the IARC and NTP as probably carcinogenic to humans (IARC Group 2A). The use of NIOSH-approved respiratory protection is recommended in dusty environments. Refer to Safety Data Sheet for complete health and safety information.

Keep product out of reach of children. Not for consumption.

For most recent data sheet, sustainability information, and SDS, visit www.gemite.com.



LIMITED WARRANTY

W. R. MEADOWS, INC. warrants at the time and place we make shipment, our material will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. Read complete warranty. Copy furnished upon request.

Disclaimer

The information contained herein is included for illustrative purposes only, and to the best of our knowledge, is accurate and reliable. W. R. MEADOWS, INC. cannot however under any circumstances make any guarantee of results or assume any obligation or liability in connection with the use of this information. As W. R. MEADOWS, INC. has no control over the use to which others may put its product, it is recommended that the products be tested to determine if suitable for specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect or engineer, contractor and owner for the design, application and proper installation of each product. Specifier and user shall determine the suitability of products for specific application and assume all responsibilities in connection therewith.