



DATA SHEET NO. 3473-000

PENTREAT™ 244-20 W/B

Water-Based, Penetrating, Water Repellent, Silane Sealing Compound

DESCRIPTION

PENTREAT 244-20 W/B is a water-based, 20% active content silane penetrating sealer. PENTREAT 244-20 W/B is a hydrophobic, impregnating sealer that helps prevent chloride-induced corrosion of rebar, scaling, spalling, freeze-thaw damage, and other causes of debilitating concrete.

USES

PENTREAT 244-20 W/B is designed for use on horizontal, vertical, new, and existing concrete and masonry above-grade surfaces. Suitable applications include residential, commercial, industrial, and municipal projects. PENTREAT 244-20 W/B can be used on all types of concrete, including parking structures, stadiums, driveways, plazas, patios, walkways, median barriers, ramps, traffic-barring concrete, and loading docks.

FEATURES/BENEFITS

- High-performance, breathable, penetrating, superior water repellent sealer.
- Minimizes penetration of water and water-soluble salts that may damage concrete/masonry surface.
- Reduces spalling of new concrete surfaces.
- Will extend the life of concrete and masonry structures.
- Penetrates deeply for maximum protection.
- Chemically bonds to the substrate, preventing liquid absorption while allowing excellent vapour transmission.
- Leaves no residue/Requires no cleaning after application.

PACKAGING

18.9 Litre (5 Gal.) Pails
208.2 Litre (55 Gal.) Drums
1041 Litre (275 Gal.) Totes

COVERAGE

Coverage rate is approximately 3.05 m²/L (125 ft.²/gal.). Coverage is approximate and may vary depending on surface finish/texture, concrete porosity and condition, climatic conditions, etc. Always apply to a test area first to determine actual coverage rate before full-scale application.

SHELF LIFE

When stored indoors in original, unopened containers at temperatures between 4° - 32° C, optimum performance and best use is obtained within one year of date of manufacture.

SPECIFICATIONS/STANDARDS

- Complies with Canada VOC Concentration Limits for Architectural Coatings Regulations.

APPLICATION

Surface Preparation ... Surfaces must be structurally sound, clean, and dry with all stains, oil, grease, dust, dirt, efflorescence, and curing compounds removed prior to application. For optimum results, wait 28 days before applying PENTREAT 244-20 W/B to new concrete. PENTREAT 244-20 W/B can be applied earlier than 28 days; however, lower penetration can be expected.

Application Method ... Apply with a low-pressure airless sprayer, such as a Chapin 1949 with a 0.379 LPM (0.1 GPM) spray rate.

Horizontal Application ... Apply in a single pass. Completely saturate the surface and leave wet for 3 - 5 minutes. Then brush out or broom all pools and puddles of material from surface.

Vertical Application ... Apply two coats wet on wet. Do not allow the first coat to fully dry before applying the second.

Continued over ...

W. R. MEADOWS® OF CANADA

70 Hannant Court, Milton, ON L9T 5C1
21 Streambank Ave., Sherwood Park, AB T8H 1N1
(800) 342-5976
Montreal Sales: (514) 865-2406

Hampshire, IL / Cartersville, GA / York, PA / Fort Worth, TX
Benicia, CA / Pomona, CA / Goodyear, AZ / Milton, ON
Sherwood Park, AB
www.wrmeadows.com
info@wrmeadows.com

Test Application ... Always perform a small test application on each type of surface prior to full-scale application to determine exact coverage rate, suitability, and final appearance. Test using the recommended application instructions. Prior to inspection, allow three days minimum for PENTREAT 244-20 W/B to fully react after application.

Drying Time ... Product dries quickly. Drying times will vary depending on application rate, temperature, humidity, and project conditions. Restrict foot traffic for at least four hours at 20° C. Twelve hours is preferable. Drying time will be extended at lower temperatures and higher RH.

Cleanup ... Immediately clean tools, equipment, and overspray with soap and warm water.

PRECAUTIONS

Not recommended for below-grade applications or for use under hydrostatic pressure. Do not use as a waterproofing or vapour barrier. PENTREAT 244-20 W/B will not block vapour transmission through defective substrates, such as cracked or improperly repaired surfaces. PENTREAT 244-20 W/B should never be in contact with bituminous products. On vertical applications, protect window panes and window frames that will be painted from contact with PENTREAT 244-20 W/B.

Treated surface must be protected from rain for six hours minimum, but 12 hours is preferable. Do not over-apply. For optimum performance, the moisture content of the concrete must not exceed 4%. The application temperature should be between 4.4° - 32.2° C. The surface temperature should be 3° F above the dew point.

Should it suddenly start to rain, stop treatment and cover impregnated areas. Do not over apply. Do not allow puddling or running to occur.

For most current data sheet, further LEED information, and SDS, visit www.wrmeadows.com.



2022-03-09

© SEALTIGHT is a registered trade mark of W. R. Meadows

WARRANTY: W. R. Meadows of Canada warrants that, at the time and place we make shipment, our materials will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTY, EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM OF TRADE OR OTHERWISE. As the exclusive remedy for breach of this Warranty, we will replace defective materials, provided, however, that the buyer examine the materials when received and promptly notify us in writing of any defect before the materials are used or incorporated into a structure. Three (3) months after W. R. Meadows of Canada has shipped the materials, all our Warranty and other duties with respect to the quality of the materials delivered shall conclusively be presumed to have been satisfied, all liability therefore terminates and no action for breach of any such duties may thereafter be commenced. W. R. Meadows of Canada shall in no event be liable for consequential damages. Unless otherwise agreed to in writing, no warranty is made with respect to materials not manufactured by W. R. Meadows of Canada. We cannot warrant or in any way guarantee any particular method of use or application or the performance of materials under any particular condition. Neither this Warranty nor our liability may be extended or amended by our salesmen, distributors or representatives, or by our distributor's representatives, or by any sales information or drawings.