



W. R. MEADOWS.

SEALTIGHT®

DATA SHEET NO. 3300-135

1215-WHITE Pigmented Curing Compound

DESCRIPTION

1215-WHITE pigmented curing compound is a waterborne, resin-based curing compound containing suspended white pigment. It permits complete hydration of the cement by retaining at least 95% of the water present in the concrete at the time of application for at least seven days. The white pigment reflects the heat-producing rays of the sun, keeping concrete surfaces cooler and preventing excessive heat build-up and resultant thermal cracking during the curing period.

USES

1215-WHITE is a reflective curing compound designed for exterior use on freshly placed concrete surfaces, both horizontal and vertical, particularly where protection from the sun's heat is required. It is recommended for use on driveways, walls, sidewalks, concrete highways, runways, overpasses, bridges, tunnels, etc.

FEATURES/BENEFITS

- Contains SUSPENSOID, a unique additive which assists pigment dispersion and prevents excessive pigment settlement.
- Excellent moisture retention properties.
- Excellent heat reflective properties.
- Excellent sprayability.
- Easy clean up.

PACKAGING

18.9 Litre Pail
205 Litre Drum

COVERAGE

4.9 m²/litre

SHELF LIFE

When stored indoors in original, unopened containers at temperatures between 4° - 32° C, optimum performance and best use is obtained within one year of date of manufacture.

SPECIFICATIONS

- ASTM C 309, Type 2, Class A and B
- Complies with Canada VOC Concentration Limits for Architectural Coatings Regulations.
- Approved by the Ministry of Transportation, Quebec.

APPLICATION

Mixing ... Only nominal agitation of 1215-WHITE is required prior to each use. Do not employ constant recirculating pumps or high-speed mixers.

Application Method ... Apply by low-pressure (30 psi) hand or power sprayer, such as a Chapin 1949, as soon as the surface water disappears from horizontal surfaces, or immediately after forms are removed from vertical surfaces. An 80° fan pattern spray nozzle rated at 1.9 LPM provides an excellent, even coating. Apply evenly over the entire surface; avoiding puddling in low areas.

Drying Time ... Restrict foot traffic for at least four hours. Drying times may be extended depending on application rate, temperature, humidity, and project conditions.

Cleanup ... Clean tools and equipment immediately after use with water. Once dried, material would need to be cleaned with xylene, toluol, or SEALTIGHT® SOLVENT from W. R. MEADOWS.

PRECAUTIONS

Do not apply when air, material and/or surface temperatures are expected to fall below 4° C within four hours of completed application. 1215-WHITE is not recommended for use on concrete surfaces that are later to be painted, tiled, hardened, sealed, or treated in any manner. Avoid breathing vapours. Avoid prolonged contact with skin. **FOR INDUSTRIAL USE ONLY.**

Continued over ...

W. R. MEADOWS® OF CANADA
70 Hannant Court, Milton, ON L9T 5C1
Phone: (905) 878-4122 • Fax: (905) 878-4125
Montreal Sales: (877) 405-5186

Hampshire, IL / Cartersville, GA / York, PA / Fort Worth, TX
Benicia, CA / Pomona, CA / Goodyear, AZ / Milton, ON
St. Albert, AB
www.wrmeadows.com

MASTERFORMAT NUMBER AND TITLE

03 39 23 – Membrane Concrete Curing

LEED INFORMATION

May help contribute to LEED credits:

- IEQ Credit 4.2: Low-Emitting Materials: Paints and Coatings
- MR Credit 2: Construction Waste Management
- MR Credit 5: Regional Materials

For most recent data sheet, further LEED information, and MSDS, visit www.wrmeadows.com

2014-10-14



© SEALTIGHT is a registered trade mark of W. R. Meadows

WARRANTY: W. R. Meadows of Canada warrants that, at the time and place we make shipment, our materials will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTY, EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM OF TRADE OR OTHERWISE. As the exclusive remedy for breach of this Warranty, we will replace defective materials, provided, however, that the buyer examine the materials when received and promptly notify us in writing of any defect before the materials are used or incorporated into a structure. Three (3) months after W. R. Meadows of Canada has shipped the materials, all our Warranty and other duties with respect to the quality of the materials delivered shall conclusively be presumed to have been satisfied, all liability therefore terminates and no action for breach of any such duties may thereafter be commenced. W. R. Meadows of Canada shall in no event be liable for consequential damages. Unless otherwise agreed to in writing, no warranty is made with respect to materials not manufactured by W. R. Meadows of Canada. We cannot warrant or in any way guarantee any particular method of use or application or the performance of materials under any particular condition. Neither this Warranty nor our liability may be extended or amended by our salesmen, distributors or representatives, or by our distributor's representatives, or by any sales information or drawings.