



INTRALOK® Bonding Agent

DESCRIPTION

INTRALOK Bonding Agent is a high-solids content, water dispersion of acrylic bonding polymers compounded specifically for modifying Portland Cement compositions. It is a milky-white, non-yellowing liquid ready to use as an interface or intramix bonding agent. When properly mixed and applied, INTRALOK forms a bond between new-to-old concrete that is typically stronger than the concrete.

Cement mortars modified with INTRALOK are hard, tough and durable. It offers superior tensile, flexural, and impact strengths. INTRALOK also improves adhesion resistance of the modified mortar. INTRALOK reduces permeability and chloride intrusion, improving freeze/thaw resistance and reducing rebar corrosion.

INTRALOK-modified concrete is unaffected by ultraviolet light and will not yellow.

USES

INTRALOK's most common uses are for patching and resurfacing, spray and fill coats, repairing pre-cast building panels and beams, industrial flooring, highway and bridge deck repairs.

INTRALOK is ideal for interior or exterior bonding, topping, levelling, patching and dressing of concrete and masonry. As a bonding grout, it improves the adhesion of pneumatically applied concrete or mortar. INTRALOK-modified mortars provide excellent adhesion to a variety of surfaces, including concrete and masonry. The result is a more attractive, durable, uniform and weatherproof concrete finish which costs far less than polishing or rubbing.

INTRALOK is also ideal for use as an interface or intramix bonding agent in bonding grouts, topping mixtures, finishing and mortar mixes. INTRALOK will not re-emulsify.

FEATURES AND BENEFITS

- Forms an excellent bond to concrete
- Functions equally effectively for interior or exterior repairs between new-to-old concrete
- Offers superior flexural, adhesive and impact strengths plus excellent abrasion resistance
- Provides a hard, durable, weather-resistant finish at far less cost than polishing or rubbing
- Will not after-yellow
- Will not stain or discolour concrete

DATA SHEET NO. 3300-501

- Ready-to-use ... requires no additional mixing
- Reduces permeability
- Reduces chloride intrusion

SPECIFICATIONS

- ASTM C 1059, Type II.
- Approved by the Ministry of Transportation, Quebec.

PACKAGING

3.78 litre jugs
18.9 litre pails
205 litre drums

COVERAGE

Approximately 7.36 m²/L (300 ft.²/U.S. gal.) straight; diluted with equal parts of water, approximately 14.73 m²/L (600 ft.²/U.S. gal.)

APPLICATION

Surface Preparation

All surfaces must be structurally sound, clean and free of grease, oil, dust, dirt, curing and release compounds and other foreign contaminants. All loose, unsound concrete must be removed.

Pre-soak all surfaces with water prior to applying the bonding grout. Remove all puddles and free water. The cementitious mix must be applied while the INTRALOK is still tacky.

Mixing

Specific mixing proportions for these various INTRALOK mixes are listed on the container. All cautions, mixing and application information and directions furnished on container labels should be read and followed. For normal mixing, dry blend the Portland Cement and sand. Mix the INTRALOK and water together, add to the cement-sand mix, and then mechanically blend the complete mix thoroughly. The quantity of water should be determined by a trial mix ... where only 50% of the water is first added to the INTRALOK, before adding to the sand-cement mix. After thorough preliminary mixing, add increments of additional water until the desired consistency is obtained.

Continued over .

W. R. MEADOWS OF CANADA

70 Hannant Court, Milton, ON L9T 5C1
Phone: (905) 878-4122 • Fax: (905) 878-4125

Montreal Sales: (877) 405-5186

Hampshire, IL / Cartersville, GA / York, PA / Fort Worth, TX
Benicia, CA / Pomona, CA / Goodyear, AZ / Milton, ON /
St. Albert, AB

www.wrmeadows.com

Application Mixes by volume

1. Bonding Slurry:

1 part INTRALOK
2-1/2 parts Portland cement
2-1/2 parts fine sand (ASTM C144)
Water: Enough for a for a thick creamy consistency (Approximately 1 part)

4 litre unit of INTRALOK used to mix a bonding slurry will yield approximately 0.014 m³ (0.49 ft.³), enough to cover an area of 8.45 m² (90.24 ft.²) at 1.59 mm (1/16") thickness or 4.18 m² (45 ft.²) at 3.18 mm (1/8") thickness. Apply with a stiff bristle brush; be sure to work bonding slurry into existing concrete pores.

2. Topping and Shallow Patching Mix:

1 part INTRALOK
5 parts Portland cement.
15 parts fine sand (ASTM C404, Size #2)
Water: - Enough for trowelable consistency (Approximately 2 parts).

3. Mortar Mix:

1 part INTRALOK
5 parts Portland cement
15 parts sand (ASTM C404, Size #2)
Water: Enough for desired consistency (Approximately 1-1/2 to 2 parts).

4 litres of INTRALOK used in a topping or mortar mix will yield approximately 0.05 m³ (1.8 ft.³) to cover an area of 7.99 m² (86 ft.²) at 6.35 mm (1/4") thickness. Topping or mortar mix should be applied while the INTRALOK Bonding Grout is still soft and plastic.

4. Finish Mix:

1 part INTRALOK
10 parts Portland cement
10 parts fine sand (ASTM C404 Size #2)
Water: Enough for stiff, brushable consistency. (Approximately 4 parts).

INTRALOK Bonding Grout must be thoroughly worked and scrubbed onto the prepared concrete surface in order to realize maximum bonding efficiency.

PRECAUTIONS

Keep from freezing. Approximate work life is 30-40 minutes at 21°C (70°F). Do not apply at surface temperatures below 4°C (40°F). Use care in finishing thin overlays. Wood float when possible. Steel trowelling should be limited to a minimum number of passes 10-15 minutes after placement. When INTRALOK is used in a bonding grout and the patch topping is plain concrete, use a membrane curing compound. If the patch or topping contains INTRALOK as an admixture, wet curing is NOT recommended.

INTRALOK Bonding Grout or Topping Mix should be mixed thoroughly to remove lumps. Avoid air entrapment. Clean tools with water immediately. Follow all cautions on container labels. Do not add to premixed grouts. Specifier and user shall determine suitability of product for specific applications and assume all responsibilities in connection therewith. INTRALOK has an effective shelf life of 6 months from the date of manufacture.

Note: Increased amounts of various fillers, extenders or additives in the concrete mix can result in the concrete having a higher than normal porosity and some very porous hot spots.

Coverage ratios must be adjusted to compensate for resulting penetration and additional coverage coats required to provide proper surface treatment. Read and follow application information and precautions. Refer to Material Safety Data Sheet for complete health and safety information.

Proper application is the responsibility of the user. Field visits by W. R. MEADOWS' personnel are for the purpose of making technical recommendations only, and are not to supervise or provide quality control on the job-site.

SPECIFICATION CLAUSE

Section 03 05 00.

Bonding Agent INTRALOK Bonding Agent; (for mix data see "Application Instructions").

FOR BEST PERFORMANCE, ENSURE MOST RECENT TECHNICAL DATA SHEET IS BEING USED ... VISIT OUR WEBSITE AT:

www.wrmeadows.com

2009-09-29



© SEALTIGHT is a registered trade mark of W. R. Meadows

WARRANTY: W. R. Meadows of Canada warrants that, at the time and place we make shipment, our materials will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTY, EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM OF TRADE OR OTHERWISE. As the exclusive remedy for breach of this Warranty, we will replace defective materials, provided, however, that the buyer examine the materials when received and promptly notify us in writing of any defect before the materials are used or incorporated into a structure. Three (3) months after W. R. Meadows of Canada has shipped the materials, all our Warranty and other duties with respect to the quality of the materials delivered shall conclusively be presumed to have been satisfied, all liability therefore terminates and no action for breach of any such duties may thereafter be commenced. W. R. Meadows of Canada shall in no event be liable for consequential damages. Unless otherwise agreed to in writing, no warranty is made with respect to materials not manufactured by W. R. Meadows of Canada. We cannot warrant or in any way guarantee any particular method of use or application or the performance of materials under any particular condition. Neither this Warranty nor our liability may be extended or amended by our salesmen, distributors or representatives, or by our distributor's representatives, or by any sales information or drawings.