



DATA SHEET NO. 3600-201

CG-86™ Construction-Grade Grout (Canada)

DESCRIPTION

CG-86 construction-grade grout is a non-ferrous, non-gaseous, non-shrink economical grout. It was specifically developed as a high-strength, cost-effective, general-purpose grout for use across a broad range of large and small construction projects. CG-86 is non-gaseous, will not rust, and contains no added chlorides or gypsum. It is furnished premixed and ready to use. CG-86 may be extended for deep grouting with pea gravel for greater yield and increased economy.

USES

CG-86 is very versatile and may be used for either interior or exterior applications. CG-86 is designed for base plate grouting, anchoring, precast wall panels, and bridge seats.

FEATURES/BENEFITS

- Furnished premixed and ready-to-use ... just add water.
- Provides a high-strength, non-ferrous, non-shrink grout for a broad range of general construction projects.
- Offers the strength and characteristics required for cost-effective, general-purpose grouting.
- Cost reductions are realized when extended with pea gravel for deep grouting.
- Requires no separate bonding agent.
- No site batching required for consistent results.
- Chloride-free.

PACKAGING

22.7 Kg Poly-Lined Bags

YIELD

0.012 m³ per 22.7 kg bag.

SHELF LIFE

One year from date of manufacture when stored indoors on pallets in a dry, cool area. Do not store product outside.

SPECIFICATIONS

- Agriculture and Agri-Food Canada accepted.
- Approved by the Ministry of Transportation, Quebec

TECHNICAL DATA

Consistency (Per ASTM C 827-95A)	Plastic	Flowable
Mix Ratio per 22.7 kg (50 lb.)	3.0 litres (6.34 U.S. pints)	3.5 litres (7.40 U.S. pints)
Flow (per ASTM C 230-90)	110%	130%
Set Time (per C 191-92, Initial)	4 - 6 hours	5 - 7 hours
Compressive Strength (per ASTM C 109-93)		
@ 1 day	38.9 MPa (5,200 psi)	26.9 MPa (3,900 psi)
@ 3 days	49.6 MPa (7,200 psi)	40.0 MPa (5,800 psi)
@ 7 days	60.7 MPa (8,800 psi)	49.0 MPa (7,100 psi)
@ 28 days	66.2 MPa (9,600 psi)	61.4 MPa (8,900 psi)

All technical data is typical information, but may vary due to testing methods, conditions, and procedures.

APPLICATION

All grouting should be done using established procedures according to American Concrete Institute (ACI) recommendations.

Surface Preparation ... All grout contact surfaces must be clean and free of oil, grease, scale, etc. Unsound concrete must be chipped out. Leave surface rough but level. Grouting area must be saturated with water 12 – 24 hours prior to grouting. Remove all excess water before placing grout.

Pouring ... Method of forming must provide for rapid, continuous grout placement. Ensure form is well sealed.

Continued over ...

W. R. MEADOWS OF CANADA
 70 Hannant Court, Milton, ON L9T 5C1
 Phone: (905) 878-4122 • Fax: (905) 878-4125
 Montreal Sales: (877) 405-5186

Hampshire, IL / Cartersville, GA / York, PA / Fort Worth, TX
 Benicia, CA / Pomona, CA / Goodyear, AZ / Milton, ON/
 St. Albert, AB
www.wrmeadows.com

Placement ... CG-86 is easily placed by pouring or pumping and compaction can be accomplished by rodding or light vibrating. Place grout on one side, flowing to opposite and adjacent sides, to avoid entrapment of air. When necessary, provide vent holes. Grout "head" and excess grout may be removed after initial set.

Curing ... Cure CG-86 immediately following application using a suitable curing compound from W. R. MEADOWS, or in accordance with ACI 308. 1100-CLEAR, 1220-WHITE, CS-309™ series, or VOCOMP®-25 from W. R. MEADOWS are recommended. When conditions exist for rapid early water loss, the use of EVAPRE™, an evaporation retarder from W. R. MEADOWS, is also recommended.

Venting ... Forming also must ensure adequate venting to avoid air entrapment. Do not make close fitting forms; allow 12.7 mm clearance and 25.4 mm for "head."

Mixing ... Small quantities of CG-86 may be hand-mixed in a concrete mixing pan until lump-free. For large quantities and continuous pours, use a mortar mixer with rubber-tipped blades. Mix for a minimum of three minutes or until uniform and lump-free. Use minimum water required to produce desired placement consistency. Do not mix more than can be placed in 30 minutes. Do not re-temper. Use only clean, potable water.

Set time and strength development is dependent on temperature; therefore, follow ACI methods during hot or cold weather grouting.

ACI 305 – "Standard on hot weather concreting"
ACI 306 – "Standard on cold weather concreting"

Cost reductions are realized when grouting large areas by adding washed, dried, and graded pea gravel. For thicknesses 50.8 – 101.6 mm, add up to 25% 9.5 mm pea gravel. For thicknesses 101.6 mm and over, add up to 50% 9.5 mm pea gravel. Always follow standard ACI concreting practices. Addition of gravel will reduce the flow of the neat mix. Addition of pea gravel is based on percentage of the weight of the dry grout.

PRECAUTIONS

Do not use as a repair mortar. (Please contact W. R. MEADOWS for specific repair mortar recommendations.) Normal cement storage handling practices should be observed. Grouting should be done using established concreting procedures, according to ACI recommendations. Read and follow application information, precautions and Material Safety Data Sheet information.

MASTERFORMAT NUMBER AND TITLE

03 62 13 - Non-Metallic Non-Shrink Grouting

LEED INFORMATION

May help contribute to LEED credits:

- MR Credit 2: Construction Waste Management
- MR Credit 5: Regional Materials

For most current data sheet, further LEED information, and MSDS, visit www.wrmeadows.com.

2014-06-25



© SEALTIGHT is a registered trade mark of W. R. Meadows

WARRANTY: W. R. Meadows of Canada warrants that, at the time and place we make shipment, our materials will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTY, EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM OF TRADE OR OTHERWISE. As the exclusive remedy for breach of this Warranty, we will replace defective materials, provided, however, that the buyer examine the materials when received and promptly notify us in writing of any defect before the materials are used or incorporated into a structure. Three (3) months after W. R. Meadows of Canada has shipped the materials, all our Warranty and other duties with respect to the quality of the materials delivered shall conclusively be presumed to have been satisfied, all liability therefore terminates and no action for breach of any such duties may thereafter be commenced. W. R. Meadows of Canada shall in no event be liable for consequential damages. Unless otherwise agreed to in writing, no warranty is made with respect to materials not manufactured by W. R. Meadows of Canada. We cannot warrant or in any way guarantee any particular method of use or application or the performance of materials under any particular condition. Neither this Warranty nor our liability may be extended or amended by our salesmen, distributors or representatives, or by our distributor's representatives, or by any sales information or drawings.