



W. R. MEADOWS.



DATA SHEET NO. 3600-800

800 CONSTRUCTION GROUT

DESCRIPTION

800 CONSTRUCTION GROUT is a pre-blended Portland cement grout containing non-ferrous admixtures to counteract plastic and drying shrinkage. The product complies fully with ASTM C827 test specifications for non-shrink grout. 800 CONSTRUCTION GROUT is formulated using admixtures recommended for non-shrink grout by the U.S. Corps of Engineers and American Concrete Institute (ACI) publications. There are no corrosive or unstable ingredients in 800 CONSTRUCTION GROUT.

USES

800 Construction Grout is ideal for every phase of structural grouting which includes structural members, bridge seats, machinery bases, crane rails, anchorage systems, underpinning and concrete repairs. Two mixes are available, depending on water addition.

The dry pack grout mix is suitable for grouting column bases, small machine bases, underpinning, patching cracks in concrete or masonry walls, abutments, tanks, etc., and as a surface seal preliminary to penetration grouting of deep interior void by pressure grouting.

The flowable concrete mix involves the addition of gravel aggregate and may be used wherever the grout thickness or individual volumes are larger than usual. Typical applications include filling of pipe boxes where the space between the pipe and wall section is over 150 mm (6") The mix can be also used for machine or structural column base plates where the space between foundation concrete and bedplate exceeds 150 mm (6").

FEATURES/BENEFITS

- Versatile in use; may be pumped, packed, or poured.
- Allows ample time for mixing, transporting, and placing.
- No special measures are necessary to preserve stability.

PACKAGING

25 Kg Multi-All Paper Bags

COVERAGE/YIELD

One bag (25 kg) will yield approximately 14,200 cm³ (1/2 ft.³)

SHELF LIFE

One year from date of manufacture when stored indoors on pallets in a dry, cool area. Do not store product outside.

SPECIFICATIONS

- ASTM C827
- CRD-C 619
- CRD-C 621

TECHNICAL DATA

Colour	Slightly darker than normal concrete
Pot Life	1 hour at 15° - 21°C
Compressive Strength	52 MPa (7500 psi) in 28 days

Strength and Flow Charts

Flowable Grout

30 - 45 seconds through flow cone

Approximately 4.5 L (1.2 gal.) of water per 25 kg bag

Days	1	7	28	90
MPa	14	31	45	52
PSI	2000	4500	6500	7500

Dry-Pack Grout

Zero slump consistency

Approximately 3.5 L (.9 gal.) of water per 25 kg bag

Days	1	7	28	90
MPa	45	55	62	76
PSI	6500	8000	9000	11000

APPLICATION

Surface Preparation ... Foundation concrete to receive grout must be roughened, cleaned of all foreign matter and laitance, and thoroughly water saturated. All freestanding water should be blown clear just prior to placing grout.

Continued ...

W. R. MEADOWS® OF CANADA

70 Hannant Court, Milton, ON L9T 5C1

21 Streambank Ave., Sherwood Park, AB T8H 1N1

(800) 342-5976

Montreal Sales: (877) 405-5186

Hampshire, IL / Cartersville, GA / York, PA / Fort Worth, TX
 Benicia, CA / Pomona, CA / Goodyear, AZ / Milton, ON
 Sherwood Park, AB
www.wrmeadows.com

Application Method ... The mix should contain only enough water to form a cohesive ball when squeezed tightly in the hand. Mixing should be done by hand using a shovel and wheelbarrow or mortar box. Water should be sprinkled over the dry material and turned into the mix thoroughly using a shovel. See water mix ratios above. The mixed grout must be rammed in place with a metal or hardwood tool. Discard mixed grout not rammed in place within one hour of initial preparation.

Extending ... For exceptionally thick sections [4" (101.6 mm) and over], 800 CONSTRUCTION GROUT should be cut 50% with pea gravel or 9.5 mm (3/8") crushed stone.

Curing ... Cure 800 CONSTRUCTION GROUT immediately following application using a suitable curing compound from W. R. MEADOWS, or in accordance with ACI 308. 1100-CLEAR, 1220-WHITE, CS-309™ series, or VOCOMP®-25 from W. R. MEADOWS are recommended. When conditions exist for rapid early water loss, the use of EVAPRE™, an evaporation retarder from W. R. MEADOWS, is also recommended.

PRECAUTIONS

Compressive strength will vary with the amount of mixing water used and with ambient temperatures during curing. Specimens for compressive strength should be taken in 50.8 mm (2") brass cube molds under total confinement and according to CRD-C 621 procedures. Less flowable consistencies will exhibit high strengths. Ambient temperatures during placing may vary from 4° C to over 30° C. At normal temperatures the working time or pot life is one full hour. Slightly accelerated or retarded working time will apply when working in hot or cool conditions respectively. Moderate vibration and agitation of the fresh grout is permitted.

MASTERFORMAT NUMBER AND TITLE

03 62 13 - Non-Metallic Non-Shrink Grouting

LEED INFORMATION

May help contribute to LEED credits:

- MRc9: Construction and Demolition Waste Management

For most current data sheet, further LEED information and SDS, visit www.wrmeadows.com.

2018-04-17



© SEALTIGHT is a registered trade mark of W. R. Meadows

WARRANTY: W.R. MEADOWS of Western Canada warrants that, at the time and place we make shipment, our materials will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTY, EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM OF TRADE OR OTHERWISE. As the exclusive remedy for breach of this Warranty, we will replace defective materials, provided, however, that the buyer examine the materials when received and promptly notify us in writing of any defect before the materials are used or incorporated into a structure. Three (3) months after W.R. MEADOWS of Western Canada has shipped the materials, all our Warranty and other duties with respect to the quality of the materials delivered shall conclusively be presumed to have been satisfied, all liability therefore terminates and no action for breach of any such duties may thereafter be commenced. W.R. MEADOWS of Western Canada shall in no event be liable for consequential damages. Unless otherwise agreed to in writing, no warranty is made with respect to materials not manufactured by W.R. MEADOWS of Western Canada. We cannot warrant or in any way guarantee any particular method of use or application or the performance of materials under any particular condition. Neither this Warranty nor our liability may be extended or amended by our salesmen, distributors or representatives, or by our distributor's representatives, or by any sales information or drawings.