



"SPEED®CRETE" Fast-Setting High Strength Concrete

DESCRIPTION

"SPEED CRETE" is a complete, ready-to-use concrete patching compound for fast, permanent repairs. Requires only the addition of water. Available in two types: Red Line for general purpose patching and Blue Line for underwater applications.

Product No. 3900-122 (Red Line)
 3900-132 (Blue Line)

USE

"SPEED CRETE" **Red Line** is used for general purpose patching and restoring of Portland cement concrete in highways, streets, bridges, floors, precast panels and pipes.

"SPEED CRETE" **Blue Line** is a special formula for use underwater in the restoration of pilings, seawalls, sewers, water mains, dams, etc.

FEATURES

- Rapid set.
- High compressive strength.
- High bond strength.
- Thermal coefficient of expansion equal to Portland cement concrete.
- High resistance to freeze-thaw and to salt.
- Red Line contains an air-entraining agent.
- Protects steel. Contains no calcium chloride.
- May be used on vertical or overhead surfaces - no forms required.
- Will support vehicular traffic in less than one hour.
- No noticeable heat of hydration.
- Up to 80% by weight of aggregate may be added.

CAUTION

Do not re-temper. Mix no more than 45.4 kg (100 lbs.) at a time.
Do not mix for more than 60 seconds.
Do not add sand - destroys bond and workability.
Do not feather edge.
Do not apply as a thin skin topping.

DATA SHEET NO. 3900-122/132

CAUTION

Prolonged contact with skin may cause irritation. Use rubber gloves when handling "SPEED CRETE".

PROPERTIES	Red Line	Blue Line
Colour	Light Grey	Light Grey
Initial Set	5 - 10 mins.	3 - 5 mins.
Final Set	15 - 20 mins.	8 - 10 mins.

Volume change

Moist cure (28 days)	+0.01%	+0.01%
Dry air cure (28 days)	-0.04%	-0.04%

ASTM C-157 (modified)

Density per m ³ (per ft. ³)	1600 kg (100 lbs.)	1600 kg (100 lbs.)
---	--------------------	--------------------

Compressive Strength

1 hour	1.0 MPa (150 psi)	-
24 hours	17.2 MPa (2500 psi)	13.8 MPa (2000 psi)
7 days	29.6 MPa (4300 psi)	N.A.
14 days	31.0 MPa (4500 psi)	N.A.
28 days	34.5 MPa (5000 psi)	34.5 MPa (5000 psi)

(ASTM C-109 modified)

Freeze Thaw Durability After 300 cycles	31.7 MPa (4600 psi)	N.A.
---	---------------------	------

(ASTM C-390)

DATA

Packaged Yield In 22.7 kg (50 lb.) multi-wall bags.
 12 742 cm³ (0.45ft.³) per bag.
 21 520 cm³ (0.76 ft.³) per bag with 18.1 kg
 (40 lb.) stone added.

Storage Store in dry, warm 21°C (70°F) area, clear
 of the ground. Storage life 1 year.

Continued over

APPLICATION

Surface Preparation

All loose, scaly, oily material shall be removed prior to placing "SPEED CRETE". In underwater applications, marine growth, deteriorated concrete or wood and rust scale shall be removed. Chip out clean edges at least 12.7 mm (1/2") deep around patch area. When depth of the patch is less than 3/4" (19 mm), or when applying over smooth concrete, a bonding agent is recommended.

Consider W. R. MEADOWS' INTRALOK Bonding Agent (Product No. 3300-501). Alternatively dampen area to be patched with water (except if temperature is below 2°C (35°F), immediately before application of "SPEED CRETE"

Mixing

A typical mixture is in the ratio of about 5.7 litres (5 quarts) of water to 22.7 kg (50 lbs.) "SPEED CRETE" Red Line (per bag), or 5.1 litres (4.5 quarts) of water to 22.7 kg (50 lbs.) "SPEED CRETE" Blue Line (per bag). Water shall be clean and either fresh or sea water. "SPEED CRETE" and water shall be thoroughly mixed for not more than one minute to the consistency of putty with NO SLUMP. There shall be no re-tempering. If mixed by hand, 2.5 to 4.5 kg (5 to 10 lbs.) can be readily mixed in a bucket. For larger quantities, use a wheelbarrow or trough. If mixed in a mortar mixer, use a small mixer with rubber tipped paddles. Mix no more than 45 kg (100 lbs.) at a time. Pour required amount of water into mixer then add (if needed) up to 80% by weight of washed pea gravel up to 9.5 mm (3/8") maximum, then add "SPEED CRETE". Mix just long enough to achieve the consistency of putty with no slump. Do not mix for more than 60 seconds. Do not add sand, anti-freeze, calcium chloride or other chemicals.

Placement

Place no slump mix in a firm manner to ensure complete bond to all areas being covered. "SPEED CRETE" can be applied by trowel or hand methods. DO NOT OVERWORK OR OVERTROWEL IT.

In vertical or overhead placements apply "SPEED CRETE" in layers and allow each layer to reach its initial set before applying a further layer. The layers can be up to 102 mm (4") thick on vertical surfaces and up to 50.8 mm (2") thick on overhead surfaces.

When repairing deep holes place the mix containing aggregate within 25.4 mm (1") of the top, and finish with a layer of "SPEED CRETE" without aggregate. If forms are used, they may be removed 30 minutes after all "SPEED CRETE" is in place.

Finishing

Finish to an even surface by tamping within 3 - 5 minutes after placement. "SPEED CRETE" may be shaved smooth after initial set. Underwater applications are best finished by hand. Cure by application of #3100 (Product No. 3050-101), #1100 (Product No. 3300-341) or #1220 (Product No. 3300-131) concrete curing compounds by W. R. MEADOWS, applied promptly after finishing. Do not use curing compounds when a bonding agent has been used.

Clean Up

Wash all tools and mixing equipment immediately after use with clean water.

Proper application is the responsibility of the user. Field visits by W. R. MEADOWS' personnel are for the purpose of making technical recommendations only, and are not to supervise or provide quality control on the job-site.

SAFETY & TOXICITY

See product label and MSDS information. Read and follow all instructions and precautions.

SPECIFICATION CLAUSE

Section 03 0130.71

Surface Repairs SPEEDCRETE Patching Compound.

FOR BEST PERFORMANCE, ENSURE MOST RECENT TECHNICAL DATA SHEET IS BEING USED ... VISIT OUR WEBSITE AT:

www.wrmeadows.com

2007-01-19

© SEALTIGHT is a registered trade mark of W. R. Meadows

WARRANTY: W. R. Meadows of Canada warrants that, at the time and place we make shipment, our materials will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTY, EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM OF TRADE OR OTHERWISE. As the exclusive remedy for breach of this Warranty, we will replace defective materials, provided, however, that the buyer examine the materials when received and promptly notify us in writing of any defect before the materials are used or incorporated into a structure. Three (3) months after W. R. Meadows of Canada has shipped the materials, all our Warranty and other duties with respect to the quality of the materials delivered shall conclusively be presumed to have been satisfied, all liability therefore terminates and no action for breach of any such duties may thereafter be commenced. W. R. Meadows of Canada shall in no event be liable for consequential damages. Unless otherwise agreed to in writing, no warranty is made with respect to materials not manufactured by W. R. Meadows of Canada. We cannot warrant or in any way guarantee any particular method of use or application or the performance of materials under any particular condition. Neither this Warranty nor our liability may be extended or amended by our salesmen, distributors or representatives, or by our distributor's representatives, or by any sales information or drawings