



DATA SHEET NO. 3900-302

MEADOW-CRETE® H

One Component Glass Fibre Reinforced Horizontal Patching Compound

DESCRIPTION

MEADOW-CRETE H is a glass fibre reinforced cementitious patching compound designed for horizontal applications. The polymer and silica fume enhanced formulation comes ready to use as a single component patching material, simply add the required amount of water and mix in an approved mixing device.

USE

MEADOW-CRETE H is designed for horizontal repairs of concrete, both small and large areas, interior and exterior applications, a minimum of 6 mm (1/4") deep. MEADOW-CRETE H is suitable for industrial and civil engineering applications.

FEATURES

Ready to use; just add water, mix and place.

May be extended with 9 mm (3/8") pea gravel for deep patching, i.e. 25 mm (1") thickness or greater.

Excellent bond to rough and damp surfaces.

Superior resistance to freeze/thaw cycling and de-icing chemicals.

Easily applied by screed or trowel.

CAUTION

Do not apply when the temperature is expected to fall below 5°C (40°F) within 24 hours after placement. Do not apply in unprotected areas when rain is imminent.

Minimum application thickness is 6 mm (1/4").

Not intended for vertical or overhead applications, use MEADOW-CRETE OV

Not intended for use as an underlayment/overlay.

Do not use over moving joints or cracks or over active leaks.

PROPERTIES, typical at 21°C (70°F).

Table with 2 columns: Property and Value. Includes Working Time (40 to 45 minutes) and Compressive Strength (ASTM C 109-90 Modified) at 24, 3, 7, and 28 hours/days.

Compressive strengths may vary due to temperature and weather conditions

Table with 2 columns: Property and Value. Includes Slant Shear Strength (ASTM C 882-87) at 22.9 MPa (3320 psi).

Table with 2 columns: Property and Value. Includes Module of Rupture (ASTM C 27-40) at 8.3 - 10.3 MPa (1200-1500 psi).

Table with 2 columns: Property and Value. Includes Freeze/Thaw Resistance (ASTM C 666-A) at Less than 1% weight loss.

Table with 2 columns: Property and Value. Includes Salt Scale Resistance at Excellent.

Table with 2 columns: Property and Value. Includes Rapid Chloride Penetration (AASHTO T277) at 483 Coulombs.

Table with 2 columns: Property and Value. Includes Water Absorption at 0.048.

STANDARDS

Accepted - Ministry of Transportation, Ontario. Agriculture and Agri-Food Canada accepted. Approved by the Ministry of Transportation, Quebec.

DATA

Packaged 22.7 kg (50 lb.) multi-wall bags. Yield Each bag yields approximately 0.013 m³ (0.44 ft.³) or covers 2 m² (21.5 ft.²) at 6 mm (1/4") thickness. Addition of 7 kg (16 lbs.) of 9 mm (3/8") clean pea gravel produces 0.015 m³ (0.54 ft.³)

Continued over ....

W. R. MEADOWS OF CANADA
70 Hannant Court, Milton, ON L9T 5C1
Phone: (905) 878-4122 • Fax: (905) 878-4125
Montreal Sales: (877) 405-5186

Hampshire, IL / Cartersville, GA / York, PA / Fort Worth, TX
Benicia, CA / Pomona, CA / Goodyear, AZ / Milton, ON /
St. Albert, AB
www.wrmeadows.com

**Storage** Store indoors, off the ground. Keep dry for a shelf life of 12 months. Lumps in the material indicate poor storage and material should not be used.

## APPLICATION

### Preparation

Mechanically abrade existing substrate to remove all unsound concrete, but do not use excessive force which may cause micro fracturing. Prepare surface in accordance with ICRI Technical Guide No. 03730. Substrate must be structurally sound and free of grease, oil, dirt or any other contaminants that can adversely affect the bond. Prepared surface must be dust-free and have a sufficient profile to ensure adequate mechanical lock.

Saw cut repair zone edges to a depth of 6 mm (1/4") to avoid feathered edging.

Completely expose all steel in repair zone and abrade entire circumference of steel to a white metal finish.

Substrate must be saturated, but with no standing water (SSD condition). Repair zone surfaces must be primed with a slurry coat of MEADOW-CRETE H. Thoroughly scrub a thin layer of the slurry coat into the substrate with a stiff bristle brush. For enhanced bond prime (SSD) substrate with a slurry coat (2 parts MEADOW-CRETE H powder to 1 part ACRY-LOK). Placement of the repair mortar must proceed when the slurry is tacky. Do not allow the slurry to dry.

### Mixing

Place the water in the mixing vessel first, then slowly add the MEADOW-CRETE H. A mortar type mixer with rubber tipped blades is recommended as this type of mixing provides optimum blending. Smaller quantities may be mixed with an electric drill and Jiffy mixer blade at a 400 - 600 rpm speed. **DO NOT MIX BY HAND** as hand mixing will not produce properly blended material.

Mix only that amount of material which can be placed and finished within the working time of approximately 40 to 45 minutes at 21°C (70°F). Hot weather will reduce and cold weather will increase working time.

Do not over mix - total mixing time should not exceed 4 to 5 minutes.

### MIXING ORDER

- (a) Pour 3.0 litres (0.66 gallon) of clean water for each bag of MEADOW-CRETE H into the mixer.
- (b) With the mixer running add bag contents, and pea gravel if employed, into the water while mixing - mix to lump-free consistency.
- (c) Add up to an additional 0.3 litres (0.07 gallon) of water, to a maximum of 3.3 litres (0.73 gal.), to obtain trowelable consistency (water may vary somewhat if pea gravel is dry versus damp).

Do not retemper or add any admixtures.

### Placing

Immediately following mixing, place material onto the water saturated area to be patched. Following the preparation method previously detailed, follow immediately with a full depth placement (do not apply in lifts) spreading evenly with a shovel or screed. **DO NOT LET SCRUB COAT DRY PRIOR TO MORTAR PLACEMENT.**

Force material against the bottom and sides of the patch and compact well. Limit finishing, do not over-trowel, with hand steel trowelling. Allow to stiffen, then smooth with wood/sponge float or broom/burlap drag for rough finishing.

### Curing

Protect the patch against rapid mix water evaporation in sunny, windy, high temperature and low humidity application conditions. The use of EVAPRE™ Evaporation Retardant from W. R. MEADOWS may proceed immediately after screeding and/or between finishing operations. MEADOW-CRETE H must be cured in accordance with ACI 308 utilizing a suitable curing compound, such as #1100 or VOCOMP®-25 from W. R. MEADOWS. Protect from freezing and rain.

### Clean Up

Clean all tools and equipment after use with water. Cured material would have to be removed mechanically.

### SAFETY & TOXICITY

Prolonged contact with skin not recommended, use rubber gloves to avoid sensitivity to Portland cement. Avoid contact with the eyes, goggles are recommended. Wash thoroughly with water. See product label and Material Safety Data Sheet for additional information. Read and follow all instructions and precautions.

Proper application is the responsibility of the user. Field visits by W. R. MEADOWS personnel are for the purpose of making technical recommendations only, and are not to supervise or provide quality control on the job-site.

### SPECIFICATION CLAUSE

Section 03 01 30.71.

**FOR BEST PERFORMANCE, ENSURE MOST RECENT TECHNICAL DATA SHEET IS BEING USED ... VISIT OUR WEBSITE AT:**

[www.wrmeadows.com](http://www.wrmeadows.com)

2007-08-14



© SEALTIGHT is a registered trade mark of W. R. Meadows

**WARRANTY:** W. R. Meadows of Canada warrants that, at the time and place we make shipment, our materials will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTY, EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM OF TRADE OR OTHERWISE. As the exclusive remedy for breach of this Warranty, we will replace defective materials, provided, however, that the buyer examine the materials when received and promptly notify us in writing of any defect before the materials are used or incorporated into a structure. Three (3) months after W. R. Meadows of Canada has shipped the materials, all our Warranty and other duties with respect to the quality of the materials delivered shall conclusively be presumed to have been satisfied, all liability therefore terminates and no action for breach of any such duties may thereafter be commenced. W. R. Meadows of Canada shall in no event be liable for consequential damages. Unless otherwise agreed to in writing, no warranty is made with respect to materials not manufactured by W. R. Meadows of Canada. We cannot warrant or in any way guarantee any particular method of use or application or the performance of materials under any particular condition. Neither this Warranty nor our liability may be extended or amended by our salesmen, distributors or representatives, or by our distributor's representatives, or by any sales information or drawings.