



DATA SHEET NO. 3900-312

MEADOW-CRETE® OV

One Component Glass Fibre Reinforced Overhead and Vertical Patching Compound

DESCRIPTION

MEADOW-CRETE OV is a glass fibre reinforced cementitious patching compound designed for overhead and vertical applications. The polymer modified and silica fume enhanced formulation comes ready to use as a single component patching material, simply add the required amount of water and mix in an approved mixing device.

USE

Ideal for varying depths of patch and resurfacing of concrete substrates - ceilings, tunnel walls and roofs, foundations, abutments, bridges, etc. Suitable for both interior and exterior surfaces.

FEATURES

Ready to use . . . just add water, mix and place.

Excellent bond to rough and damp surfaces.

Superior resistance to freeze/thaw cycling and de-icing chemicals.

Easily applied by trowel, may be applied in layers for thicker applications.

CAUTION

Do not apply when the temperature is expected to fall below 5°C (40°F) within 24 hours after placement. Do not apply in unprotected areas when rain is imminent.

Minimum application thickness is 6 mm (1/4").

Do not use over moving joints or cracks or over active leaks.

PROPERTIES, typical at 21°C (70°F).

Table with 2 columns: Property Name and Value. Includes Working Time (15 to 20 minutes) and Compressive Strength (ASTM C 109-90 Modified) at 24, 3, 7, and 28 days.

Compressive strengths may vary due to temperature and weather conditions

Table with 2 columns: Property Name and Value. Includes Slant Shear Strength (ASTM C 882-87), Module of Rupture (ASTM C 27-40), Freeze/Thaw Resistance (ASTM C 666-A), Salt Scale Resistance, Rapid Chloride Penetration (AASHTO T277), and Water Absorption (7.6%).

STANDARDS

Agriculture and Agri-Food Canada accepted.

DATA

Table with 2 columns: Property Name and Value. Includes Packaged (22.7 kg), Yield (0.013 m³), and Storage instructions.

Continued over

W. R. MEADOWS OF CANADA

70 Hannant Court, Milton, ON L9T 5C1
Phone: (905) 878-4122 • Fax: (905) 878-4125

Montreal Sales: (877) 405-5186

Hampshire, IL / Cartersville, GA / York, PA / Fort Worth, TX
Benicia, CA / Pomona, CA / Goodyear, AZ / Milton, ON /
St. Albert, AB
www.wrmeadows.com

APPLICATION

Preparation

Mechanically abrade existing substrate to remove all unsound concrete, but do not use excessive force which may cause micro fracturing. Prepare surface in accordance with ICRI Technical Guide No. 03730. Substrate must be structurally sound and free of grease, oil, dirt or any other contaminants that can adversely affect the bond. Prepared surface must be dust-free and have a sufficient profile to ensure adequate mechanical lock.

Saw cut repair zone edges to a depth of 6 mm (1/4") to avoid feathered edging.

Completely expose all steel in repair zone and abrade entire circumference of steel to a white metal finish.

Substrate must be saturated, but with no standing water (SSD condition). Repair zone surfaces must be primed with a slurry coat of MEADOW-CRETE OV. Thoroughly scrub a thin layer of the slurry coat into the substrate with a stiff bristle brush. For enhanced bond prime (SSD) substrate with a slurry coat (2 parts MEADOW-CRETE OV powder to 1 part ACRY-LOK). Placement of the repair mortar must proceed when the slurry is tacky. Do not allow the slurry to dry.

Mixing

Add the MEADOW-CRETE OV to the water in the mixing vessel. A mortar type mixer with rubber tipped blades is recommended as this type of mixing provides optimum blending. Smaller quantities may be mixed with an electric drill and Jiffy mixer blade at a 400 - 600 rpm speed.

DO NOT MIX BY HAND as hand mixing will not produce properly blended material. Mix only that amount of material which can be placed and finished within the working time of approximately 15 to 20 minutes at 21°C (70°F). Hot weather will reduce and cold weather will increase working time. Do not over mix - total mixing time should not exceed 4 to 5 minutes.

MIXING ORDER

- (a) Pour 4.0 litres (0.88 Imperial gallon) of clean water for each bag of MEADOW-CRETE OV into the mixer.
- (b) With the mixer running add bag contents gradually and mix to a lump-free consistency.
- (c) Add up to an additional 0.3 litres (0.07 gallons) of water, to a maximum of 4.3 litres (0.95 gal.), to obtain desired consistency.

Do not re-temper or add any admixtures.

Placing

Immediately following mixing, place material onto the water saturated area to be patched, following the preparation method previously detailed. DO NOT LET SCRUB COAT DRY PRIOR TO MORTAR PLACEMENT.

On rough surfaces fill in the voids first forcing material against bottom and sides of the patch. The material develops a fast set which allows the application of consecutive layers approximately 10 to 15 minutes apart - because of temperature and weather variances make sure that each layer develops enough bond strength to support weight of new layers.

Smooth final layer with wood or sponge float and close with a steel trowel if necessary. Do not overwork surface.

Curing

Protect the patch against rapid mix water evaporation in sunny, windy, high temperature and low humidity application conditions. The use of EVAPRE™ Evaporation Retardant from W. R. MEADOWS may proceed immediately after screeding and/or between finishing operations. MEADOW-CRETE OV must be cured in accordance with ACI 308 utilizing a suitable curing compound, such as #1100 or VOCOMP®-25. from W. R. MEADOWS. Protect from freezing and rain.

Clean Up

Clean all tools and equipment after use with water. Cured material would have to be removed mechanically.

Proper application is the responsibility of the user. Field visits by W. R. MEADOWS' personnel are for the purpose of making technical recommendations only, and are not to supervise or provide quality control on the job-site.

SAFETY & TOXICITY

Prolonged contact with skin not recommended, use rubber gloves to avoid sensitivity to Portland cement. Avoid contact with the eyes, goggles are recommended. Wash thoroughly with water. See product label and Material Safety Data Sheet for additional information. Read and follow all instructions and precautions.

SPECIFICATION CLAUSE

Section 03 01 30.71

FOR BEST PERFORMANCE, ENSURE MOST RECENT TECHNICAL DATA SHEET IS BEING USED ... VISIT OUR WEBSITE AT:

www.wrmeadows.com

2007-08-14



® SEAL TIGHT is a registered trade mark of W. R. Meadows

WARRANTY: W. R. Meadows of Canada warrants that, at the time and place we make shipment, our materials will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTY, EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM OF TRADE OR OTHERWISE. As the exclusive remedy for breach of this Warranty, we will replace defective materials, provided, however, that the buyer examine the materials when received and promptly notify us in writing of any defect before the materials are used or incorporated into a structure. Three (3) months after W. R. Meadows of Canada has shipped the materials, all our Warranty and other duties with respect to the quality of the materials delivered shall conclusively be presumed to have been satisfied, all liability therefore terminates and no action for breach of any such duties may thereafter be commenced. W. R. Meadows of Canada shall in no event be liable for consequential damages. Unless otherwise agreed to in writing, no warranty is made with respect to materials not manufactured by W. R. Meadows of Canada. We cannot warrant or in any way guarantee any particular method of use or application or the performance of materials under any particular condition. Neither this Warranty nor our liability may be extended or amended by our salesmen, distributors or representatives, or by our distributor's representatives, or by any sales information or drawings.