



DATA SHEET NO. 7100-201

PROTECTION COURSE (VIBRAFLEX® PC)
Waterproofing Protection Board

DESCRIPTION

PROTECTION COURSE (VIBRAFLEX PC) waterproofing protection board is a semi-flexible core board composed of a mineral-fortified asphaltic core between two outside layers of asphalt-impregnated fibreglass mat.

USES

PROTECTION COURSE (VIBRAFLEX PC) is used for protection of waterproofing membranes from damage by backfill or construction traffic.

FEATURES/BENEFITS

- Absorbs the impact of placing concrete or asphalt and normal jobsite traffic on waterproofed slabs.
Protects membranes from penetration by sharp aggregate during backfilling of foundation walls.
Fully compatible with built-up dampproofing and cold-applied or hot-applied waterproofing membranes...

PACKAGING

Table with 3 columns: No. (70, 150), Thickness (3.2 mm, 6.4 mm), and Dimensions (914 mm x 1.5 m, 1219.2 mm x 1.5 m)

Custom sizes and thicknesses [4.8 mm (3/16"), 9.5 mm (3/8"), 12.7 mm (1/2")] available upon request.

SPECIFICATIONS

- ASTM D6506, Type 2, Class B
Type 70 Approved by the Ministry of Transportation, Quebec

TECHNICAL DATA

Load required to compress Type 150 to 50% of original thickness - 19.3 MPa (2800 psi).

ASTM D 6506

PROTECTION BOARD REQUIREMENTS

Table with 3 columns: Property (Puncture Strength, Thickness, Water Absorption, Asphalt % by weight, Resistance to Decay) and two rows (Type 70, Type 150)

APPLICATION

Install PROTECTION COURSE (VIBRAFLEX PC) to form a continuous protective layer over the membrane waterproofing. Sheets are easily cut with a roofer's knife for fitting around protrusions.

Horizontal Surfaces ... Use Type 70 for light duty installations.

Use Type 150 for landscaped deck areas and under coarse aggregates. Lay PROTECTION COURSE (VIBRAFLEX PC) on the membrane in accordance with membrane manufacturer's instructions.

Edges of sheets adjacent to a vertical surface shall lie within 6.4 mm (1/4") of the vertical surface. Cut sheets to fit, as necessary. Alternatively, butt sheet edges and cover with fibreglass tape [152 mm (6") wide] laid in hot asphalt.

Continued Over ...

W. R. MEADOWS OF CANADA
70 Hannant Court, Milton, ON L9T 5C1
Phone: (905) 878-4122 Fax: (905) 878-4125

Montreal Sales: (877) 405-5186

Hampshire, IL / Cartersville, GA / York, PA / Fort Worth, TX
Benicia, CA / Pomona, CA / Goodyear, AZ / Milton, ON /
St. Albert, AB
www.wrmeadows.com

Vertical Surfaces ... Use Type 70 where backfill contains no coarse elements. Use Type 150 where backfill contains coarse gravel or stone. Install PROTECTION COURSE (VIBRAFLEX PC) as soon as permitted by membrane manufacturer.

Place PROTECTION COURSE (VIBRAFLEX PC) sheets against the wall at the footing with longer dimension horizontal. Butt the sheets and hold in place while backfill is placed in 609 - 762 mm (24" - 30") lifts. Continue up the wall in similar manner, staggering the vertical joints of PROTECTION COURSE (VIBRAFLEX PC), backfilling and compacting successive lifts.

An alternative method is to adhere PROTECTION COURSE (VIBRAFLEX PC) to the membrane before placing backfill. Consult the membrane manufacturer for a compatible adhesive. Consider the use of DETAIL STRIP from W. R. MEADOWS.

PRECAUTIONS

If PROTECTION COURSE (VIBRAFLEX PC) is to be adhered to the waterproofing membrane, obtain membrane manufacturer's recommendation as to adhesive.

As PROTECTION COURSE (VIBRAFLEX PC) is an effective vapour barrier, do not place on wet membranes or adhesives requiring solvent evaporation.

Product is not to be used in any application where contact with a coal tar based waterproofing system is possible.

If PROTECTION COURSE (VIBRAFLEX PC) is to be nailed to a vertical surface, obtain membrane manufacturer's approvals and recommendations for sealing resulting membrane punctures.

Where taped joints are used with tape set in hot asphalt, consult membrane manufacturer regarding compatibility, etc.

Use only rubber-tired construction equipment.

It is advisable to cover PROTECTION COURSE (VIBRAFLEX PC) within 48 hours after installation. Exposure of the complete waterproofing system to continuous jobsite damage should be limited to as short a time as possible.

If PROTECTION COURSE (VIBRAFLEX PC) is left exposed to the elements for an extended period of time, it will oxidize slightly on the surface and turn a grey colour. This will not impede its performance as a protection board. However, it should be covered as soon as possible.

Flood coat PROTECTION COURSE (VIBRAFLEX PC) with roofing asphalt whenever it will be exposed or partially exposed on a permanent basis to the elements, e.g., under concrete pavers or under a gravel drainage course.

MASTERFORMAT NUMBER AND TITLE

07 10 00 – Dampproofing and Waterproofing

LEED INFORMATION

May help contribute to LEED credits:

- IEQ Credit 3.1: Construction IAQ Management Plan: During Construction
- IEQ Credit 7.1: Thermal Comfort - Design
- MR Credit 2: Construction Waste Management
- MR Credit 4: Recycled Content
- MR Credit 5: Regional Materials

For most recent data sheet, further LEED information, and MSDS, visit www.wrmeadows.com.



2012-09-10

© SEALTIGHT is a registered trade mark of W. R. Meadows

WARRANTY: W. R. Meadows of Canada warrants that, at the time and place we make shipment, our materials will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTY, EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM OF TRADE OR OTHERWISE. As the exclusive remedy for breach of this Warranty, we will replace defective materials, provided, however, that the buyer examine the materials when received and promptly notify us in writing of any defect before the materials are used or incorporated into a structure. Three (3) months after W. R. Meadows of Canada has shipped the materials, all our Warranty and other duties with respect to the quality of the materials delivered shall conclusively be presumed to have been satisfied, all liability therefore terminates and no action for breach of any such duties may thereafter be commenced. W. R. Meadows of Canada shall in no event be liable for consequential damages. Unless otherwise agreed to in writing, no warranty is made with respect to materials not manufactured by W. R. Meadows of Canada. We cannot warrant or in any way guarantee any particular method of use or application or the performance of materials under any particular condition. Neither this Warranty nor our liability may be extended or amended by our salesmen, distributors or representatives, or by our distributor's representatives, or by any sales information or drawings.