



## DATA SHEET NO. 7500-610

### 610 ALL WEATHER FIBRATED ROOF COATING

#### DESCRIPTION

610 ALL WEATHER FIBRATED ROOF COATING is a solvent cutback type roof coating that provides a tough, flexible waterproof coating.

#### USES

610 ALL WEATHER FIBRATED ROOF COATING is designed for use as a re-roofing material over existing built-up roofs and other roof surfaces to prolong life. It can be applied over asphalt, wood, gypsum, and steel.

#### FEATURES/BENEFITS

- Provides a tough, flexible coating.
- Prolongs life of existing roof.
- Can be applied to multiple substrate types.

#### PACKAGING

18.9 Litre Pails

#### COVERAGE

Coverage is 2.1 m<sup>2</sup>/L - 3.1 m<sup>2</sup>/L (100 ft.<sup>2</sup>/gal. - 150 ft.<sup>2</sup>/gal.) depending on porosity of the surface.

#### SHELF LIFE

When stored indoors in original, unopened containers at temperatures between 4° - 32° C, optimum performance and best use is obtained within two years of date of manufacture.

#### SPECIFICATIONS

Complies with CAN/CGSB-37.8-M88. To be applied according to CGSB 37-GP-14M.

#### TECHNICAL DATA

Colour	Black
Solids	61%
Weight	1 kg/L (10 lb./gal.)
Drying Time	
Touch dry	3.5 hours
Firm dry	24 hours
Application Temperature	-20° C Minimum
Flammability	
Wet	Flammable
Dry	Burns
Moisture Permeance	.05 perms at 3.2 mm (1/8") film
Water Content	1% maximum

#### APPLICATION

**Surface Preparation ...** Surface shall be firm and free from loose particles, cracks, grease, oil, frost, snow, ice, and other foreign matter. Patch problem areas with 625 PLASTIC CEMENT from W. R. MEADOWS. At temperatures below 4° C, apply a prime coat of 600 ASPHALT PRIMER from W. R. MEADOWS.

**Mixing ...** Mix thoroughly before application.

**Application Method ...** Apply by brush or sprayer at a minimum rate of 3.1 m<sup>2</sup>/L (150 ft.<sup>2</sup>/gal). If necessary, apply a second coat.

#### PRECAUTIONS

Avoid use where solvent odours are objectionable. If the material has thickened due to low temperatures, leave the container in a heated building overnight. DO NOT HEAT WITH AN OPEN FLAME. Product contains flammable solvents. Use in a well-ventilated area. KEEP AWAY FROM HEAT AND OPEN FLAMES.

#### MASTERFORMAT NUMBER AND TITLE

07 50 00 – Membrane Roofing

Continued over ...

### W. R. MEADOWS® OF CANADA

70 Hannant Court, Milton, ON L9T 5C1

38 Rayborn Crescent, St. Albert, AB T8N 4B1

(800) 342-5976

Montreal Sales: (877) 405-5186

Hampshire, IL / Cartersville, GA / York, PA / Fort Worth, TX  
Benicia, CA / Pomona, CA / Goodyear, AZ / Milton, ON  
St. Albert, AB  
[www.wrmeadows.com](http://www.wrmeadows.com)

## LEED INFORMATION

- MRc9: Construction and Demolition Waste Management

2018-01-23



© SEALTIGHT is a registered trade mark of W. R. Meadows

**WARRANTY:** W. R. Meadows of Western Canada warrants that, at the time and place we make shipment, our materials will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTY, EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM OF TRADE OR OTHERWISE. As the exclusive remedy for breach of this Warranty, we will replace defective materials, provided, however, that the buyer examine the materials when received and promptly notify us in writing of any defect before the materials are used or incorporated into a structure. Three (3) months after W. R. Meadows of Western Canada has shipped the materials, all our Warranty and other duties with respect to the quality of the materials delivered shall conclusively be presumed to have been satisfied, all liability therefore terminates and no action for breach of any such duties may thereafter be commenced. W. R. Meadows of Western Canada shall in no event be liable for consequential damages. Unless otherwise agreed to in writing, no warranty is made with respect to materials not manufactured by W. R. Meadows of Western Canada. We cannot warrant or in any way guarantee any particular method of use or application or the performance of materials under any particular condition. Neither this Warranty nor our liability may be extended or amended by our salesmen, distributors or representatives, or by our distributor's representatives, or by any sales information or drawings.