

CEM-KOTE CW PLUS (2ND LAYER RATE OF 1.4lbs/yd² (.75kg/m²) APPLIED) (TOTAL RATE OF 2.8lbs/yd² (1.5kg/m²) APPLIED) (APPLIED TO PROPERLY PREPARED SURFACE)

CEM-KOTE CW PLUS (1ST LAYER RATE OF 1.4lbs/yd² (.75kg/m²) APPLIED) (APPLIED TO PROPERLY PREPARED SURFACE)

CEM-KOTE FLEX ST (63 MILS) (DETAILING LAYER) (APPLIED TO PROPERLY PREPARED SURFACE)

MEADOW-CRETE OV (2" x 2" (50.8mm x 50.8mm) - 2½" x 2½" (63.5mm x 63.5mm) COVE) (APPLY TO WET EDGE FIBRE-PRIME & SOUND SUBSTRATE)

STEEL PIPE

EXISTING- REMOVE ALL RUST BEFORE APPLICATION.

NEW- CLEAN WITH TSP SOLUTION TO REMOVE ANY OIL RESIDUE (TEST BOND OF FIBRE-PRIME IF UNSURE)

PAINTED- ABRABE USING SAND PAPER AND PRESSURE WASH DUST AWAY

FIBRE-PRIME (FOR PROPER BOND) (APPLY TO PROPERLY PREPARED & SOUND SUBSTRATE)

NOTE: DETAIL IS A GUIDE FOR INSTALLATIONS OF W. R. MEADOWS PRODUCTS ONLY. DETAIL MUST BE REVIEWED AND VERIFIED BY A DESIGN PROFESSIONAL FOR SUITABILITY ON THE PROJECT. W. R. MEADOWS DOES NOT ASSUME RESPONSIBILITY FOR ERRORS IN DESIGN OR ENGINEERING.



TITLE:

**CEM-KOTE CW PLUS- STEEL PIPE PENETRATION
(MEADOW-CRETE) (CEM-KOTE FLEX ST)**

SCALE: NTS
DATE: MAY 12, 2022

DWG NO.: CKOTE-09